

# Comparative Study of Accelerating Admixtures on Properties of Concrete

D.Selvaganesh<sup>1</sup>, R.Prabhakaran<sup>2</sup>, M.Mohana Prasanna<sup>3</sup>, M.Mohamed Fayyaz<sup>4</sup>

U.G. Student, Department of Civil Engineering, Fatima Michael College of Engineering and Technology, Madurai,  
Tamil Nadu, India<sup>1,2,3</sup>,

Assistant Professor, Department of Civil Engineering, Fatima Michael College of Engineering and Technology,  
Madurai, Tamil Nadu, India<sup>4</sup>

**ABSTRACT:** Accelerating admixtures affect the rates of reactions between cement and water to give an overall increase in the hydration rate. Thus, the use of accelerators in concrete provides a shortening of setting time and/or an increase in early strength development. In this paper the issue of slow down setting and hardening of concrete or addressed by the use of accelerating admixture are (sodium nitrite and calcium nitrite) in concrete. Sodium nitrite and Calcium nitrite was added in four samples having the quantity of 1%, 1.5 %, 2%, 2.5% and 3% by weight of cement was taken as mix -1 and mix -2. The concrete samples were tested 7, 14 and 28 days of Compressive strength, Split tensile strength and Flexural strength. The concrete specimens were laid for M25 grade of concrete.

**KEYWORDS:** Admixture, Sodium nitrite, Calcium nitrite, Compressive strength, Split tensile strength and Flexural strength.

## I. INTRODUCTION

The rates of chemical reactions between clinker materials in cements and water, often referred to as cement hydration reactions, may be altered by adding small amounts of chemical substances to the cement-water mix. Substances affecting these rates to give an overall increase in the hydration rate, i.e. an accelerating effect, are termed accelerating admixtures or simply accelerators. Hence, an accelerator is added to concrete for the purpose of shortening setting time and/or increasing early strength development. In the first case the main action of the accelerator occurs in the plastic state of the cement paste, while in the latter case the accelerator acts primarily in the hardened state. Some accelerators affect either setting or hardening, while several accelerate both setting and hardening.

The aim of this report is to provide an overview of chemical admixtures reported to accelerate setting and/or hardening of Ordinary Portland Cement (OPC) and OPC based concrete. Both accelerators for normal concrete.

As almost 100 % of concrete accelerators on the market are in liquid form (a few are sold as readily soluble powders), and the fact that most operators at concrete mixing plants prefer to handle accelerators in liquid form, this report does not treat powder accelerators insoluble in water. Accelerating admixtures can be used to increase either the rate of stiffening or setting of the concrete or the rate of hardening and early strength gain to allow earlier formwork striking and demoulding. Most accelerators achieve one rather than both of these functions.

Calcium Nitrite has a great variety of uses. It can be use as antifreeze due to its high solubility, either in solution or powder. It can promote the hydration of minerals in cement using this antifreeze at sub freezing temperature; the operative temperature can be reduced to  $-20^{\circ}\text{C}$ . It also works as metal corrosion inhibitor, so it can protect steel in concrete buildings and structures from rust, to extend life of specific buildings.

# International Journal of Innovative Research in Science, Engineering and Technology

(A High Impact Factor, Monthly, Peer Reviewed Journal)

Visit: [www.ijirset.com](http://www.ijirset.com)

Vol. 7, Issue 2, February 2018

Sodium nitrite is an effective corrosion inhibitor and is used as an additive in industrial greases as an aqueous solution in closed loop cooling systems and in a molten state as a heat transfer medium.

In this research sodium nitrite and calcium nitrite is used as accelerating admixtures in the quantity range of 1% to 2.5% by weight of cement. So it can be arising the heat evolution and strength development. It behaves as a stimulant in the hydration of tricalcium silicate ( $C_3S$ ) and tricalcium aluminate ( $C_3A$ ). Concrete sample with various percentages of sodium nitrite and calcium nitrite were tested for Compressive strength, Split tensile strength and Flexural strength.

## II. MATERIAL USED

**Cement:** Cement is a binder, a substance used for construction that sets, hardens and adheres to other materials, binding them together. Cement is seldom used on its own, but rather to bind sand and gravel (aggregate) together. Cement is used with fine aggregate to produce mortar for masonry, or with sand and gravel aggregates to produce concrete. The project deals with ordinary Portland cement 43 grade conforming to IS 8112 was used throughout the work.

**Fine aggregate:** It is the aggregate most of which passes 4.75 mm IS sieve and contains only so much coarser as is permitted by specification. According to source fine aggregate may be described as:

- Natural Sand– it is the aggregate resulting from the natural disintegration of rock and which has been deposited by streams or glacial agencies
- Crushed Stone Sand– it is the fine aggregate produced by crushing hard stone.
- Crushed Gravel Sand– it is the fine aggregate produced by crushing natural gravel.

According to size the fine aggregate may be described as coarse sand, medium sand and fine sand. IS specifications classify the fine aggregate into four types according to its grading as fine aggregate of grading Zone-1 to grading Zone-4. The four grading zones become progressively finer from grading Zone-1 to grading Zone-4. 90% to 100% of the fine aggregate passes 4.75 mm IS sieve and 0 to 15% passes 150 micron IS sieve depending upon its grading zone.

**Coarse aggregate:** It is the aggregate most of which is retained on 4.75 mm IS sieve and contains only so much finer material as is permitted by specification. According to source, coarse aggregate may be described as:

- Uncrushed Gravel or Stone– it results from natural disintegration of rock
- Crushed Gravel or Stone– it results from crushing of gravel or hard stone.
- Partially Crushed Gravel or Stone– it is a product of the blending of the above two aggregate.

According to size coarse aggregate is described as graded aggregate of its nominal size i.e. 40 mm, 20 mm, 16 mm and 12.5 mm etc. for example a graded aggregate of nominal size 20 mm means an aggregate most of which passes 20 mm IS sieve.

A coarse aggregate which has the sizes of particles mainly belonging to a single sieve size is known as single size aggregate. For example 20 mm single size aggregate mean an aggregate most of which passes 20 mm IS sieve and its major portion is retained on 10 mm IS sieve.

**Sodium Nitrite:** Sodium nitrite is the inorganic compound with the chemical formula  $NaNO_2$ . It is a white to slightly yellowish crystalline powder that is very soluble in water and is hygroscopic. It is in the form of fine powder so it was easily added in the mix for purpose of increasing the properties of concrete. Fig -1 shows sodium nitrite and Fig -2 shows mixed ingredients of concrete for mix proportion.

# International Journal of Innovative Research in Science, Engineering and Technology

(A High Impact Factor, Monthly, Peer Reviewed Journal)

Visit: [www.ijirset.com](http://www.ijirset.com)

Vol. 7, Issue 2, February 2018

**Calcium Nitrite:** Calcium nitrite can be produced by different synthesis processes. One is by reacting hydrated lime with NOX gas, which typically comes from a nitric acid plant. . It is in the form of fine powder so it was easily added in the mix for purpose of increasing the properties of concrete. Fig -3 shows calcium nitrite and Fig -4 shows mixed ingredients of concrete for mix proportion.

**TABLE 1: PHYSICAL PROPERTIES OF MATERIALS**

S.NO	PROPERTY	TEST RESULTS	IS - SPECIFICATION
1	<b>Cement : 43 grade OPC cement</b>		<b>IS 8112: 1988</b>
	Specific gravity	3.18	
	Initial setting time	30 min	
	Final setting time	5 hrs 10 min	
2	<b>Physical properties of fine aggregate</b>		<b>IS 383: 1970</b>
	Specific gravity	2.78	
	Fineness modulus	2.48	
	Bulk density	17KN/m <sup>3</sup>	
	Grading	Zone – 2	
3	<b>Physical properties of coarse aggregate (20mm)</b>		<b>IS 383: 1970</b>
	Specific gravity	2.78	
	Fineness modulus	6.02	



**Fig: 1 Sodium Nitrite**



**Fig: 2 Calcium Nitrite**

# International Journal of Innovative Research in Science, Engineering and Technology

(A High Impact Factor, Monthly, Peer Reviewed Journal)

Visit: [www.ijirset.com](http://www.ijirset.com)

Vol. 7, Issue 2, February 2018

## III. EXPERIMENTAL INVESTIGATION

**Mix proportions:** the concrete mix design was proposed by using IS 10262. The grade of concrete has been laid M-25 with water cement ratio 0.50

**TABLE 2: Mix proportion - 1**

S.No	Sodium Nitrite	Water to cement ratio	Water (kg/m <sup>3</sup> )	Cement (kg/m <sup>3</sup> )	Sodium Nitrite (kg/m <sup>3</sup> )	Fine Aggregate (kg/m <sup>3</sup> )	Coarse Aggregate (kg/m <sup>3</sup> )	Slump value (mm)
1	0%	0.50	192	383	0.0	834	1062	30.5
2	1%	0.50	192	383	3.83	834	1062	32
3	1.5%	0.50	192	383	5.74	834	1062	33.5
4	2%	0.50	192	383	7.66	834	1062	34
5	2.5%	0.50	192	383	9.57	834	1062	36
6	3%	0.50	192	383	11.49	834	1062	30

**TABLE 3: Mix proportion - 2**

S.No	Calcium Nitrite	Water to cement ratio	Water (kg/m <sup>3</sup> )	Cement (kg/m <sup>3</sup> )	Calcium Nitrite (kg/m <sup>3</sup> )	Fine Aggregate (kg/m <sup>3</sup> )	Coarse Aggregate (kg/m <sup>3</sup> )	Slump value (mm)
1	0%	0.50	192	383	0.0	834	1062	30.5
2	1%	0.50	192	383	3.83	834	1062	31.7
3	1.5%	0.50	192	383	5.74	834	1062	33.0
4	2%	0.50	192	383	7.66	834	1062	34.6
5	2.5%	0.50	192	383	9.57	834	1062	36.0
6	3%	0.50	192	383	11.49	834	1062	29.0

**Test on fresh concrete:** Slump cone test used extensively in site work all over the world. Very useful in detecting variations in the uniformity of a mix of given nominal proportions. Rich mixes behave satisfactorily, their slump being sensitive to variations in workability. The slump test were performed according to IS 1199- 1959.

**Test on hardened concrete:** The main destructive tests on hardened concrete are as follows.

- Cube test: Compressive strength of hardened concrete is done by cube test. More details about Cube. The size of the concrete cube size as 150mm × 150mm × 150mm.
- Tensile splitting test on concrete cylinders as a size of 150mm × 300mm.
- Flexure test on concrete as a size of 500mm × 100mm × 100mm.

## IV. RESULTS AND DISCUSSION

**Compressive strength:** Compression strength is the capacity of a material or structure to withstand loads tending to reduce size, as opposed to tensile strength, which withstands loads tending to elongate. In other words, compressive strength resists compression (being pushed together), whereas tensile strength resists tension (being pulled apart). In the study of strength of materials, tensile strength, compressive strength, and shear strength can be analysed independently. These tests were carried out for 7, 14 and 28 days. An increasing compressive strength was observed up to 2.5% of

# International Journal of Innovative Research in Science, Engineering and Technology

(A High Impact Factor, Monthly, Peer Reviewed Journal)

Visit: [www.ijirset.com](http://www.ijirset.com)

Vol. 7, Issue 2, February 2018


sodium nitrite as a admixture has been decreased in compressive strength and 2.5% of calcium nitrite has been slightly increased.

**TABLE 4: Compressive strength test results**

S.No	% of Accelerating admixture	Strength attained by Sodium nitrite (N/mm <sup>2</sup> )			Strength attained by Calcium nitrite (N/mm <sup>2</sup> )		
		7 days	14 days	28 days	7 days	14 days	28 days
1	0	13.90	16.00	26.10	13.90	16.00	26.10
2	1	16.20	17.30	27.80	16.00	17.15	27.85
3	1.5	16.70	17.70	27.90	16.50	17.80	27.95
4	2	17.30	18.50	28.00	17.00	18.90	28.15
5	2.5	19.50	22.00	28.50	17.50	19.50	28.60
6	3	14.10	13.60	24.90	14.00	16.00	24.00



**Fig: 3 Compressive strength Test**



**Fig: 4 Compressive strength results for sodium nitrite**

# International Journal of Innovative Research in Science, Engineering and Technology

(A High Impact Factor, Monthly, Peer Reviewed Journal)

Visit: [www.ijirset.com](http://www.ijirset.com)

Vol. 7, Issue 2, February 2018




Fig: 5 compressive strength results for calcium nitrite

**Split tensile strength:** The tensile strength of concrete is one of the basic and important properties. Splitting tensile strength test on concrete cylinder is a method to determine the tensile strength of concrete. The concrete is very weak in tension due to its brittle nature and is not expected to resist the direct tension. The concrete develops cracks when subjected to tensile forces. Thus, it is necessary to determine the tensile strength of concrete to determine the load at which the concrete members may crack.

TABLE 5: Split tensile strength test results

S.No	% of Accelerating admixture	Strength attained by Sodium nitrite (N/mm <sup>2</sup> )			Strength attained by Calcium nitrite (N/mm <sup>2</sup> )		
		7 days	14 days	28 days	7 days	14 days	28 days
1	0	2.01	3	3.2	2.01	3	3.2
2	1	2.5	3.8	3.31	2.2	2.6	2.8
3	1.5	2.51	3.80	3.36	2.23	2.72	2.81
4	2	2.66	3.82	3.8	2.5	2.8	3
5	2.5	2.67	3.4	3.6	2.8	2.81	3.33
6	3	1.77	2.39	2.84	1.45	2.01	2.15




Fig: 6 split tensile strength

## International Journal of Innovative Research in Science, Engineering and Technology


(A High Impact Factor, Monthly, Peer Reviewed Journal)

Visit: [www.ijirset.com](http://www.ijirset.com)

Vol. 7, Issue 2, February 2018



**Fig: 7 split tensile strength results for sodium nitrite**



**Fig: 8 split tensile strength results for calcium nitrite**

**Flexural strength test:** The flexural strength would be the same as the tensile strength if the material were homogeneous. In fact, most materials have small or large defects in them which act to concentrate the stresses locally, effectively causing a localized weakness. When a material is bent only the extreme fibers are at the largest stress so, if those fibers are free from defects, the flexural strength will be controlled by the strength of those intact 'Fibers'. However, if the same material was subjected to only tensile forces then all the fibers in the material are at the same stress and failure will initiate when the weakest fibre reaches its limiting tensile stress.



**Fig: 9 Flexural strength**

# International Journal of Innovative Research in Science, Engineering and Technology


(A High Impact Factor, Monthly, Peer Reviewed Journal)

Visit: [www.ijirset.com](http://www.ijirset.com)


Vol. 7, Issue 2, February 2018

**TABLE 6: Flexural strength test results**

S.No	% of Accelerating admixture	Strength attained by Sodium nitrite (N/mm <sup>2</sup> )			Strength attained by Calcium nitrite (N/mm <sup>2</sup> )		
		7 days	14 days	28 days	7 days	14 days	28 days
1	0	1.34	2.36	3.33	1.34	2.36	3.33
2	1	1.36	2.45	3.45	1.4	2.46	2.85
3	1.5	1.42	2.49	3.6	1.56	2.53	3.46
4	2	1.54	2.51	3.64	1.7	2.55	3.51
5	2.5	1.59	2.9	4.1	1.78	2.61	3.55
6	3	1.23	2.1	3	1.1	2.14	2.07



**Fig: 9 Flexural strength results for sodium nitrite**



**Fig: 10 Flexural strength results for calcium nitrite**



# International Journal of Innovative Research in Science, Engineering and Technology

(A High Impact Factor, Monthly, Peer Reviewed Journal)

Visit: [www.ijirset.com](http://www.ijirset.com)

Vol. 7, Issue 2, February 2018

## V. CONCLUSION

On the basis of results obtained, following conclusions are drawn:

1. For the normal mix of concrete the compressive strength of the concrete was gained as 13.9, 16.01, 26.10 N/mm<sup>2</sup> has been achieved at 7, 14 & 28 days.
2. For the 2.5% of sodium nitrite added in the concrete & achieved the strength as 40.28%, 37.5% & 9.19% increase in compressive strength of concrete with respect to the reference mix at 7, 14 & 28 days.
3. For the 2.5% of calcium nitrite added in the concrete & achieved the strength as 10.6%, 21.8% & 9.5% increase in compressive strength of concrete with respect to the reference mix at 7, 14 & 28 days.
4. By the comparison of both the accelerating admixtures the greater compressive strength is achieved in the concrete by the addition of optimum dosage level (i.e. 2.5%) of sodium nitrite.
5. For the normal mix of concrete the split tensile strength of the concrete was gained as 2.01, 3, 3.2 N/mm<sup>2</sup> has been achieved at 7, 14 & 28 days.
6. For the 2.5% of sodium nitrite added in the concrete & achieved the strength as 32.8%, 13.33% & 12.5% increase in split tensile strength of concrete with respect to the reference mix at 7, 14 & 28 days.
7. For the 2.5% of calcium nitrite added in the concrete & achieved the strength as 39.3%, 6.33% & 4% increase in split tensile strength of concrete with respect to the reference mix at 7, 14 & 28 days.
8. By the comparison of both the accelerating admixtures the greater split tensile strength is achieved in the concrete by the addition of optimum dosage level (i.e. 2.5%) of sodium nitrite.
9. For the normal mix of concrete the flexural strength of the concrete was gained as 1.34, 2.36, 3.33 N/mm<sup>2</sup> has been achieved at 7, 14 & 28 days.
10. For the 2.5% of sodium nitrite added in the concrete & achieved the strength as 18.65%, 22.88% & 23.12% increase in flexural strength of concrete with respect to the reference mix at 7, 14 & 28 days.
11. For the 2.5% of calcium nitrite added in the concrete & achieved the strength as 32.8%, 10.59% & 6% increase in flexural strength of concrete with respect to the reference mix at 7, 14 & 28 days.
12. By the comparison of both the accelerating admixtures the greater flexural strength is achieved in the concrete by the addition of optimum dosage level (i.e. 2.5%) of sodium nitrite.
13. An increase of compressive strength, split tensile strength and flexural strength at 7, 14 and 28 days corresponding to 2.5% sodium nitrite addition notifies its absolute possibility of usage as accelerating admixture.
14. Sodium nitrite can be used as accelerating admixture particularly in cold climate at 2.5% dosage by weight of cement without any harmful effects.
15. Calcium nitrite can also be used as accelerating admixture but sufficient strength is not attained when compared to the sodium nitrite.

## REFERENCES

- [1] Effect of a Retarding Admixture on the Setting Time of Cement Pastes in Hot Weather.
- [2] Annual book of ASTM Standards (1979), part 13, ASTM C 191 – 77: Standard test method for time of setting of hydraulic cement. ASTM Race St. Philadelphia, pa. 19103.
- [3] Baradan B. (1998). Construction Materials –II (5th.ED). Dokuz Eylul University, Technical faculty publication section, Izmir Turkey.
- [4] 43 Grade Ordinary Portland cement – Specification. IS 8112:1989, Bureau of Indian Standards, New Delhi.
- [5] Specification for Coarse and Fine Aggregates from Natural Sources for Concrete. IS: 383-1970, Bureau of Indian Standards, New Delhi.
- [6] Recommended Guidelines for Concrete Mix Design. IS: 10262-1982, Bureau of Indian Standards, New Delhi.
- [7] Methods of Sampling and Analysis of Concrete. IS: 1199-1959, Bureau of Indian Standards, New Delhi.
- [8] Methods of Tests for Strength of Concrete. IS: 516-1959, Bureau of Indian Standards, New Delhi.
- [9] Splitting Tensile Strength of concrete – Methods of test. IS 5816:1999.
- [10] Pierre Richard, Marcel Cheyrezy, (1995), "Composition of Reactive Powder Concrete", Cement and Concrete Research Journal, 25(7), pp 1501-1511.
- [11] The American Concrete Institute, Committee Report ACI 212.3R-04, Chemical Admixtures for Concrete, 2004.
- [12] Scian A N et al, Mechanochemical activation of high alumina cements – Hydration behaviour. I, Cement and Concrete Research, 21, 1991, pp 51-60.



ISSN(Online): 2319-8753  
ISSN (Print): 2347-6710

## International Journal of Innovative Research in Science, Engineering and Technology

*(A High Impact Factor, Monthly, Peer Reviewed Journal)*

Visit: [www.ijirset.com](http://www.ijirset.com)

**Vol. 7, Issue 2, February 2018**

- [13] Rodger S A and Double D D, The chemistry of hydration of high alumina cement in the presence of accelerating and retarding admixtures, Cement and Concrete Research, 14, 1984, pp 73-82.
- [14] Paglia C et al, The influence of alkali-free and alkaline shotcrete accelerators within cement systems. Influence of the temperature on the sulphate attack mechanisms and damage, Cement and Concrete Research, 33, 2003, pp 387-395.
- [15] Myrdal R et al, A New Chemical Approach to Obtain High Early Strength in Shotcrete, "Shotcrete: Engineering Developments", Proc. International Conference on Engineering Developments in Shotcrete (Edited by E S Bernard), Hobart, Tasmania, April 2-4, 2001, Balkema Publishers, The Netherlands, 2001, pp 193-196.