



e-ISSN: 2319-8753 | p-ISSN: 2347-6710

# IJIRSET

International Journal of Innovative Research in  
**SCIENCE | ENGINEERING | TECHNOLOGY**

# INTERNATIONAL JOURNAL OF INNOVATIVE RESEARCH

IN SCIENCE | ENGINEERING | TECHNOLOGY

Volume 11, Issue 10, October 2022

**ISSN** INTERNATIONAL  
STANDARD  
SERIAL  
NUMBER  
INDIA

Impact Factor: 8.118

9940 572 462

6381 907 438

[ijirset@gmail.com](mailto:ijirset@gmail.com)

[www.ijirset.com](http://www.ijirset.com)



# Studies on the Mechanical and Durability Properties of Fly ash Concrete – A Review

R.Aarani Devi<sup>1</sup>, S.Abinash<sup>1</sup>, S.Bharani<sup>1</sup>, Dr.K.Nirmalkumar<sup>2</sup>, Dr.K.Vishnuvardhan<sup>3</sup>

Final year Student, Kongu Engineering College, Perundurai, Erode, India<sup>1</sup>

Professor, Kongu Engineering College, Perundurai, Erode, India<sup>2</sup>

Assistant Professor, Kongu Engineering College, Perundurai, Erode, India<sup>3</sup>

**ABSTRACT** - In the world, concrete is an essential building material. In the current situation, admixtures and waste substances from various sectors are added to the combination. Our review's goal is to determine how effective fly ash concrete is. Fly ash generally enhances new concrete by lowering the amount of water needed for mixing and enhancing paste flow characteristics. Fly ash provides several benefits and enhances the performance of Portland Cement Concrete (PCC) in both the fresh and hardened states. The use of fly ash in concrete increases both the strength and durability of hardened concrete as well as the workability of plastic concrete. Reducing fly ash is also affordable. Concrete may require less portland cement if fly ash has been included. Concrete's durability is increased by a drop in free lime, an increase in cementitious compounds as a result, and a decrease in permeability. This has a wide range of benefits. To increase concrete's performance, fly ash is added to admixtures. About 65% of Portland cement is made of lime. When you hydrate, some of this lime becomes free and accessible. When fly ash and free lime are combined, more cementitious elements are created chemically, increasing many of the qualities of the concrete.

**KEYWORDS:** Fly ash, FAC, Mechanical properties, Durability.

## I. INTRODUCTION

A collection of substances known as fly ash has a range of chemical compositions. It is the leftover coal ash that has been gathered in a baghouse or on an electrostatic precipitator. When powdered coal is used to generate power, it mixes with the flue gases that are produced. The use of coal has increased since the 1970s oil crisis. Around the world, 460 million metric tonnes of coal ash were created in 1992. Fly ash was created in the United States for around 10% of this. In the United States, concrete weighed more than 7 million metric tonnes in 1996. Utilizing as much of this affordable ash as possible makes financial sense, especially if it can be utilised as a substitute for cement

Coal is the product of pressure-induced decay of plant matter over millions of years, and its composition is uncertain. Electric firms also use flue-gas conditioners, sodium sulphate, oil, and other additives to prevent corrosion, particulates, and fouling to enhance the power produced from coal. The resulting fly ash can have a wide range of additives, incomplete combustion products, and a varied composition.

The most of fly ash is pozzolanic, or siliceous or siliceous and aluminous, and when combined with calcium hydroxide, it reacts to create cement. Lime and hydrated calcium silicate (CSH) are the products of the reaction between water and portland cement. The lime fills the gaps as the hydrated silicate gains strength. If fly ash and lime are combined properly, CSH—the same cementing compound found in cement concrete created. The combination of lime and fly ash in concrete enhances the strength. Fly ash is often added to structural concrete at a ratio of 15–35% by weight of the cement, but for mass concrete used in dams, roller-compacted concrete pavements, and parking lots, up to 70% by weight of the cement is added. Fly ash selection must be performed with special consideration to ensure improved properties in concrete.

## II. LITERATURE REVIEW

Using modelling, N.Z. Nkomo et al. concentrated on the prediction and modification of the properties of poly ethylene terephthalate (PET) fibre reinforced concrete with fly ash served as a partial cement replacement. By simultaneously



altering the elements, test specimens were created using a full factorial experimental design methodology in order to create a model for overall response variance. The mechanical characteristics of the freshly formed and hardened fiber-reinforced concrete were achieved through numerical optimization. Predictive modified quadratic equations were created for the following variables: slump value, compressive, flexural, split tensile strength, and total cost. After the analysis of variance test was run for each of the stated responses, the developed model was able to successfully and reliably predict the slump value and mechanical properties of the fibre reinforced concrete with a coefficient of determination in the range of 0.5-0.9467. The optimum composition proportion of 15.76% fly ash and 0.32% PET fibre was determined to produce the maximum mechanical strength at the lowest cost. The results for these optimum values for compressive strength, flexural strength, tensile strength, slump value, and total cost, respectively, were 25.65 MPa, 3.69 MPa, 2.36 MPa, 31.48 mm, and R2744.17. Experimental validation of these hypotheses revealed a significant relationship between the predicted and determined values for compressive strength, flexural strength, tensile strength, slump value, and cost, respectively, with observed standard deviations of 0.1335, 0.031, 0.005, 0.676, and 0.02 for each. The best PET fibre percentage and fly ash proportion were determined for concrete slabs for a wide range of potential end uses. Fly ash made up 19.09% of the ideal mixture for suspended slabs, and PET fibre made up 0.34%. For the total cost, split tensile, flexural, compressive strength, and slump value, these values corresponded to answers of R2742.03/kg/m<sup>3</sup>, 2.30 MPa, 3.68 MPa, 24.77 MPa, and 30.60 mm. The preferred mixture for foundation slabs was 3.94 percent fly ash and 0.65 percent PET fibre, and the corresponding response values are R 2760.47 per kilogramme per square metre, 1.82 MPa, 3.26 MPa, 19.32 MPa, and 10.78 mm for total cost, split tensile, flexural, compressive strength, and slump value, respectively. The best combination for paving slabs was 0.65% PET fibre, which produced responses of R 2775.13 kg/m<sup>3</sup>, 1.41 MPa, 3.29 MPa, 19.11 MPa, and 9.92 mm, respectively, for the total cost, split tensile, flexural, compressive strength, and slump value [1].

Similar qualities, traits, and outcomes were found in the study of [7-10].

Fly ash was used as supplementary cementitious material by P. Nath and P. Sarker, who added sustainability to concrete by reducing CO<sub>2</sub> emissions associated with cement manufacture. Various studies have shown that using fly ash as a partial replacement for cement increases the durability of concrete; however, the degree of improvement relies on the parameters of fly ash. The durability characteristics of high-strength concrete were examined in this study using high volume Class F fly ash from Western Australia. The test specimens were cast using concrete mixtures that included fly ash as between 30% and 40% of the total binder. The fly ash and control concrete specimens' compressive strength, drying shrinkage, sorptivity, and fast chloride permeability also were evaluated. The concrete compositions' 28-day compressive strength varied from 65 to 85 MPa. When made for the same 28-day compressive strength of the control concrete, the fly ash concrete samples dried with less shrinkage than the control concrete samples. Fly ash was added, and it greatly decreased sorptivity and chloride ion penetration after 28 days, and it continued to do so after six months. The durability of concrete was generally increased by using fly ash as a partial replacement for cement. [2].

Similar characteristics, features, and observations were observed in the research. [11-13].

M Amran et al use 's of affordable, easily accessible FA as mineral fillers in concrete has many benefits, including a decrease in the amount of ordinary Portland cement (OPC) needed, a removal of the need to dispose of FA in landfills, and a reduction in CO<sub>2</sub> emissions, all of which help to maintain a clean environment. With FA, a durable FAGPC is an engineered composite material that is relatively new, revolutionary, and sustainable. It has a range of advantages, such as high early strength and enhanced durability features (such as reduced permeability against aggressive environments). The global construction industry has been increasingly interested in the production of sustainable and environmentally friendly concretes. This study examines clean manufacture, determinants of FA-GPC durability, and effects of FA disposal on human health and the environment. In addition to summarising the research development trends to generate comprehensive insights into the potential applications of FA as a sustainable and environmentally friendly construction material, for making a greener concrete composite, towards industrialisation environmentally friendly buildings today, this review provided a critical review of the long-term durability properties and the behaviour of FA-GPC composites. [3].

Similar features, qualities, and implications have been observed in the investigations of [14-16].

A laboratory research on the strength development of concrete containing fly ash and the effective usage of fly ash in concrete was presented by A. Oner et al. According to the partial replacement method, fly ash was added to mixtures. There were made a total of 28 various mixtures with various mix designs. To establish the Bolomey and Feret coefficients, four of them were created as control mixtures with cement contents of 250, 300, 350, and 400 kg/m<sup>3</sup> (KB, KF). Each group of mixtures, which each had six different mix designs, was created using the cement content of one of the control mixtures as the foundation. Starting mixes in each group had cement contents of 200, 240, 280, and 320 kg/m<sup>3</sup>, respectively, after 20% of the cement content of the control mixture was removed. As a partial cement





replacement, fly ash was applied in amounts equal to 15%, 25%, 33%, 42%, 50%, and 58% of the remaining cement content. Before compressive strength testing, all specimens had 28 and 180 days of moist curing. Bolomey and Feret strength equations were employed to determine the effectiveness and the highest fly ash concentration that yields the highest compressive strength. Thus, the highest amount of useful fly ash with the greatest efficiency was established. According to this study, strength rises with the addition of fly ash up to a certain point, beyond which the strength starts to fall off. For the testing groups, nearly 40% of cement is the ideal amount of fly ash to use. An significant parameters affecting fly ash's performance is the fly ash/cement ratio.[4].

A. Dhawan et al. created the samples using a range of cement and sand replacement percentages. As a result, a concrete mix is created utilising fly ash (replacing 20% of the cement) and a partial replacement of sand with a commercial waste called sugarcane bagasse ash (replacing 0%, 10%, and 20% of the sand). Banana fibre is also included (0%, 2.5%, and 5%). Under typical compressive strength and flexural strength conditions, samples were assessed and compared to a normal concrete mix. The combination that provides higher mechanical qualities, according to research, is the addition of 2.5% banana fibre to cement, which is partially replaced by 20% fly ash, and sand, which is partially replaced by 10% bagasse ash. Concrete's strength and durability characteristics make it the most dynamic technical material in the construction industry. The consumption of raw materials by the building industry not only exhausts natural resources but also increases the amount of harmful compounds in the environment. It has been discovered that substitute items can help the environment and natural resources to some extent. In the same framework, natural and industrial wastes including fly ash, sugarcane bagasse ash, and banana fibre are used in place of some traditional components of concrete mixes.[5].

Similar properties, qualities, and benefits were identified in the investigations of [17-18].

Siddique R. presented the findings of a study that used experimental methods to assess the mechanical characteristics of concrete mixtures in which Class F fly ash was used to replace some of the fine aggregate (sand). Five weight-based replacements for fine aggregate (sand) were made: 10%, 20%, 30%, 40%, and 50% of Class F fly ash. The qualities of recently laid concrete were tested. At 7, 14, 28, 56, 91, and 365 days, compressive strength, splitting tensile strength, flexural strength, and elastic modulus were assessed. According to test results, using fly ash as a partial replacement for fine aggregate (sand) improved ordinary concrete's strength qualities significantly and might be utilised to make structural concrete.[6].

Similar capabilities, characteristic, and objectives were discovered during the investigations of [19-20].

### III. RESULT AND DISCUSSION

Fly ash concrete specimens had superior compressive strength, splitting tensile strength, flexural strength, and elastic modulus at all ages when compared to plain concrete (control mix) specimens. After 28 days, there was a more noticeable difference in strength between the fly ash concrete specimens and plain concrete specimens. Fine aggregate (sand) concrete was used in place of fly ash concrete, and its compressive strength, splitting tensile strength, flexural strength, and modulus of elasticity all increased with time for all fly ash percentages (6). Strength improves with an increase in fly ash up to a certain point, after which the strength starts to diminish with additional fly ash addition. For the four experimental groups, over 40% of cement is the ideal number of fly ash to use. An significant parameters affecting fly ash's productivity is the fly ash/cement ratio (4). more effective resilience to ASR Because fly ash reacts with the alkali that is present in the concrete, several silica minerals contained in the aggregates are less likely to react with it. an enhancement in sulphate attack resistance. Three phenomena that fly ash causes increase sulphate resistance. Fly ash absorbs the free lime, preventing it from reacting with sulphate. The concrete cannot absorb sulphate due to the reduced permeability. improved corrosion resistance The corrosion resistance is increased by the lowering in permeability.

### REFERENCES

1. Nkomo, N. Z., Masu, L. M., & Nziu, P. K, "Optimisation of mechanical properties of polyethylene terephthalate fibre/fly ash hybrid concrete composite", Case Studies in Construction Materials vol. 17,(2022).
2. Nath, P., & Sarker, P, "Effect of fly ash on the durability properties of high strength concrete", Procedia Engineering, vol.14,(2011),pp 1149–1156.
3. Amran, M., Debbarma, S., & Ozbakkaloglu, T, "Fly ash-based eco-friendly geopolymer concrete: A critical review of the long-term durability properties", Construction and Building Materials vol. 270,(2021),No. 121857.



4. Oner, A., Akyuz, S., &Yildiz, R., “An experimental study on strength development of concrete containing fly ash and optimum usage of fly ash in concrete”, Cement and Concrete Research vol. 35(6),(2005),pp 1165–1171.
5. Dhawan, A., Gupta, N., Goyal, R., & Saxena, K. K, “Evaluation of mechanical properties of concrete manufactured with fly ash, Bagasse Ash and banana fibre”,Materials Today: Proceedings vol. 44(2021), pp 17–22.
6. Siddique, R, “Effect of fine aggregate replacement with class F fly ash on the mechanical properties of concrete”,Cement and Concrete Research, vol. 33(4),pp 539–547.
7. D. Karthik, K Nirmalkumar& R. Priyadarshini, “Characteristic assessment of self-compacting concrete with supplementary cementitious materials”, International Journal of Construction and Building Materials Vol. 297, (2021), No. 123845, pp 1-14.
8. M. Velumani& K Nirmalkumar, “Effect of copper slag on mechanical and durability aspects for different strength concretes”, International Journal of Cement WapnoBeton, Vol. 26, Issue 2, July 2021, pp. 156-166.
9. Bhuvanewari N &Nirmalkumar K (2019), ' Experimental Study on the Mechanical Strength Properties of Steel Slag in Concrete and Weld Slag in Concrete', International Research Journal of Engineering and Technology, Vol. 06, Issue: 02, Feb. 2019, pp. 260-263.
10. Yazhini K &Nirmalkumar K (2019),' Studies on the Mechanical Strength Properties of the Metakaolin Concrete', International Research Journal of Engineering and Technology, Vol. 06, Issue: 02, Feb. 2019, pp. 470-474.
11. Nirmalkumar K &Sivakumar V., 'A Study on the Durability Impact of Concrete by Using Recycled Waste Water', JIPC Journal, Vol. 24(1), pp. 17-22, 2008.
12. Nirmalkumar K &Sivakumar V., 'Acid Resistance Behavior of Concrete made using Untreated and Treated Tannery Effluent', Journal of Modern Applied Science, Vol. 3, No. 1, pp. 139-143, 2009.
13. Karthick M & Nirmalkumar K., 'Durability Properties of High Strength Self Compacting Concrete using Silica Fume and Quarry Dust', International Journal of Scientific Engineering and Applied Science, Volume-2, Issue-4, April 2016, PP. 389-395.
14. Soundharya S & Nirmalkumar K ., 'Study on the Effect of Calcite-Precipitating Bacteria on Self Healing Mechanism of Concrete', Journal of Engineering Research and Management Technology, Vol. 1, No. 4, pp. 202-207, 2014.
15. Soundharya S &Nirmalkumar K., 'Strength Improvement Studies on Self-Healing Characteristics of Bacterial Concrete', International Journal of Engineering Science Invention Research & Development, Vol. 1, No. 4, pp. 162-167, 2014.
16. Nirmalkumar K &Sivakumar V., 'Experimental Studies on Durability of Concrete Using Textile Effluent', International Journal of Civil Engineering Research and Practice, Vol. 5, No.1, pp 29-42, 2008.
17. Nirmalkumar Krishnaswami, Sampathkumar Velusamy, Chandrasekaran Palanisamy,Gowthaman Govindharajan, Guhan Elanchezhian, Gowtham Ravi, 'Experimental studies on recycled E-waste by using coarse aggregate in concrete', Journal of Materials Today: Proceedings, Vol. 65, pp 1996-2002 (August 2022).
18. Nirmalkumar Krishnaswami, Sampathkumar Velusamy, Chandrasekaran Palanisamy, Gowtham Prakash,Kaven Krishna Loganathan, Jithandrakumar Moorthy, 'Experimental studies on light weight concrete using gib & coconut shell in concrete', Journal of Materials Today: Proceedings, Vol. 65, pp 1774-1778 (August 2022).
19. Chandrasekaran Palanisamy, Nirmalkumar Krishnaswami, SampathkumarVelusamy,Harsath Krishnamurthy, Harish kumaar Velmurugan, Harish Udhayakumar, 'Transparent concrete by using optical fibre', Journal of Materials Today: Proceedings, Vol. 65, pp 1900-1907 (August 2022).
20. Chandrasekaran Palanisamy, SampathkumarVelusamy, Nirmalkumar Krishnaswami, Keerthevarman Manickam, Logeshwaran Rathinasamy & Ilavarasapandi Annamalai, 'Experimental investigation on self-compacting concrete with waste marble and granite as fine aggregate', Journal of Materials Today: Proceedings, Vol. 65, pp 1900-1907 (August 2022).



**INNO SPACE**  
SJIF Scientific Journal Impact Factor  
**Impact Factor: 8.118**



**ISSN** INTERNATIONAL  
STANDARD  
SERIAL  
NUMBER  
INDIA



# INTERNATIONAL JOURNAL OF INNOVATIVE RESEARCH

IN SCIENCE | ENGINEERING | TECHNOLOGY

 **9940 572 462**  **6381 907 438**  **ijirset@gmail.com**



[www.ijirset.com](http://www.ijirset.com)

Scan to save the contact details