



e-ISSN: 2319-8753 | p-ISSN: 2347-6710

IJRSET

International Journal of Innovative Research in
SCIENCE | ENGINEERING | TECHNOLOGY

INTERNATIONAL JOURNAL OF INNOVATIVE RESEARCH

IN SCIENCE | ENGINEERING | TECHNOLOGY

Volume 12, Issue 4, April 2023

ISSN INTERNATIONAL
STANDARD
SERIAL
NUMBER
INDIA

Impact Factor: 8.423

 9940 572 462

 6381 907 438

 ijirset@gmail.com

 www.ijirset.com

Analysis of Heat Transfer Rate of Different Metals before and after Heat Treatment

Pranav Kharwar¹, Bhautik Sorathiya¹, Bhushan Chaudhari¹, Jay Patel¹, Neel Gadhia¹,
Rakesh R. Patel², Divyesh S. Jariwala²

Diploma Student, Department of Mechanical Engineering, Tapi Diploma Engineering College, Surat, Gujarat, India¹

Professor, Department of Mechanical Engineering, Tapi Diploma Engineering College, Surat, Gujarat, India²

ABSTRACT: Our project involves conducting experiments to measure the heat transfer rate of different metal samples before and after undergoing heat treatment processes, such as annealing and quenching. The project aims to analyze and compare the changes in heat transfer rate of the metals, as well as investigate the relationship between the heat treatment process and the resulting thermal properties. The findings from this project can provide valuable insights into the impact of heat treatment on the heat transfer behavior of different metals and contribute to the understanding of material behavior and performance in various industrial applications.

KEYWORDS: Heat transfer rate, heat treatment, Metal, Thermal Properties, Effect of heat treatment, Effect on heat transfer rate.

I. INTRODUCTION

Heat transfer is a fundamental phenomenon that plays a crucial role in many industrial processes, such as manufacturing, energy generation, and material processing. The efficiency of heat transfer is highly dependent on the thermal properties of the materials involved, including their heat transfer rate and thermal conductivity. Heat treatment is a common process used in materials science and metallurgy to modify the properties of metals, including their heat transfer behavior.

The aim of this scientific paper is to analyze the heat transfer rate of different metals before and after heat treatment. The analysis will involve measuring and comparing the heat transfer rates of various metal samples, both in their as-received condition and after undergoing different heat treatment processes. The selected metals for this study may include commonly used engineering materials such as EN-31, EN-8, Stainless steel 304, aluminum 606.

The heat treatment processes that may be investigated in this study could include annealing and quenching. These processes are known to alter the microstructure and properties of metals, including their heat transfer behavior. By examining the changes in heat transfer rate before and after heat treatment, this study aims to gain insights into the effects of heat treatment on the thermal properties of metals and their heat transfer performance.

The results of this analysis could have significant practical implications for various industrial applications where heat transfer efficiency is critical. Understanding the impact of heat treatment on the heat transfer rate of different metals can aid in material selection, process optimization, and overall system performance. Moreover, the findings of this study could contribute to the fundamental understanding of the relationship between heat treatment, microstructure, and thermal properties of metals, advancing the knowledge in the field of materials science and heat transfer.

II. LITERATURE REVIEW

Previous research has shown that the heat transfer behavior of metals can be modified by heat treatment parameters such as temperature, heating rate, cooling rate, and holding time. For example, in copper, heat treatment can cause changes in the grain size and crystal structure, which affects the thermal conductivity and convective heat transfer coefficient. Similarly, heat treatment can induce phase transformations and alter the microstructure of aluminum and steel, leading to changes in their thermal properties and heat transfer rate.

However, there is a lack of comprehensive studies that systematically investigate the impact of heat treatment on the heat transfer rate of different metals, and there may be variations in the results reported in the literature. Therefore, this study aims to bridge this gap by providing a comparative analysis of the heat transfer rate of EN-31, EN-8, Stainless steel 304, aluminum 606. before and after heat treatment and elucidating the underlying mechanisms that govern the changes in the heat transfer behavior of these metals.

III. METHODOLOGY

The process for analyzing the heat transfer rate of different metals before and after heat treatment can be outlined in the following steps:

Metal specimen preparation: we started by obtaining 4 different types of metal rod (EN-31, EN-8, Aluminum 6061, Stainless Steel 304)

Dimension of specimen:

EN-31: Diameter= 14mm, Length =150mm (3 Specimen)

EN-8: Diameter=16mm, Length= 150mm long (3 Specimen)

Aluminum 6061: Diameter= 10mm, Length=150mm (2 Specimen)

Stainless Steel 304: Diameter 10mm, Length=150mm (2 Specimen)

using precision cutting tools. Ensure that the specimens are prepared with uniform dimensions to minimize any variability in the experimental results.

Heat treatment: then the specimens were subjected to the desired heat treatment process. This involved annealing and hardening, which are common heat treatment techniques used to modify the properties of metals. Annealing typically involves heating the specimens to a specific temperature and holding them at that temperature for a certain duration, followed by slow cooling, while hardening involves heating the specimens to a higher temperature and then rapidly quenching them in a cooling medium to obtain a harder structure.

Hardness measurement: After the heat treatment process, we measured the hardness of the specimens using a hardness testing machine, Rockwell hardness tester as shown in Fig:1. We Recorded the hardness values for each specimen before proceeding to the next step.



Fig.1 Rockwell Hardness Tester



Fig.2 Experimental Setup

Heat transfer rate experiment: then we conducted heat transfer rate experiment on each specimen using a suitable experimental setup as shown in fig:2. This involved placing the specimen in a holder over a live flame with specified distance above the flame and from the holder and as shown in fig:2 a thermocouple was inserted on the other end of the specimen. We kept 100°C as a standard value so whenever the temperature reached 100°C we stopped the timer and recorded the time

Data collection and analysis: We Record the temperature data obtained from the heat transfer rate experiment and analyze the results.

IV. RESULTS OBTAINED

EN-8:

After subjecting the EN-8 specimen to heat treatment, it was observed that the heat transfer rate of the material decreased. This result can be attributed to the changes in the microstructure and composition of the material caused by the heat treatment process.

Heat Treatment	Hardness (center)	Hardness (Side)	Starting Temperature(°C)	Time (Min)
Untreated	61 HRC	59 HRC	29.3	9:33.98
Annealed	56 HRC	55 HRC	30.5	10:27.08
Hardened	88 HRC	80 HRC	29.2	11:50.08

EN-31:

After subjecting the EN-31 specimen to heat treatment, it was observed that the heat transfer rate of the material decreased. This result can be attributed to the changes in the microstructure and composition of the material caused by the heat treatment process.

Heat Treatment	Hardness (center)	Hardness (Side)	Starting Temperature(°C)	Time (Min)
Untreated	67 HRC	68 HRC	32.2	9:12.43
Annealed	59 HRC	56 HRC	32	13:00.30
Hardened	89 HRC	86 HRC	32.5	13:20.54



Aluminium 6061:

After subjecting the aluminum 6061 specimen to heat treatment, the results were inconclusive with regard to its heat transfer rate. This may have been due to a variety of factors, including the specific parameters of the heat treatment process and the inherent variability of the material itself.

Heat Treatment	Hardness (center)	Hardness (Side)	Starting Temperature(°C)	Time (Min)
Untreated	B53 HRB	B59 HRB	32.8	2:04.74
Annealed	B33 HRB	B24 HRB	32.5	1:56.33

Stainless Steel 304:

In this study, we attempted to heat a rod of stainless steel up to 100 degrees Celsius using a heat source at one end of the rod. However, we observed that the other end of the rod did not reach the desired temperature despite sufficient heating time. In this study, we attempted to heat a rod of stainless steel up to 100 degrees Celsius using a heat source at one end of the rod. However, we observed that the other end of the rod did not reach the desired temperature despite sufficient heating time. Our results suggest that careful consideration should be given to the selection of materials and experimental setup to ensure accurate temperature measurements and uniform heating in similar applications.

V. CONCLUSION

In conclusion, the analysis of heat transfer rate of different metals before and after heat treatment revealed that the heat transfer performance of the specimens was influenced by the heat treatment process. The results showed that the heat transfer rate of the specimens decreased after heat treatment, indicating a reduction in their heat transfer capabilities.

The observed decrease in heat transfer rate can be attributed to the changes in the microstructure and properties of the metals induced by the heat treatment process. Annealing and hardening treatments can alter the crystal structure, grain size, and mechanical properties of the metals, which in turn can affect their heat transfer behavior.

REFERENCES

- [1]. Torsten Ericsson, "Principal of Heat treating of Steels"; ASM Handbook Volume 4 ,1991 edition, pp 14 – 25.
- [2]. Ashish Bhateja, Aditya Varma, Ashish Kashyap, Bhupinder singh, "Study the Effect on the Hardness of three Sample Grades of Tool Steel i.e. EN-31,EN-8 and D3 after Heat Treatment processes such as Annealing,Normalizing, and Hardening & Tempering, The International Journal of Engineering And Science(IJES), Volume 1,Issue 2,2012,pp 253-259.
- [3]. Karlsson, L. ESAB EB, Gothenburg. "Stainless Steels Past, Present and Future". Svetsaren, Vol. 1, p. 47-52, 2004.
- [4]. Callister, W.D. "Materials Science and Engineering: An Introduction". 4th edition. New York: John Wiley and Sons, Inc. 1997.
- [5]. Beddoes, J. "Introduction to Stainless Steels". In: Beddoes, J. Parr, J.G. (Edts.). "Introduction to stainless steels". Materials Park, Ohio: ASM International. 1999.



INNO SPACE
SJIF Scientific Journal Impact Factor
Impact Factor: 8.423



ISSN INTERNATIONAL
STANDARD
SERIAL
NUMBER
INDIA



INTERNATIONAL JOURNAL OF INNOVATIVE RESEARCH

IN SCIENCE | ENGINEERING | TECHNOLOGY

9940 572 462 **6381 907 438** **ijirset@gmail.com**



www.ijirset.com

Scan to save the contact details