



e-ISSN: 2319-8753 | p-ISSN: 2347-6710

IJRSET

International Journal of Innovative Research in
SCIENCE | ENGINEERING | TECHNOLOGY

INTERNATIONAL JOURNAL OF INNOVATIVE RESEARCH

IN SCIENCE | ENGINEERING | TECHNOLOGY

Volume 13, Issue 5, May 2024

ISSN INTERNATIONAL
STANDARD
SERIAL
NUMBER
INDIA

Impact Factor: 8.423

9940 572 462

6381 907 438

ijirset@gmail.com

www.ijirset.com

Evaluation of Mechanical Properties and Microstructure of Silicon Nitride Particulates Reinforced with Al6063 Alloy Composites Using Stir Casting Method

Sampath Swamy K M¹, Manoj H², Sandeep G³, Mustafa Niyaz⁴, Dr. Manjunatha T H⁵

U.G Student, Department of Mechanical Engineering, Ballari Institute of Technology & Management, Ballari,
Karnataka, India^{1 2 3 4}

Associate Professor, Department of Mechanical Engineering, Ballari Institute of Technology & Management, Ballari,
Karnataka, India⁵

ABSTRACT: The aluminium alloys are important in many industrial applications and space applications because of their light weight and good mechanical properties. For this reason many researches had been done to enhance their properties. In this study, particles of silicon nitride are used as reinforcement in aluminium matrix alloy to fabricate AMMC through stir casting. Investigation of mechanical properties such as tensile strength and hardness is made. And the wear and surface roughness in machining of these composites with different cutting speed and feed with constant depth of cut is studied. And also the microstructure of the composites is analyzed. The aluminium alloys are of particular interest to both the aerospace industry and automotive industry because of their attractive combinations of properties such as medium strength, formability, weldability, corrosion resistance and low cost. Compared with a metal matrix material, significant improvements in the mechanical and physical properties such as strength, toughness, and thermal conductivity can be achieved in metal matrix composites (MMCs). In this work of investigation aluminium alloy AA6063 was reinforced by 3, 6, 9 and 12% (in weight %) of Si₃N₄(silicon nitride) order to investigate the influence of the particulate phase in the microstructure and mechanical properties of the composites obtained. The microstructure of the powders and the sintered materials were evaluated by means of SEM and the Hardness and were evaluated by hardness test.

KEYWORDS: Aluminum, Mechanical Properties, Microstructure, Metal Matrix Composites, Stir Casting.

I. INTRODUCTION

Composite materials are engineered or naturally occurring materials made from two or more constituent materials with significantly different physical or chemical properties which remain separate and distinct at the macroscopic or microscopic scale within the finished structure. A common example of a composite would be disc brake pads, which consist of hard ceramic particles embedded in soft metal matrix. The most advanced examples perform routinely on spacecraft in demanding environments. Composites are made up of individual materials referred to as constituent materials. Aluminium is the most popular matrix for the metal matrix composites(MMCs).

The Al alloys are quite attractive due to their low density, their capability to be strengthened by precipitation, their good corrosion resistance, high thermal and electrical conductivity, and their high damping capacity. Aluminium matrix composites (AMCs) have been widely studied since the 1920s and are now used in sporting goods, electronic packaging, armours and automotive industries. They offer a large variety of mechanical properties depending on the chemical composition of the Al-matrix. They are usually reinforced by Al₂O₃, SiC, C but SiO₂, B, BN, B₄C, AlN may also be considered.

The aluminium matrices are in general Al-Si, Al-Cu, 2xxx or 6xxx alloys. As proposed by the American Aluminium Association the AMCs should be designated by their constituents: accepted designation of the matrix / abbreviation of the reinforcement's designation / arrangement and volume fraction in % with symbol of type (shape) of reinforcement. The mechanical alloying (MA) process, using ball-milling techniques, has received much attention as a powerful tool for the fabrication of several advanced materials including equilibrium, non- equilibrium (e.g., amorphous, quasi crystals, nano crystalline, etc.), and composite materials. The MA is a unique process in which a solid state reaction takes place between the fresh powder surfaces of the reactant materials at room temperature. Consequently, it can be used to produce alloys and compounds that are difficult or impossible to obtain by the conventional melting and casting techniques [1-6]. The main aim of this work is to report the effect of the high energy milling processes on the

fabrication of aluminium matrix composite powders, reinforced with a homogeneous dispersion of silicon nitride and aluminium nitride reinforcing particles.

II. LITERATURE SURVEY

Hani Aziz Ameen et al., [1], made an attempt to study the wear rate for different materials (Steel, Aluminum and brass) under the effect of sliding speed, time and different loads, where the apparatus pin on disc has been used to study the specification of the adhesive wear. The experiments have been performed on a group of specimens under different cases of times (5 to 30) minutes, and under different loads (0.5 to 2) Kg, and different speeds (2.5 to 9) m/sec. A mathematical model has been made for all cases that were studied depending on the method of least squares which helps in forecasting about the wear rate through the knowledge of time limits as a variable with fixing the other variables; also building a model with the same method by which forecasting the rate of adhesive wear through knowing the sliding speed as a variable after fixing the other variables, also making another model forecasting the rate of adhesive wear through knowing the variable loads. A study was made for the damaged surface from wearing for the aluminum alloy as a sample to illustrate the wear lines to the direction of the formation of wear; and from the results, it was clear that the cracks which are vertical on the direction of sliding and will meet together with the lines of weariness, and the results will show that the rate of adhesive wear will be directly proportional with (time, sliding speed and load), and the low carbon steel has less wear rate than the other materials.

Vikas Chawla et al., [2] made the modest attempt to develop aluminium based silicon carbide particulate MMCs with an objective to develop a conventional low cost method of producing MMCs and to obtain homogeneous dispersion of ceramic material. To achieve these objectives two step-mixing method of stir casting technique has been adopted and subsequent property analysis has been made.

Riyadh A. Al-Samarai et al., [3], studied the effect of load and speed on sliding friction coefficient and performance tribology of aluminum-silicon casting alloy was evaluated using a pin-on-disc with three different loads (10, 20, and 30 N) at three speeds (200, 300, and 400 r/min) and relative humidity of 70%. Factors and conditions that had significant effect were identified. Experiments showed that the load and the speed affect the coefficient of friction and wear rate of the alloy. The results showed that the wear rate increased with increasing load and decreased with increasing sliding distance, whereas the friction coefficient decreased with increasing sliding speed before a stable state was reached. The friction coefficient also decreased with increasing load.

S. Basavarajappa et al., [4] studied the influence of wear parameters like applied load, sliding speed, sliding distance and percentage of reinforcement on the dry sliding wear of the metal matrix composites. Material selected for the investigation was based on the Al-Cu-Mg matrix alloy, designated by the aluminium association as AA2219 and reinforcement was SiC. The SiC particles, which were used to fabricate the composite, had an average particle size of 25 μm and average density of 3.2 g/cm³. The SiC particle reinforcement varied from 0 to 15 wt pct in steps of 5. The liquid metallurgy technique was used to prepare composite specimens. A plan of experiments, based on techniques of Taguchi, was performed to acquire data in controlled way. An orthogonal array and the analysis of variance were employed to investigate the influence of process parameters on the wear of composites. The objective is to establish a correlation between dry sliding wear of composite and wear parameters. The relations were obtained by multiple regressions. Finally, confirmation tests were conducted to verify the experimental results foreseen from the mentioned correlations.

G. B. Veeresh Kumar et al., [5] investigated the mechanical and tribological properties of Al6061-SiC and Al7075-Al₂O₃ Metal Matrix Composites. From their experiment they found that the dispersed SiC in Al6061 alloy and Al₂O₃ in Al7075 alloy contributed in enhancing the tensile strength of the composites. The tensile strength properties of the composites are found higher than that of base matrix and Al6061-SiC composites superior tensile strength properties than that of Al7075-Al₂O₃ composites. The wear resistance of the composites are higher, further the SiC contributed significantly in improving wear resistance of Al6061-SiC composites.

Emrah Koraman et al., [6], studied Dry sliding wear behavior of Al-Fe-Si-V alloys at elevated temperatures. Dry sliding wear tests of two Al-Fe-V-Si alloys, which have finer and coarser dispersoids in their microstructures, were carried out at various temperatures ranging between 200C and 3500C. The results were then evaluated with respect to the tensile properties at the same temperatures. Results showed that dispersoids size or strength have no significant effect on the wear rate at room temperature. We arrate of both alloys exponentially increase with increasing temperature. Even though they possess higher strength, smaller dispersoids result in higher wear rate at

elevated temperatures. This observation suggests that coarser dispersoids in the microstructure is more effective than strength in limiting the wear rate of Al–Fe–V–Si alloy at elevated temperatures. SEM examinations and EDS analysis within the wear tracks revealed that oxidative wear at lower temperatures, and plastic deformation and delaminating wear at elevated temperatures are dominant wear mechanisms. There is a wear transition between these two mechanisms at 1500C for finer dispersoids alloy and 2500C for coarser dispersoids alloy. Therefore coarser dispersoids in the microstructure shift wear transition to a higher temperature.

F.Labib et.al., [7], studied dry tribological behavior of Mg/SiCp composites at room and elevated temperatures. Pure magnesium and its composites reinforced with 5, 10 and 15 vol% SiC particulates were fabricated by powder metallurgy process. The tribological behavior of the samples was investigated under normal loads of 5–60 N at sliding speed of 0.4 m/s and at wear temperatures of 25– 200 °C. At the wear temperature of 25 °C, results showed almost close wear rates under normal loads of 5 and 20N. However, under higher normal loads the composites showed lower wear rate than that of the unreinforced magnesium. At the higher wear temperatures of 100, 150 and 200 °C, a significant lower wear rate was observed for the composites compared to the pure magnesium. Increasing the normal load resulted in a transition from mild to severe wear at all wear temperatures. Below the transition load oxidation was a dominant wear mechanism, while above that severe plastic deformation and adhesion were the main wear mechanisms. The results also showed wear rate improvement of the composites with increasing SiC content. Finally, a wear map showing mild and severe wear regimes as a function of load and wear temperature was adopted for the composites.

S.B.Chikalthankar et.al., [8], conducted experiments to study the Effect of Silicon Carbide Content on Tribological Properties of Aluminium Zinc Alloy Composite at Elevated Temperature. The pin on-disc (by pin heating) test machine is used to study effect of wear parameters like Silicon carbide percentage, disc rpm, temperature and applied load of on the wear of the alloy have been investigated. Taguchi technique is used to conduct the experiment for acquiring the data in controlled way. An orthogonal array and the analysis of variance are employed to investigate the influence of process parameters on the wear of alloy. The objective of experimentation is to establish correlation between dry sliding wear of alloy and wear parameters. This correlation is obtained by regressions and confirmation tests. This test is conducted to verify the experimental results from the mentioned correlations. It is observed that there is a transition from severe wear to mild wear after a time of sliding that decreases at 300°C and 2Kg (low) load.

K. L. Meena et.al., [9] observed that mechanical properties of the developed SiC reinforced Al6063 metal matrix composite material using the melt stirring technique. The experiment was performed by varying the reinforced particle size as 200 mesh, 300 mesh, 400 mesh and different weight percentage, 5%, 10%, 15%, and 20% of SiC particle reinforced composite material. The stirring process was conducted at 200 rpm using a graphite impeller on behalf of 15 min. A homogenous dispersion of SiC particle in the aluminium matrix was observed. Tensile strength, hardness and breaking strength improved with the enlargement in reinforced.

Ehsan Ghasali et al., [10] made an attempt to study on Investigation on macrostructural and mechanical properties of B4C–aluminum matrix composites prepared by microwave sintering and concluded that having strong bonding strength.

P.Pugalenthi et al., [11] made an attempt to study on Evaluation of Mechanical Properties of Aluminium Alloy 7075 Reinforced with SiC and Al₂O₃ Hybrid Metal Matrix Composites and concluded that strength of the material increases by adding reinforcement.

Kenneth Kanayo Alaneme et.al., [12] studied the Macrostructural characteristics, mechanical and wear behaviour of aluminium matrix hybrid composites reinforced with alumina, rice husk ash and graphite. Alumina, RHA and graphite mixed in varied weight ratios were utilized to prepare 10 wt% hybrid reinforced Al-Mg- Si alloy based composites using two-step stir casting. Hardness, tensile properties, scanning electron microscopy, and wear tests were used to characterize the composites produced. The results show that Hardness decreases with increase in the weight ratio of RHA and graphite in the composites; and with RHA content greater than 50%, the effect of graphite on the hardness becomes less significant. The tensile strength for the composites containing 0.5wt% graphite and up to 50% RHA was observed to be higher than that of the composites without graphite. The wear resistance decreased with increase in the graphite content from 0.5 to 1.5 wt%.

Soorya Prakash Kumarasamy [13] investigated mechanical and machinability behaviour of Aluminium Metal Matrix Composite (AMMC) developed through two- step casting method by reinforcing constant amount of fly ash

cenosphere (10%) and varying quantity of graphite (2%, 4% and 6%). Morphological analysis result shows the presence of dendritic arms and homogeneous distribution of the cenosphere and graphite in Al7075 matrix. The hardness and tensile strength upturn with addition of cenosphere and vice versa for the addition of graphite.

M. Sreenivasa Reddy et.al., [14] evaluated Hardness and Tensile Properties of Aluminium 7075 alloy reinforced with E-glass and fly ash particulates to form MMC using graphite die for casting. Hardness of the Al-cast alloy produced in this work is lower at 2% of E-Glass when compared to 4% and 6%. However, after thermal treatment the water quenched specimens exhibit higher hardness. The ultimate tensile strength (UTS) of the new alloy produced is higher in 2% of E-Glass and lower in 4 and 6% E-Glass.

Pardeep Sharma et.al., [15] studied the effect of graphite particles addition on the microstructure of Al6082 metal matrix composites manufactured by conventional stir casting process. The reinforcement content was varied from 0% to 12% in a step of 3%.

Johny James.S [16] prepared hybrid aluminium metal matrix composite to study its machining and mechanical properties. Preparation of hybrid aluminium metal matrix composite is made by reinforcing Silicon carbide and Titanium di boride .

P. Pugalenth et.al., [17] made an attempt to study on Evaluation of Mechanical Properties of Aluminium Alloy 7075 Reinforced with SiC and Al₂O₃ Hybrid Metal Matrix Composites In 2014.

III. METHODOLOGY


The fabrication of Al6063-Si₃N₄ composites will be carried out by liquid metallurgy route via stir casting technique. The major components of the casting process consist of electrical resistance furnace; zirconium coated steel impeller and cast iron permanent mould. The power rating of electrical furnace will be 60kw and maximum temperature limit is 1200 degree Celsius. The mechanical stirrer used for stirring the molten alloy during the preparation of composites with high temperature and to prevent migration of ferrous ions from the stirrer material into Al6063 alloy melts.

Calculated amount of the Al6063 alloy ingots are charged into the furnace for melting. The melting point of Aluminium alloy is 660 °C. The melt superheated to a temperature of 750 °C. The temperature will be recorded using achrome-alumel thermocouple. The molten metal is then degassed using solid hexachloroethane (C₂Cl₆) for 3 min. A stainless steel impeller coated with zirconium is used to stir the molten metal to create a vortex. The stirrer will be rotated at a speed of 300rpm and the depth of immersion of the impeller was 60 percent of the height of the molten metal from the surface of the melt. Further, the Si₃N₄ particulates are preheated in a furnace upto 300°C will be introduced into the vortex. Stirring is continued until interface interactions between the reinforcement particulates and the matrix promotes wetting. Then, Al6063- 3,6 and 9 wt. % Si₃N₄ mixture are poured into permanent cast iron mold having dimensions 125mm length and 15mm diameter.

The micro structural study was carried out on the investigating composites using scanning electron microscope and EDS. Samples around 15 mm diameter cut from the castings and are polished properly. Keller’s reagent is used to etch the samples. Further, based on the microstructural study compression, fatigue and wear properties are evaluated as per ASTM standards.

IV. EXPERIMENTAL RESULTS

TENSILE STRENGTH



(a)




(b)

Figure(b) shows a Tensile tested samples

Table 1: Shows the tensile result

Sl. No.	Sample	UTS (MPa)	YS (MPa)	% Elong
1	Al6063 Alloy	129.30	106.30	15.33
2	Al6063-3% Si3N4	143.44	124.36	14.30
3	Al6063-6% Si3N4	169.56	145.57	13.73
4	Al6063-9% Si3N4	181.32	160.36	13.07
5	Al6063-12% Si3N4	170.93	143.36	12.13

ULTIMATE TENSILE STRENGTH



Graph1: showing the variations in ultimate tensile strength of 6063al before and after addition of different wt. % of si3n4 particulate

COMPRESSION STRENGTH

A majority of parts of structures, machines or devices are invariably subjected to uniaxial compression load. The behaviour of a material under simple uniaxial compression is called compression behaviour. The test performed for this purpose is referred to as compression test.


Among the various mechanical testing, compression testing is one of the most important and widely used. One can obtain important information concerning the materials ductile properties, the character and extent of plastic deformation, ultimate strength and toughness. The response of materials to other type of loading can sometimes be explained or predicted on the basis of their behavior under simple compression. So much information can be obtained from a single test justifies its extensive use not only in engineering materials research but also in engineering



industries for quality control and design purpose. Different materials respond differently to uniaxial compressive forces. The compressive curves correspond to these responses have discussed in below:

Table 2: Shows the Compression results

Sl. No.	Sample	CS (MPa)
1	Al6063 Alloy	480.16
2	Al6063-3% Si3N4	553.28
3	Al6063-6% Si3N4	625.76
4	Al6063-9% Si3N4	686.96
5	Al6063-12% Si3N4	699.03




Graph2: showing the variations in Compression strength of 6063Al before and after addition of different wt. % of si3n4 particulate

The compression strength of Al6063 alloy and various wt. % of Si3N4 composites. From the graph as weight percentage of Si3N4 reinforcement increases from 3 to 12 wt. %, This increase compression strength is mainly due to high compression strength of Si3N4 particulates. The compression strength of Al6063 alloy increased from 553.28 MPa to 699.03 MPa by adding 12 wt. % of Si3N4 particulates in the matrix.

HARDNESS STRENGTH

TABLE 3: Shows the hardness results

Sl. No.	Sample	BHN
1	Al6063 Alloy	53.18
2	Al6063-3% Si3N4	60.26
3	Al6063-6% Si3N4	71.36
4	Al6063-9% Si3N4	79.64
5	Al6063-12% Si3N4	77.36



Graph3: showing the variations in BHN of 6063Al before and after addition of different wt. % of Si₃N₄ particulate


it is observed macro-hardness of increasing linearly with increase in weight percentage of si₃n₄ particles. this may be attributed because of escalation in occurrence of hard si₃n₄ particles in the aluminium matrix and high hardness of si₃n₄ particles. incorporation of reinforcement particles in the aluminium matrix enhances their surface area and the size of aluminium matrix grains reduced. the occurrence of these hard surface areas of si₃n₄ particles offers huge resistance to the plastic deformation which results into augmentation of the hardness of fabricated.


MICROSCOPIC ANALYSIS

Microscope was used to examine the casted surfaces of the test samples. In present study, OLYMPUS Microscope BX51M with Clemex Image analyzer was used for the analyzing material characterization of surface of the materials. Microscopic images of different casted specimen such as 0%, 3%, 6%, 9% and 12 wt% of Si₃N₄ were analysed with a magnification of 1000X and 3000X.




Figure shows sample for Characterization analysis





SCANNING ELECTRON MICROSCOPE IMAGES



For both the composite rods, the microstructure shows the grain boundaries, interdendritic network of silicon nitride particles distributed in a matrix of aluminium solid solution throughout the structure. The composite reinforced with silicon nitride in (b), also presents a microstructure without porosity with uniform distribution of the reinforcing phase (Si₃N₄) and without the presence of agglomerations.

Energy dispersive spectrographs (EDS) of Al6063




TABLE 4: Shows the EDS results of Al6063

Element	N	Mg	Al	Si
Weight (%)	0.21	3.17	95.21	1.40

V. CONCLUSION

The AMMC with different Weight fraction of silicon nitride is fabricated and various investigations were made.

- Hardness values of the components were found and the hardness of the component increases with the increase in Si₃N₄ percentage.
- Tensile strength has been increased at 3, 6, and 9 wt.% of Si₃N₄, but when the percentage of Si₃N₄ is increased further to 12 wt.%, the tensile strength is decreased.
- The microstructure shows the grain boundaries, interdendritic network of aluminium oxide and silicon nitride particles distributed in a matrix of aluminium solid solution throughout the structure.
- There is increase in compression strength with addition of 6 and 9 wt. % Si₃N₄ particulates to base Al6063 alloy.

REFERENCES

[1] Abhishek Kumar, Shyam Lal, Sudhir Kumar “ Fabrication and characterization of A359/Al₂O₃ metal matrix composite using electromagnetic stir casting method” Noida Institute of Engineering and Technology, Greater Noida, Uttar Pradesh, India. 7 March 2013

[2] Oskouei , R.N. Ibrahim “An investigation on the fatigue behaviour of Al 7075-T6 coated with titanium nitride using R.H. physical vapour deposition process” Department of Mechanical & Aerospace Engineering, Monash University, Clayton, VIC 3800, Australia

[3] S.A. Sajjadi, H.R. Ezatpour, H. Beygi “Comparison of microstructure and mechanical properties of A356 aluminium alloy/Al₂O₃ composites fabricated by stir and compo-casting processes” Department of Material Science and Engineering, Faculty of Engineering, Ferdowsi University of Mashhad, Mashhad, Iran

[4] XIU Zi-yang, CHEN Guo-qin, WU Gao-hui, YANG Wenshu, LIU Yan-mei “Effect of volume fraction on microstructure and mechanical properties of Si₃N₄/Al composites” School of Materials Science and Engineering, Harbin Institute of Technology, Harbin 150001, China 25 July 2011

[5] S.A. Sajjadi a, M. Torabi Parizi b, H.R. Ezatpoura, A. Sedghic “Fabrication of A356 composite reinforced with micro and nano Al₂O₃ particles by a developed compocasting method and study of its properties” a Department of Materials Science and Metallurgical Engineering, Engineering Faculty, Ferdowsi University of Mashhad, Mashhad, Iran b Department of Materials Science and Engineering, Saveh Branch, Islamic Azad University, Saveh, Iran c Department of Materials Science and Metallurgical Engineering, Engineering Faculty, Imam Khomeini International University of Qazvin, Qazvin, Iran

- [6] C.S. Ramesha, R. Keshavamurthy, B.H. Channabasappa, Abrar Ahmedb “Microstructure and mechanical properties of Ni–P coated Si₃N₄ reinforced Al6061 composites” a Professor, Mechanical Engineering, PES Institute of Technology, Bangalore-560 085, Karnataka, India b Research scholars, Mechanical Engineering, PES Institute of Technology, Bangalore-560 085, Karnataka, India
- [7] Hashim J, Looney L, Hashmi MSJ 2001 The Wettability of SiC Particle in Cast AluminiumMatrix Composites Journal of Material Processing Technology 119 pp. 329-335.
- [8] Ozben T et al 2008 Investigation Mechanical and Machinability Properties of SiC ParticleReinforced AlMMCJournal of Materials Processing Technology 1 98 220-225e.
- [9] Viswanatha B M, Kumar P M, Basavarajappa S 2013 Mechanical Properties Evaluation of A356/SiCp/Gr Metal Matrix Composites Journal of Engineering Science and Technology 8pp. 754-763.
- [10] Meena K L, Manna A, Banwait S S 2013 An Analysis of Mechanical Properties of The Developed Al/SiCMMC.American Journal of Mechanical Engineering 1 pp. 14-19.
- [11] B.A. Parker, D.S. Saunders, and J.R. Griffiths, The QuantitativeEvaluation of Microstructure of a StrontiumModified Al-Si-MgAlloy FollowingProlonged SolutionTreatment, Met. Forum, Vol5, p48-53, 1982.
- [12] J.W. Martin and R.D. Doherty, Stability of Microstructures inMetallic Systems, Cambridge University Press, London, p 210-216, 1980
- [13] C.W. Meyers and J.S. Lyons, Fracture Toughness--Second ParticleInteractions in A357 Alloys, Technology for Premium QualityCastings, E. Dunn and D.R. Durham, Ed., The Metallurgical Society,p 151-179, 1986
- [14] C.Q. Chen and J.F. Knott, Effects of Dispersoid Particles onToughness of High Strength Aluminum Alloys, Met. Sci., Vol 15,p 357-366, 1981
- [15] R.H. Sailors, Properties Related to Fracture Toughness, ASTMSTP 605, American Society for Testing and Materials, p 34-39,1976
- [16] K. Tynelius, "A Parametric Study of the Evolution of Microporosityin Al-Si Foundry Alloys," Ph.D. thesis, Drexel University,Mar1992.
- [17] Anjan Kumar Dr. Sanjay kumar S.M “A Review on Microstructure and Mechanical Properties of Silicon Nitride Reinforced AMMC Using Stir Casting Method” International Research Journal of Engineering and Technology (IRJET) ISSN: 2395-0056 Volume: 05 Issue: 10 Oct 2018.
- [18] P. S. Raghavendra Rao and C. B. Mohan, Study on mechanical performance of silicon nitride reinforced aluminium metal matrix composites, Materials Today: Proceedings, <https://doi.org/10.1016/j.matpr.2020.03.405>.
- [19] K. Gajalakshmi, S. Kathiresan, K.S. Sreenivasan, S. Ravindran, Investigation of microstructure and mechanical properties of silicon nitride reinforced ammc using stir casting method, IOSR J. Mech. Civ. Eng., 61–65 (2014), e-ISSN: 2278- 1684, p-ISSN : 2320–334X.
- [20] Pardeep Sharma, Satpal Sharma, Dinesh Khanduja, A study on microstructure of aluminium matrix composites, 14 May 2015, doi.10.1016.
- [21] M. Wang, D. Wang, T. Kups, P. Schaaf, Size effect on mechanical behavior of Al/ Si₃N₄multilayers by nanoindentation, Mater. Sci. Eng.: A, (644) (2015) 275– 283.



INTERNATIONAL
STANDARD
SERIAL
NUMBER
INDIA



INTERNATIONAL JOURNAL OF INNOVATIVE RESEARCH

IN SCIENCE | ENGINEERING | TECHNOLOGY

 9940 572 462  6381 907 438  ijirset@gmail.com



www.ijirset.com

Scan to save the contact details