

(An ISO 3297: 2007 Certified Organization) Vol. 5, Issue 5, May 2016

# Ag-Mn Mixed Tartrate Crystals: A Growth and Spectrometric Studies

Mansi Tailor<sup>1</sup>, Mayuri Dave<sup>2</sup>, Vimal Joshi<sup>3</sup>\*

Research Student, Research Laboratory, Department of Physics, Shri R.K. Parikh Arts and Science College, Petlad,

Dist: Anand, Gujarat, India<sup>1</sup>.

Research Student, Research Laboratory, Department of Physics, Shri R.K. Parikh Arts and Science College, Petlad-,

Dist: Anand, Gujarat, India<sup>2</sup>.

Principal, Department of Physics, Shri R.K. Parikh Arts and Science College, Petlad, Dist: Anand, Gujarat, India<sup>3</sup>.

**ABSTRACT:** The different tartrate compounds draw attention of many researchers because of its several applications in science and technology as well as in the field of medical and pharmaceutical sciences. In the present investigation, authors present their research on the crystal growth of silver-manganese mixed tartrate crystals using the method of single diffusion gel growth technique in silica gel made from aqueous solution of sodium metasilicate and tartaric acid. During the growth of silver-manganese mixed tartrate crystals, two types of morphology of grown crystals have observed. One is flower shape crystals having light pink colour and another is spherulitic crystals having light brown colour. The X-ray diffraction and FT-IR spectroscopic studies were carried out on the powdered sample of grown crystals. The results are discussed.

**KEYWORDS:** gel growth, crystal growth, silver-manganese mixed tartrate crystal, powder XRD, FT-IR

## I. INTRODUCTION

The gel growth technique is one of the oldest techniques to grow the crystals at ambient temperatures, which are sparingly soluble in water or decompose before melting. Study of growth, characterization and applications of several crystals have been carried out by many authors [1-4]. Many types of pure and mixed tartrate crystals have been grown in hydro silica gel. Growth and characterization of different crystals of pure and mixed tartrate compounds were elaborately reported by earlier researchers [5-15].

Interest in the morphology of crystals started in 17<sup>th</sup> century when Kepler [16] observed dendritic snow crystals in 1611 and Steno [17] was attracted by variety of polyhedral forms of rock crystals[18-19]. Different types of tartrate crystals can be grown in hydro silica gel with the help of single diffusion technique[2]. Mainly tartrate crystals have attracted attention due to their interesting physical properties and application like dielectric and ferroelectric[20-23]. Growth and characterization of pure and mixed crystals were reported earlier by many researchers[24-27].

In the present investigation, growth of Silver-Manganese mixed tartrate crystals and their characterized by FT-IR spectroscopy and powder X-ray diffraction techniques were reported. Unit cell parameters and crystal structure of grown crystals were calculated by powder x-ray diffraction technique with the help of powder X software. The functional group present in the grown crystals were reported by FT-IR spectroscopy.

## Crystal growth

## **II. EXPERIMENTAL TECHNIQUES**

In the present study single diffusion gel growth technique was employed to grow Silver-Manganese mixed tartrate crystals. The glass test tubes were used as crystalline apparatus. Dimension of glass test tubes were 25mm internal diameter and 150mm length. Hydro silica gel was used as a gel media to grow Silver-Manganese mixed tartrate crystals. The hydro silica gel was prepared by aqueous solution of sodium meta silicate having 1.05 specific gravity was acidified by 1M tartaric acid in such a manner that pH 5.0 could be set for gel mixture. This gel mixture was



(An ISO 3297: 2007 Certified Organization)

### Vol. 5, Issue 5, May 2016

transformed in to different glass test tubes and allowed to set into gel form. The gel set within 2 to 3 days. After setting gel, 10ml of supernatant solution was gently poured over a set gel without break the gel. The supernatant solution was prepared by mixing different proportion of  $1.5M \text{ AgNO}_3$  and  $1.5M \text{ Mn}(\text{NO}_3)_2$ .

The growth of crystalshas started after three to four weeks. Before crystal growth start, it was observed that some precipitates formed near Gel-Liquid Interface (GLI). The formation of precipitates were denser near the GLI and density of precipitates become decreases as move away from GLI. This precipitates were formed in the band shape. The growth of crystals were observed in the layered form. Two types of crystal morphology were observed in the test tubes. One was pinkish colour floret shape and another was spherulitic brown colour. The morphology of both the crystals were different. In the present study, authors present the characterization of the pink crystals grown by the supernatant solution containing mixture of 2 ml AgNO<sub>3</sub> and 8 ml  $Mn(NO_3)_2$ . Fig. 1 shows the precipitates and grown crystals within the test tube. Whereas, the grown crystals depicted in the fig.2.




Fig.1 Precipitates and grown crystals within the test tube Fig 2 Grown crystals

### **Characterization Techniques**

#### FTIR spectroscopic analysis

Fourier Transform Infrared Spectroscopy is a non-destructive technique which is used to obtain an infrared spectrum of absorption and emission. This technique is applicable to the analysis of solids, liquid and gases. FTIR is tool for identifying the functional group present in given sample.

In the present study, the FT-IR spectrum of powdered sample of grown Silver-Manganese mixed tartrate crystals were recorded in the range of 400cm<sup>-1</sup> to 4000cm<sup>-1</sup> using Perkin Elmer Fourier Transform Infrared Spectrometer Model: Spectrum GX.

#### Powder XRD analysis

Crystalline nature and unit cell parameters can be studied by powder X-ray diffraction technique.

In the present study, powder X-ray diffraction pattern of grown Silver-Manganese mixed tartrate crystals was recorded using Philips Holland, Model: X'pert MPDX-ray diffractometer with  $CuK_{\alpha}$  radiation.



(An ISO 3297: 2007 Certified Organization)

#### Vol. 5, Issue 5, May 2016

### **III.RESULT AND DISCUSSION**

#### Fourier Transform Infrared Spectroscopic (FTIR) Analysis

The FTIR spectrum of grown pink crystals of Silver-Manganese tartrate was recorded in the wave number range of 400cm<sup>-1</sup> to 4000cm<sup>-1</sup> is shown in fig.3.




Fig.3 absorption spectrum of powdered sample of grown crystals

The absorption peaks at 3549.18cm<sup>-1</sup>, 3444.58cm<sup>-1</sup>, 3176.39cm<sup>-1</sup> and 2971.31cm<sup>-1</sup> are due to stretching of O-H bond, which normally indicates the presence of water crystallization. The strong absorption peak at 2290.98cm<sup>-1</sup> and 1394.42cm<sup>-1</sup> are due to combination of C-H stretching like  $\delta$  and  $\pi$ . The absorption peaks at 1632.18cm<sup>-1</sup> and 1575cm<sup>-1</sup> are due to the carbonyl C=O group. The strong peak at 1448.27cm<sup>-1</sup> is assigned to C=O symmetric and  $\delta$ (O-C=O) mode. The absorption peaks at 1299.66cm<sup>-1</sup>, 1235.83cm<sup>-1</sup> and 1220.21cm<sup>-1</sup> are due to O-H plane bending. The C-H stretching vibrations give rise to the absorption at 1126.77cm<sup>-1</sup>, 1115.19cm<sup>-1</sup> and 1050.91cm<sup>-1</sup>. The absorption peak at 832.49cm<sup>-1</sup> and 815.49cm<sup>-1</sup> are due to C-C stretching. The absorption peaks at 704.28cm<sup>-1</sup> and 637.98cm<sup>-1</sup> are due to water crystallization in Silver-Manganese tartrate crystals. The absorption peaks at 545.69cm<sup>-1</sup> and 520.46cm<sup>-1</sup> are due to the metal–oxygen stretching vibrations in Silver-Manganese tartrate crystals. The observed vibrational frequencies and their assignments are listed in table 1.

Absorption PeakPositions (cm <sup>-1</sup> )	Assignments		
3549.18,3444.58,3176.39,2971.31	O-H stretching (water)		
2290.98	Combination C-H stretching		
1632.18,1575.12	C=O stretching		
1448.27	C=O symmetric and $\delta$ (O-C=O)		
1394.42	Combination C-H stretching		
1299.66,1235.83,1220.21	O-H plane bending		
1126.77,1115.19,1050.91	C-H stretching		
832.49, 815.49	C-C Stretching		
704.28, 637.98	Water crystallization in silver-		
	manganese tartrate		
545.69, 520.46	Metal-oxygen stretching		

Table 1 Peak assignments of powdered sample of grown crystals




(An ISO 3297: 2007 Certified Organization)

## Vol. 5, Issue 5, May 2016

### **Powder X-ray Diffraction Analysis**

The recorded powder XRD pattern for the powdered sample of grown pink colour Silver-Manganese mixed tartrate crystals is shown in fig. 4. The experimental 20 range is  $3^{\circ}-90^{\circ}$  with a step size of 0.05° and a counting time of 60s per step. The program of graphic tool for powder diffraction named as powder X [28]. The powder X software is also used to determine the observed diffraction peak positions of the crystal and analytical indexing of the powder pattern. The grown crystalis found to be crystallized in nature having orthorhombic structure.



The calculated and observed values of 20 and d corresponding to h k l parameters are summarized in Table 2.

Hkl		20		D	Intensity
	(Exp.)	(Calc.)	(Exp.)	(Cal.)	(Exp.)
1 2 0	14.122	14.259	6.26627	6.20634	9.00
2 1 1	16.678	16.695	5.31147	5.30588	11.38
1 3 1	21.283	21.347	4.17135	4.15904	4.55
0 1 3	22.875	22.874	3.88457	3.88467	7.07
1 4 0	16.177	26.121	3.40154	3.40866	3.79
4 0 1	28.534	28.431	3.12573	3.13682	2.58
2 4 1	29.625	29.694	3.01299	3.00622	4.03
0 4 3	33.623	33.675	2.66331	2.65937	2.34
2 5 0	34.713	34.587	2.58215	2.59130	11.77
2 4 3	36.350	26.480	2.46955	2.46106	5.18
4 4 0	37.528	37.593	2.39469	2.39071	4.91
0 6 1	38.955	38.928	2.31016	2.31174	3.15
620	43.691	43.694	2.07010	2.06996	6.21
603	47.637	47.615	1.90745	1.90828	4.34
173	51.012	51.022	1.78887	1.78853	3.36
560	52.386	52.397	1.74515	1.74481	3.32
065	54.211	54.262	1.69062	1.68916	10.31
605	56.941	56.984	1.61588	1.61477	3.38
8 1 2	59.204	59.227	1.55939	1.55884	2.59
663	62.605	62.604	1.48261	1.48262	4.97
294	68.804	68.828	1.36338	1.36295	2.76
647	75.193	75.172	1.26258	1.26289	3.54

Table 2 Powder diffraction data of pink colour Silver -Manganese mixed tartrate crystals.



(An ISO 3297: 2007 Certified Organization)

#### Vol. 5, Issue 5, May 2016

#### **IV. CONCLUSION**

The pink colour crystals of Silver –Manganese mixed tartrate crystals are successfully grown by single diffusion technique in hydro silica gel. The grown crystals are of pinkish colour having floret type morphology. With the help of powder X-ray diffraction analysis, it is found that powdered sample is crystalline in nature and confirms the unit cell parameters and d-values. The FTIR spectrum shows presence of various functional group like O-H, C-C, C=O and metal oxygen bond.

### ACKNOWLEDGEMENT

Authors are thankful for allowed to official use the Powder X software. Authors are especially thankful to Dr. M.J. Joshi, Professor of Physics, Departments of Physics, Saurashtra University, Rajkot for HIS keen interest. The authors are also thankful to Petlad Education Trust, Petlad for Motivation.

#### REFERENCES

- [1] Henisch, H.K., Dennis, J., Hanoka, H.I., "Crystal growth in gels", Physics and Chemistry of Solids, Vol. 26, issue 3, pp. 493-500, 1965.
- [2] Patel, A.R. and Rao, A.V., "Crystal growth in Gel media", Bulletin of Materials Science, Vol. 4, issue 5, pp. 527-548, 1982.
- [3] Henisch, H.K., "Crystal growth in Gels", Pennsylvania State University Press, University Park, 1973.
- [4] Patel, A.R. and Arora, S.K., "Growth of mixed Sr<sub>1-x</sub>Ca<sub>x</sub>C<sub>4</sub>H<sub>4</sub>O<sub>6</sub> crystals in gel", Journal of Crystal Growth, Vol. 37, Issue 3, pp. 343-345, 1977.
- [5] Selvarajan, P., Das, B.N., Gon, H.B., Rao, K.V, "Infrared Spectroscopic and Thermal Studies of Calcium Tartrate Single Crystals Grown by Silica-Gel Technique", Journal of materials science letters, Vol. Issue. 12, No.15, pp.1210-1211, 1993.
- [6] Suryanarayana, K., Dharmaprakash, S.M. and Sooryanarayana, K., "Optical and Structural Characteristics of Strontium dopped Calcium Tartrate Crystals", Bulletin of Materials Science, Vol. 21, No.1, pp.87-92, 1998.
- [7] Dabhi, R.M. and Joshi, M. J., "Thermal studies of gel grown zinc tartrate crystals", Indian Journal of Physics, Vol. 76A, pp. 481-485, 2003.
- [8] Joshi, S.J., Parekh, B.B., Vohra, K.D. and Joshi, M.J., "Growth and characterization of gel grown pure and mixed iron-manganese levo-tartrate crystals", Bulletin of Materials Science, Vol. 29, issue 3, pp. 307-312, 2006.
- [9] Joshi, V.S. and Joshi, M.J., "FTIR spectroscopic and thermal studies of calcium tartrate trihydrate crystals grown by gel assistance", Indian Journal of Physics, Vol. 75A, issue 2, pp. 159-163, 2001.
- [10] Rahimkutty, M.H., Rajendra Babu, K., Sreedharan Pillai, K., Sudarsana Kumar, M.R. and Nair, C.M.K., "Thermal behaviour of strontium tartrate single crystals grown in gel", Bulletin of Materials Science, Vol. 24, No. 2, pp. 249–252, 2001.
- [11] Sajeevkumar, G., Raveendran, R., Ramadevi, B.S. and Vaidyan, A.V., "Growth features of ammonium hydrogen-tartrate single crystals", Bulletin of Materials Science, Vol. 27, No.4, pp. 323–325, 2004.
- [12] Sahaya, S. X. and Mahadevan, C., "On the growth of calcium tartrate tetrahydrate single crystals", Bulletin of Materials Science, Vol. 27, No. 4, pp. 327–331, 2004.
- [13] Sawant, D.K., Patil, H.M., Bhavsar, D.S., Patil, J.H., Girase, K.D., "Growth and Characterization of Mixed Crystals of Ca-Sr Tartrate in Silica Gel", Archives of Physics Research, Scholars Research Library, Vol. 2, Issue.1, pp.219-228, 2011.
- [14] Freeda, M. M., Mary D.S., Krishna Priya, R., Freeda, T.H., Almusallam, A.W., Recent Research in Science and Technology, Vol. 2, Issue 10, pp.9-11, 2010.
- [15] Tailor, M. and Joshi, V.S., "Crystallization, FT-IR and powder XRD study of gel grown iron-manganese-nickel ternary dextro-tartrate crystals in hydro silica gel", Advances in Applied Science Research, Pelagia Research Library, Vol.5, Issue 6, pp.115-119, 2014.
- [16] Kepler, J., Strena seu de nive sexangula, Francofurti ad Moenum, Godfrey Tampach, Frankfurt;
- English translation "A new year's gift or on the six-cornered snowflakes", by Hardie, C., Oxford Univ. Press, Oxford, 1611.
- [17] Steno, N. (1669) De solido intra solidum naturaliter contento dissertationis prodromus, Florence; English translation by J. G. Winter, The Prodromus of Nicolous Steno's dissertation concerning a solid body enclosed by process of nature within a solid, Hafner, New York (1968).
- [18] Ichiro S., "Growth and Morphology of Crystals", Forma, Vol.14, pp.147–166, 1999.
- [19] Byrappa, K., Ohachi, T., "Crystal Growth Technology", Springer-Verlag Berlin Heidelberg, New York, pp.1-2, 2003.
- [20] Angel, M.G.J., Sahaya Shajan, X., Devadoss, H., "Electrical conductivity studies on pure and barium added strontium tartrate trihydrate crystals", Indian Journal of Science and Technology, Vol.3, No.3, 250-252, 2010.
- [21] Bachav, S.K., Patil, N.S., Kale, M.S. Bhavsar, D.S., "Crystal Growth and Characterization of Cobalt Doped Barium Tartrate Crystals by Silica Gel Method", International Journal of Enginnering Research and Application, Vol.4, Issue 8, version 7, pp.108-112, 2014.
- [22] Patil, H.M., Sawant, D.K., Bhavsar, D.S., Patil, J.H., Girase, K.D., "Crystallographic and FT-IR Characteristics of Gel Grown Cerium Tartrate Crystals", Archives of Physics Research, Scholars Research Library, Vol.2, Issue 1, pp.239-245, 2011.
- [23] Mathivanan V. and Haris, M., "Structural, compositional, optical, thermal and magnetic analysis of undoped, copper and iron doped potassium hydrogen tartrate crystals", Indian Journal of Pure and Applied Physics, Vol.51, pp.851-859, 2013.
- [24] Dabhi, R.M. and Joshi, M.J., "Thermal studies of gel grown zinc tartrate spherulites", Indian Journal of physics, Vol. 76 A, Issue 5, pp.481-485, 2003.
- [25] Joshi, V.S. and Joshi, M.J., "FTIR spectroscopic and thermal studies of calcium tartrate trihydrate crystals grown by gel assistance", Indian Journal of Physics, Vol.75A, Issue2, pp.159-163, 2001.
- $\label{eq:constant} [26] \quad \text{Patel, A.R. and Arora, S.K., "Growth of mixed $r_{1-x}Ca_xC_4H_4O_6$ crystals in gel", Journal of Crystal Growth, Vol. 37, issue 3, pp.343-345, 1977. In the second sec$
- [27] Sanjeevkumar, G., Raveendran, R., Ramadevi, B.S., Alexander, V.V., "Growth features of ammonium hydrogen d-tartrate single crystals", Bulletin of Material Science, Vo.27, Issue4, pp.323-325,2004.
- [28] Cheng Dong, "Powder X: Windows-95-based program for powder X-ray diffraction data processing", Journal of Applied Crystallography, Vol. 32, pp.838, 1999.