

Preponderance of RBI Grade 81 as a Chemical Additive for Soil Modification

Riddhi Choksi¹, C. B. Mishra², Nandan Patel³

P.G. Student, Department of Civil Engineering, BVM Engineering College, V. V. Nagar, Anand, India¹

Associate Professor, Department of Civil Engineering, BVM Engineering College, V. V. Nagar, Anand, India²

Assistant Professor, Department of Civil Engineering, B & B Institute of Technology, V. V. Nagar, Anand, India³

ABSTRACT: Soil is the fundamental establishment for any asphalt. It is required to hold up under the heaps without disappointment. In this investigation, at first the examination of ordinary soil is done to survey the engineering properties as showed by Indian Standard (1498 – 1970) by organizing investigation centre tests and to assess the alteration in properties by the using RBI Grade 81 stabilizer of 2%, 4%, 6% and 8% measurement to be utilized as a piece of the flexible pavement for the economy. The result helps in taking a gander at the adjustment in CBR, OMC and MDD esteem when soils were settled by RBI Grade-81. This likewise gets the ideal mix of soil and RBI Grade 81 which gives least cost procedure to building asphalt. By influencing utilization of RBI Grade-81 as stabilizer, fantastic load bearing limit is achieved.

KEYWORDS: CBR, MDD, RBI Grade-81, OMC, Stabilization

I. INTRODUCTION

Numerous sort of expansive soil and covers expansive region of world, for the most part found in the dry and semi bone-dry area. In India it covers around 20% of land region and incorporates roughly the whole Deccan Plateau, Maharashtra, Karnataka, Andhra Pradesh and part of Gujarat and Madhya Pradesh. It displays low bearing limit and high volume change because of the nearness of montmorillonite soil mineral. Adjustment of soil is a powerful strategy for enhancing the quality, firmness and workability of the soil. As of late different polymer stabilizers have risen and are being utilized for soil adjustment. RBI Grade-81 is one of them. It supports speedier application periods and can slash down the cost of development of asphalt and give asphalt a prevalent strength and quality.

II. LITERATURE REVIEW

Alaka Sridhar et al.[1] presented in his study that expansive soils pose a great problem especially for foundations, & using the locally available in situ soils is a big issue. RBI Grade-81 can be mixed in proper proportions to achieve desired results. Modified Proctor Test on Black Cotton soil is conducted and the following proportions 1%, 2%, 4%, 6% and obtained results for OMC & MDD.

Neelesh Raghuwanshi et al.[2] presume that with the expansion of RBI Grade-81 the plastic furthest reaches of soil increments and fluid point of confinement of soil abatements and hence versatility record of soil additionally diminishes. MDD reductions and OMC increments with the expansion of RBI Grade-81 however the quality does not diminish with lessening of MDD. With the expansion of RBI Grade-81 and with the increment of curing period span, the splashed CBR and UCS esteem likewise increments. The cost of asphalt for 2% RBI Grade-81 was observed to be least, among the various instances of soil and RBI Grade-81 blend. With the expansion of RBI content, the free swell record of soil diminishes.

International Journal of Innovative Research in Science, Engineering and Technology

(A High Impact Factor, Monthly, Peer Reviewed Journal)

Visit: www.ijirset.com

Vol. 7, Issue 5, May 2018

Lekha B.M. et al.[3] have led an examination on "Research center Performance of RBI 81 Stabilized Soil for Pavements". The gathered soil tests were treated with RBI 81 in different blend proportions. Splashed CBR test comes about show that the stabilizer utilized functions admirably with firm soils, (for example, BC soils). Exhaustion life test comes about show a high weariness life for every single treated soil when subjected to rehash stacking (thinking about 1/3rd UCS quality qualities) when contrasted with the untreated soils.

Mamta et al.[4] led an investigation to enhance the designing properties of BC soil and lateritic (red soil) by utilizing RBI Grade-81. The dark cotton soil and red soil blended with 0%, 1% and 2% of RBI-81 were tried for Atterberg's point of confinement test, CBR test and UCS test. The CBR estimation of dark cotton soil was 4.5% which expanded to 5.7% and 7.1% for soil blended with 1% and 2% RBI stabilizer under unsoaked condition and 7% and 10% for soil blended with 1% and 2% RBI stabilizer following 3 days curing period. The CBR estimation of red soil was 8.3% which expanded to 11.4% and 12.3% for soil blended with 1% and 2% RBI stabilizer under unsoaked condition and 13% and 15% for soil blended with 1% and 2% RBI stabilizer following 3 days curing period. This investigation reasoned that RBI-81 is viable stabilizer from upgrade of geotechnical properties of lateritic soil and Black cotton Soil.

Venugopal et al.[5] creator has endeavor to enhance the dark cotton soil with RBI Grade-81. The examination of the quality outcomes with or without RBI Grade-81 has been finished. Different examples have been made by taking soil with various rate 2%, 4%, 6% and 8% of RBI Grade-81. The essential research center test outcomes demonstrated that the soil has low penetrability, low quality and high volume change properties. Soil has a place with CH amass according to IS order. The particular gravity expanded with increment in rate measurement of stabilizer. Subsequently, 6% of RBI Grade-81 is considered as ideal rate for dark cotton soil. The soil with the expansion of stabilizer has demonstrated the lessening in Plasticity Index of the soil with expanded in the % measurements of stabilizer which was observed to support. OMC expanded and MDD diminished marginally because of the expansion of RBI Grade-81 when contrasted and local soil is appropriate for subgrade of street. There was an extreme change in splashed CBR of treated soil. CBR changes were observed to be critical at 6% RBI content for unsoaked and 4 days of drenching as it accomplishes the required an incentive according to the Indian street congress models. The expansion in UCS esteem compares to the expansion in RBI Grade-81 content was observed to be critical at 6% of RBI Grade-81 content and further expansion makes the UCS esteem a genuinely noteworthy increments.

III. MATERIALS

- **Soil:**

The Soil is collected from the SURAT city (kamrej to chalthal) NH-6 at 1.5 m depth. The soil used is the extracted waste tarnish, which on the visual test and by laboratory test known to be clay soil. The tarnish is average highly clayey soil, i.e. CH soil (table 2). Test according to Indian Standards are performed on the soil to examine the properties of untreated and treated the soil with stabilizer. Properties of clay soil are shown in table 1.

Table 1 Properties of parent soil

Sr.no.	Property	Value
1	Specific gravity	2.4
2	Liquid limit	50%
3	Plastic limit	30%
4	Plasticity index	20%
5	Optimum moisture index	17.50%
6	Maximum dry density	1.74gm/cc
7	Unconfined compressive strength	1.77kg/cm ²
8.	California bearing ratio	3.36%

International Journal of Innovative Research in Science, Engineering and Technology

(A High Impact Factor, Monthly, Peer Reviewed Journal)

Visit: www.ijirset.com

Vol. 7, Issue 5, May 2018

Table 2 Grain size distribution

Soil	Grain Size Distribution			IS Classification
	Gravel (%)	Sand (%)	Silt/Clay (%)	
Clay Soil	5	16	79	CH

- RBI Grade 81:**

Road Building International Grade-81 is a chemical stabilizer which has been used by various researchers for improving the properties of different type of soils. Table 3 shows the summary Physical properties and Chemical properties of RBI Grade-81. It reacts with soil by hydration reaction and strength of soil treated with it increases with age.

Table 3: Summary of Physical properties and Chemical properties of RBI Grade-81

Physical Properties of RBI Grade-81		Chemical Properties of RBI Grade-81	
Properties	RBI Grade-81	Properties	% By Mass
Appearance	Beige powder	Calcium Oxide (CaO)	52-56
Odour	Odourless	Silicon Dioxide (SiO ₂)	15-19
pH	12.5 (saturated paste)	Sulphur TriOxide (SO ₃)	9-11
Vapour pressure	Not measurable	Aluminium Oxide (Al ₂ O ₃)	5-7
Flammability	Inflammable	Iron Oxide (Fe ₂ O ₃)	0-2
Specific Gravity	2.5	Magnesium Oxide (MgO)	0-1
Solubility	In water 0.2pts/100pts	Fibers (polypropylene)	0-1
Freezing point	None, solid	Additives	0-4
Viscosity	None, solid		

IV. EXPERIMENTAL RESULTS

- Atterberg's test:**

It precisely portrays limits utilizing dampness substance at the particular focuses where the physical changes happen. Information of these qualities helps in plan of streets. The qualities can add to ID of possibly broad soils and are executed according to IS 2720: Part 5. The estimations of Atterberg's points of confinement are as appeared in table 4. The outcome demonstrates genuinely huge lessening in Plasticity Index (PI) showing a change in soil.

International Journal of Innovative Research in Science, Engineering and Technology

(A High Impact Factor, Monthly, Peer Reviewed Journal)

Visit: www.ijirset.com

Vol. 7, Issue 5, May 2018

Table 4: Atterberg's limits of clay soil

RBI Content (%)	LL (%)	PL (%)	PI (%)
0	50	30	20
2	46	32	14
4	44	35	09
6	41	37	04
8	40	38	02

• **Standard Proctor Test**

The Proctor Compaction Test and its variations are utilized to decide ideal dampness content for soils. This test is particularly valuable while deciding the connection between water content and the dry unit weight of soils to build up the greatest thickness of a soil required for a fill region according to IS 2720: Part 8. The outcomes are introduced in figure 1,2,3,4. It can be seen that there is noteworthy changes in the MDD and OMC because of the expansion of RBI Grade-81 to the local soil.




Figure 1 MDD & OMC for 2% RBI Grade 81




Figure 3 MDD & OMC for 6% RBI Grade 81




Figure 2 MDD & OMC for 4% RBI Grade 81




Figure 4 MDD & OMC for 8% RBI Grade 81

International Journal of Innovative Research in Science, Engineering and Technology

(A High Impact Factor, Monthly, Peer Reviewed Journal)

Visit: www.ijirset.com

Vol. 7, Issue 5, May 2018

• California Bearing Ratio (CBR)

California bearing proportion (CBR) is an observational test much of the time utilized as apart of the appraisal of granular materials in base, subbase and subgrade layers of street. CBR esteem has been connected with some crucial properties of soils, for example, pliancy records, grain-measure circulation, bearing limit and embellishment dampness content. Test is directed according to IS 2720: Part 16 for local soil and soil blended with RBI Grade-81 with fluctuated measurements. The outcomes are appeared in table 5.

Table 5: CBR of RBI Grade 81

RBI Content (%)	CBR (%)
0	3.36
2	9.27
4	10.15
6	15.99
8	13.07

V. CONCLUSION

The examination completed in lab presumes that dirt has a place with CH gather according to IS characterization. Results demonstrate that an exceptional change in drenched CBR of treated soil is seen and that excessively rising request indicating change in soil with an expansion of RBI Grade 81 and that too at 6% the quality, strength and life time of street will be more as contrast with customary built street.

REFERENCES

- [1] Alaka Sreedhar, G. M. (2016). A Study on Soil Stabilization Using Rbi Grade 81. IOSR Journal of Mechanical and Civil Engineering. e-ISSN: 2278-1684, p-ISSN : 2320-334X PP 72-79.
- [2] Lekha B.M. and A. U. Ravi Shankar (2014) "Laboratory performance of RBI 81 stabilized soils for pavements". International Journal of Civil Engineering Research. ISSN 2278-3652, Volume 5, Number 2, 2014.
- [3] Mamta, Mallikarjun. Honna (2014) "A comparative studies of black cotton soil and lateritic soil using RBI grade 81". IJRET: International Journal of Research in Engineering and Technology e-ISSN: 2319-1163 | p-ISSN: 2321-7308, Volume: 03 Special Issue: 03, May-2014, NCRIET-2014.
- [4] Neelesh Raghuwanshi, S. K. (JULY,2016). A review on soil stabilization using RBI grade-81. International Research Journal of Engineering and Technology. e-ISSN: 2395-0056, p-ISSN: 2395-0072, Volume: 03, Issue: 07. July-2016.
- [5] Venugopal G, C. F. (December 2014). Studies on Black Cotton Soil Stabilization. International Journal of Innovative Research in Science. ISSN: 2319-8753 Vol. 3, Issue 12, December 2014
- [6] Tejinder Singh & Navjot Riar (2013) "Strengthening of sub-grade by using RBI Grade-81, a case study". IOSR Journal of Mechanical and Civil Engineering (IOSRJMCE) e-ISSN: 2278-1684, p-ISSN: 2320-334X, Volume 8, Issue 6 (Sep.-Oct. 2013).
- [7] IS 1498-1970, "Soil Classification"
- [8] IS: 2720 (Part 2) - 1973, "Determination of Water Content"
- [9] IS: 2720 (Part 4) - 1985, "Determination of Grain Size Analysis"
- [10] IS: 2720 (Part 5) - 1985, "Determination of Liquid and Plastic Limit"
- [11] IS: 2720 (Part 8) - 1983, "Determination of Water Content - Dry Density Relation Using Heavy Compaction"
- [12] IS: 2720 (Part 16) - 1987, "Laboratory Determination of CBR"
- [13] IS: 2720 (Part X) - 1991, "Determination of Unconfined Compressive Strength"