

# International Journal of Innovative Research in Science, Engineering and Technology

(A High Impact Factor, Monthly, Peer Reviewed Journal)

Visit: [www.ijirset.com](http://www.ijirset.com)

Vol. 8, Issue 3, March 2019

## Utilization of Artificial Aggregates

V.Aravindh<sup>1</sup>, S.Christy Immanuel Raj<sup>2</sup>, S.Kaviyaran<sup>3</sup>, P.Mahendhiran<sup>4</sup>, P.Balamurugan<sup>5</sup>

UG Student, Department of Civil Engineering, Dhanalakshmi Srinivasan Institute of Technology, Trichy,  
Tamilnadu, India<sup>1</sup>

UG Student, Department of Civil Engineering, Dhanalakshmi Srinivasan Institute of Technology, Trichy,  
Tamilnadu, India<sup>2</sup>

UG Student, Department of Civil Engineering, Dhanalakshmi Srinivasan Institute of Technology, Trichy,  
Tamilnadu, India<sup>3</sup>

UG Student, Department of Civil Engineering, Dhanalakshmi Srinivasan Institute of Technology, Trichy,  
Tamilnadu, India<sup>4</sup>

Assistant Professor, Dept. of Civil Engineering, Dhanalakshmi Srinivasan Institute of Technology, Trichy,  
Tamilnadu, India<sup>5</sup>

**ABSTRACT:** Infrastructure development is still dominant in Upgrading countries. These exercises require countless aggregates. To make cement concrete and asphalt concrete, it requires 60% to 75% of aggregate in total volume of the mixture. This high volume of totals may cause decrease on accessibility of regular total. Another issue is that not all zone in india can give satisfactory totals with the goal that it can bolster the foundation advancement particularly in remote zones. The total preparation may confront disturbance this examination endeavors to show a thought of making a fake total. The artificial aggregate is made by mixing the alkali silica, named as fly ash geopolymer with the alkaline solution.

**KEYWORDS:** Fly ash & Alkaline solution

### I. INTRODUCTION

The name geopolymer was coined by a french educator davidovits in 1978 to address a wide extent of materials depicted by frameworks of inorganic molecules. The geopolymers rely upon thermally actuated common materials like meta kaolinite or mechanical results like fly cinder or slag to give a wellspring of silicon (Si) and aluminum (Al). These silicon and aluminum is broken up in a soluble enacting arrangement and in this manner polymerizes into atomic chains and turn into the folio. Educator B. Vijaya rangan 2008 curtin college australia expressed that "the polymerization procedure includes a significantly quick substance response under antacid conditions On silicon aluminum minerals that outcomes in a three dimensional polymeric chain and ring stucture...." 4 a definitive structure of the geopolymer depends to a great extent on the proportion of si to al si al with the materials frequently considered for use in transportation foundatione typically having an Si:Al between 2 and 3.5 5 &6 . The counterfeit total is made by blending the soluble base silica named as fly powder geopolymer with the basic arrangement watchwords fly cinder basic arrangement I Polymeric chain and ring structure comprising of si o al o bonds7 the schematic development of geopolymer material can be appeared portrayed by conditions.

### II. NECESSITIES OF ARTIFICIAL AGGREGATE

Improvement is one of the rapidly creating fields overall as indicated by the present world estimations reliably around 260 00 000 tons of cement is required. This quantity will be increased by 25% inside a range of another 10 years. Since

# International Journal of Innovative Research in Science, Engineering and Technology

(A High Impact Factor, Monthly, Peer Reviewed Journal)

Visit: [www.ijirset.com](http://www.ijirset.com)

Vol. 8, Issue 3, March 2019

the lime stone is the standard source material for the ordinary portland bond a genuine absence of limestone may come following 25 to 50 years. Increasingly finished while creating one ton of bond roughly one ton of carbon di oxide will be discharged to the air which is a noteworthy risk for nature. Notwithstanding the above tremendous amount of vitality is additionally required for the creation of concrete thus it is most fundamental to locate an elective cover. The solid creation delivered carbon di oxide which dirties the atmosphere .The Warm business makes a waste called flyash which is fundamentally dumped on the earth has larges regions. The waste water from the compound enterprises is released into the ground which debases ground water. By creating geopolymers solid all the previously mentioned issues will be unraveled by revising them. Squander fly slag from warm industry + squander water from synthetic refineries = geopolymers concrete. Since geopolymers concrete doesn't use any bond the age of bond will be decreased and consequently the contamination of environment by the discharge of Carbon di oxide will likewise be limited.

### III. MATERIALS USED

Coming up next are the constituents of geopolymers concrete,

- Cement
- Fine Aggregate

Other Materials,

- Flyash
- Sodium Hydroxide
- Sodium Silicate
- Manganese Dioxide

### IV. EXPERIMENTAL PROCEDURE

The materials used are volcano ash to be reacting with the geopolymers binder alkaline activator consisting of sodium silicate ( $\text{Na}_2\text{SiO}_3$ ) and sodium hydroxide ( $\text{NaOH}$ ) solutions. The sodium hydroxide powder utilized was of 99% virtue and fixed at 8M in this examination. The sodium hydroxide and sodium silicate were first blended and mixed until the soluble activator framed a homogeneous arrangement. The proportion  $\text{Na}_2\text{SiO}_3/\text{NaOH}$  utilized was 0.6 geopolymers glue were set up by blending well of lava powder with the essential activator. The volcano ash / alkaline activator ratio was 1.7 The blending material was blended into a homogeneous glue blend for five minutes the glue must be palleted as appeared in fig 1 and afterward dried at a temperature of  $60^\circ\text{C}$  for 30 minutes to shape the 14 20 mm total the pelletized fake geopolymers total was then sintered for 1 hour at 500 600 and  $800^\circ\text{C}$ . The grain estimate conveyance must meet the ASTM C 33 necessity for use as a counterfeit total.

#### 1. PRODUCTION OF GEOPOLYMER ARTIFICIAL AGGREGATE:

The following procedure is used for preparation of artificial aggregate:

- Preparation of  $\text{NaOH}$  solution: The required quantity of commercially available  $\text{NaOH}$  pellets is dissolved in water to obtain required molarity of  $\text{NaOH}$  solution. In this work, 16M  $\text{NaOH}$  solution is used. In order to obtain 1kg of 8 M  $\text{NaOH}$  solution, 254gms of  $\text{NaOH}$  pellets and remaining portion of water are mixed together.
- Readiness of  $\text{Na}_2\text{SiO}_3$  arrangement the  $\text{Na}_2\text{SiO}_3$  arrangement is financially accessible in market in gel structure.
- Preparation of antacid arrangement: The  $\text{NaOH}$  solution and  $\text{Na}_2\text{SiO}_3$  solution are mixed together in correct proportions in order to obtain required alkaline solution. In this work,  $\text{NaOH}$  solution and  $\text{Na}_2\text{SiO}_3$  ratio is taken as 1:2.5. After preparing alkaline solution, it should be kept for 24hrs before mixing with fly ash.

#### 2. AGGREGATE PELLATIZATION PROCESS:

In the pelletization effectiveness communicated in rate mass of total of size more prominent than 4.75 mm produced as against the quantity of flyash used by experimentally. A Circle pelletizer with arrangement for changing and controlling the tendency of the plate.

## International Journal of Innovative Research in Science, Engineering and Technology

(A High Impact Factor, Monthly, Peer Reviewed Journal)

Visit: [www.ijirset.com](http://www.ijirset.com)

Vol. 8, Issue 3, March 2019

- To deliver the fly cinder total by pelletization process water was added to the blend fly fiery debris + soluble base activator the substance were completely blended of fly searing remains.
- Adjusting the angle of mixer drum as 35 - 55 degree and control the rotate disc in the vertical manner at the varying speed as 10 - 100 rpm with 1rpm accuracy.
- At first some level of water is added to the folio and poured in to the plate remaining water is showered amid the pivoting time frame in light of the fact that While turning period in light of the fact that while pivoting without water in the plate the fly fiery remains control will in general structure knots and does not build the conveyance of molecule measure. The pelles are shaped in exact length of 20mm.

The obtained Geopolymerpellatized aggregate is shown in figure



**Aggregate pellatization**



**Pulverized Artificial Aggregate**

### 3. AGGREGATE PULVERISING:

Fly blazing flotsam and jetsam is blended with the alkaline solution thoroughly. Then the mass is heat cured for 24hrs. The hardened mass is then pulverized in to artificial aggregates by hammer or by crushing mass blocks. The pulverised aggregates are then sieved by using 20mm sieve so that the required 20mm artificial aggregate is obtained for grading of aggregates. .

## V. TESTS RESULTS

### 1. COMPRESSIVE TEST:

Every one of the shapes were tried to discover compressive quality by utilizing the pressure testing machine ctm the rate of stacking was 2 5kn/s amid the test. The compressive nature of concrete 3D squares were tried at 7 and 21 days the consequences of the discoveries of the present work is completely coordinating with the prior agents. At the temperature of 70 c for the time of two hours the examples were appearing compressive quality for the molarity of 12m of soluble arrangement of KOH. The optimum usage of superplasticizer was 1.5% by weight of binder.

# International Journal of Innovative Research in Science, Engineering and Technology

(A High Impact Factor, Monthly, Peer Reviewed Journal)

Visit: [www.ijirset.com](http://www.ijirset.com)

Vol. 8, Issue 3, March 2019



Failure Pattern of Specimen Test

## 2.DIRECT TENSILE STRENGTH:

Geopolymer mortars examples for direct strain are thrown with the extraordinarily arranged molds and the standard molds of size 100mm×100mm×500mm are utilized for flexure. They are put into the sight-seeing ovens for restoring at determined temperature of 30oc and 60oc and permitted to remedy for 24 hourss. Specimens are de-moulded and allowed to ambient curing at sufficient room temperature until for test process. The Geopolymer mortar specimens are tested for direct tensile strength at the age of 28 days. The mean of three tried examples each for direct pressure and flexure is accounted for as the delegate quality of the comparing blend.

## TESTS AND RESULTS


Molarity	Curing temperature ( °C)	Cube compressive strength (MPa)	Prism compressive strength (MPa)	Direct tensile strength (MPa)	Flexural strength (MPa)
M1	60 °C	26.46	18.7	3.33	3.94
M2	70°C	38.88	21.74	3.54	4.8
M3	80°C	34.12	25.42	3.74	5.68
M1	60°C	29.68	24.07	3.45	5.37
M2	70°C	20.06	28.13	3.95	5.96
M3	80°C	38.08	29.77	5.11	6.88

## International Journal of Innovative Research in Science, Engineering and Technology

(A High Impact Factor, Monthly, Peer Reviewed Journal)

Visit: [www.ijirset.com](http://www.ijirset.com)

Vol. 8, Issue 3, March 2019



### VI. CONCLUSION

In this project work, a new class of geopolymeric binders with replacement of cement and aggregates with industrial waste flyash is obtained which in turn produced. A conservative and ecological inviting cement with less utilization of vitality assets and carbon dioxide discharge. The principle target of the investigation was to investigate the utilization of geopolymer for counterfeit totals. From The available number of scholarly deals with the properties and characteristics of geopolymer strong using fake aggregates admixtures and included substances it is taken note that utilizing low calcium fly slag based cement alongside fake totals it would additionally improve the properties like penetrability and quality looked at to conventional geopolymer concrete. The collected literatures were using various admixtures and additives. Hence, present study aims to conduct experiment on geopolymer aggregate using different mixes of fly ash and alkali activators and to arrive at an optimum proportions.

1. The particular specific gravity of 20mm artificial aggregate obtained is 2.9 and that of 20mm conventional aggregate is 2.69. The specific gravity is increased by 7.25%.
2. The water absorption of 20mm artificial aggregate and 20mm conventional aggregate are approximately same.
3. The impact value of 20mm artificial aggregate and 20mm conventional aggregate are 15.324 and 23.47 respectively. Even if artificial aggregate have high value, it is within the limit for using in wearing surfaces as given in IS code.

### REFERENCES

1. B VijayaRangan, "Mix design and production of fly ash based geopolymerconcrete".The Indian Concrete Journal, May 2008.
2. Sudhakar .M. Rao and Indra Prasad Acharya , Jounal of materials in civil engineering, submitted December 11, 2012; accepted June 18, 2013; posted ahead of print June 20, 2013.
3. Prof more Pratapkishanrao universal diary of creative research in science designing and innovation/vol 2 issue 5 may 2013 4 m.
4. M. I Abdul Aleem and P. D Arumairaj ,*Indian journal of science and technology*, Vol. 5, No.3, March 2012.
5. N A Lloyd and B V Rangan, " Geopolymer concrete : A review of development and opportunities", 35<sup>th</sup> conference on OUR WORLD IN CONCRETE & STRUCTURES: 25-27 August 2010, Singapore.