



e-ISSN: 2319-8753 | p-ISSN: 2347-6710

IJIRSET

International Journal of Innovative Research in
SCIENCE | ENGINEERING | TECHNOLOGY



INTERNATIONAL JOURNAL OF INNOVATIVE RESEARCH

IN SCIENCE | ENGINEERING | TECHNOLOGY

Volume 10, Issue 7, July 2021

ISSN INTERNATIONAL
STANDARD
SERIAL
NUMBER
INDIA

Impact Factor: 7.569



9940 572 462



6381 907 438



ijirset@gmail.com



www.ijirset.com

Review on Thermal Interface Materials used to Improving the Performance and Efficiency of Cooling Packing of Electronic Devices

Musthak.Ahamed.T.H¹, Rahul.H.N², Karan.H.S³, Purushotham.N.G⁴

Department of Mechanical Engineering, Alva's Institute of Engineering and Technology,
Mijar, Moodbedri, Karnataka, India

Abstract- The current highly integrated electronics and energy systems are raising a growing demand for more sophisticated thermal management. Thermal interface material (TIM) is used to enhance heat flow by reducing thermal resistance across the thermal interface between the heat source and the heat sink, and to minimize the variance of the interface resistance as compared to just surface-to-surface contact. In this mini review, the different type of cooling system, along with the recent developments in the thermal properties of various commonly used low melting point alloys used and advanced thermal interface materials are discussed with the new technologies employed for improving the performance of TIMs.

KEYWORDS: Thermal interface materials, heat flow, heat sink, interface resistance, surface-to-surface contact, contact resistance

I. INTRODUCTION

Recently, demands have arisen for electronic equipment's to have more complexity, more multi-functionality, advanced dependency and highly compactness. High density multi-chip packaging technology has been applied in order to meet these demands. However, the greater the scale of high density multi-chip packaging becomes, the more the power dissipation per unit area will be. So, a new package cooling technology has been requested to reduce the chip junction temperature of devices.

Advanced gadgets are being presented day by day in today's world of electronics with more modest size and quicker speed. A well-designed thermal management program is necessary in order to optimize performance, efficiency and reliability for the smooth operation of these electronic gadgets. A heat sink is attached to the semiconductor for efficient transfer of heat from the source to the surrounding. A Thermal Interface Material (TIM) is implemented to improve heat flow across this thermal interface by eliminating air voids.

In light to the need for improved heat dissipation, various forms of liquid cooling and refrigeration are being thought of. All liquid cooling systems have significant drawbacks, including parts and work costs, reduction reliability and expanded weight. Adding up is the fluid pump consuming power. Use of materials with extremely high thermal conductivities can help in implementation the use of convection cooling, efficiently overcoming the need for liquid cooling. Thermoelectric Coolers (TECs), which require input power, are widely used for temperature control of laser diodes and micromechanical devices. Materials with high thermal conductivities can improve thermo electric cooling efficiency and performance with reduction in power consumption and with the increase in shelf life of the component.

TIMs are helpful in eliminating interstitial air gaps from the thermal interface by conforming to the rough and uneven mating surfaces. Since TIMs have significantly higher thermal conductivity than the air they replace, the resistance across the interface decreases, and the junction temperature will be reduced significantly. The different varieties of TIMs include: Elastomeric Pads/Insulators, Thermally Conductive Adhesive Tapes, Phase Change Materials, Thermally Conductive Gap

Fillers, Thermally Conductive “Cure in Place” Compounds, Thermal Compounds or Greases and Thermally Conductive Adhesives.

The success of any thermal interface will totally depend on the design, the quality of the interface material and its proper installation. There is a crucial difference between thermal greases, phase change materials (PCMs), thermal pads and films, adhesives, and alloy composite materials. In principle, a phase change material is a solid at room temperature and then as the device heats up, the PCM changes their phase from a solid to a flowable phase, where the material can fill in all the surface roughness similar to a grease. The phase change materials tend to be much harder than thermal pads, so the pressure required to meet thermal targets often presents a mechanical challenge for design engineers. Manufacturers design and developed thermally conductive compounds and thermal adhesives for the application of heat sinks to high-powered electronic components like Arctic Silver 5 (AS-5), Matrix, Arctic Alumina, Céramique, ArctiClean, Arctic Silver Thermal Adhesive and Arctic Alumina Thermal Adhesive.

The research people have discovered that Carbon has farther more advantages than Silicon. By using carbon as the manufacturing material, we can achieve compact, faster and stronger chips. An electronic Chip is manufactured using carbon as the wafer. A diamond chip works at High Temperature up to 1000 degrees Celsius, while silicon chips stop working above 150 degrees Celsius. Diamond can also resist voltages up to 200 volts, compared to around 20 volts for a silicon chip. By considering this power electronics, such as an inverter, can become made much smaller in size. One drawback is that electricity cannot travel fluently through diamond. As compared to Barium Oxide (BeO) substrate package, diamond substrate package performed better in mean-time-to-failure by a factor of two. A new integral dielectric heat sink material consisting of diamond deposited carbon/carbon composite with metallic layer(s) on the diamond surface is developed that provide the characteristics including microstructure, thermal conductivity, diamond coating quality and thickness of metallized layer.

There exists some low melting point metals, such as Gallium, Caesium, Rubidium, Lead, Tin and Bismuth etc. These metals change its phase from solid state to the liquid state under a few tens of degrees C. However, these materials are very expensive and their available alloy ores are less in numbers that makes them as said before expensive and hard to find.

Advanced electronic devices are developed based on synthetic diamond as the semiconductor material. Chemical Vapor Deposition (CVD) process allows single crystal CVD diamond to be manufactured to a high purity and consistency. CVD Diamond is resistant to heat, radiation and acid attack and boasts the best thermal conductivity of any material near room temperature. It is a good electrical insulator but can be doped like silicon to produce semiconductor devices. It is available in single crystal and polycrystalline forms.

The heat generated within the electronic device is most often concentrated in a small area and that region may experience higher temperature. By even distribution of the localized heat generated by the device, DiaTherm™ (a diamond heat spreader) can improve cooling capability of laser die in assembled devices by 30% to 100%. In this mini review, the updates in the field of thermal properties of various used thermal interface materials are put up with the new technologies employed for improving the performance and efficiency of TIMs.

II. TYPE OF COOLING SYSTEM

A. Air Cooling

Air cooling is still widely used and will always be favored, wherever possible, over all other electronic cooling techniques. But the poor thermal conductive properties of air, require forced circulation of air at speeds which often approach the upper accepted limits for noise and vibration. In general, air-cooling techniques are about to reach extension for cooling of high-power applications. With standard fans a maximum heat transfer coefficient of maybe 150 W/m²K can be achieved with acceptable noise range, which is about 1 W/cm² for a 60°C temperature difference. Most data centers use air-cooled systems for the heat removal process.

The two major air distribution problem have been identified in this type of cooling are stated below:

1. Recirculation air occurs when a flow of air to the equipment is not sufficient and part of the hot air is recirculated, which results in a considerable difference between inlet temperature at the bottom and the top of the rack can occur.
 2. By-pass of the cold air occurs due to a high flow rate or leaks through the cold air path. In this case, part of the cold air stream skips directly from the source to the exhaust air without contributing to the cooling process.
- This poor air management results in a low cooling efficiency and generates a vicious cycle of rising local temperature.

B. Liquid Cooling

As we know liquids have much higher thermal conductivities than gasses. Therefore, liquid cooling is more effective than air cooling. But it had some drawback such as leakage, extra weight, corrosion and condensation. This can be classified as direct cooling and indirect cooling.

By boiling, heat can be carried away over 200kW/cm², using high velocities and high pressure. Liquid-cooled systems can be constructed using micro-channels flow and cold-plate heat exchangers in direct contact with the components, such as CPUs and DIMMs. The emergent liquid cooling technology is the fully immersed direct liquid-cooled system. The server enclosure is fully sealed and contains a fluoro-organic dielectric coolant in direct contact with electronics, which is used to transfer heat to a water jacket by natural convection.

III. THERMAL INTERFACE MATERIALS

A. Selection of Thermal Interface materials

The most challenging and integral part of thermal design process is the selection of the optimal TIM for a specific product application. Having an elemental understanding of their strengths, weaknesses, and applicability is a key to successful selection of the most appropriate interface material. The selection of suitable TIM depends on many factors like: power density, heat dissipation, process requirements, Bond Line thickness (BLT), and rework ability and user preferences.

B. Advanced thermal interface materials

A wide scope of standard and well-designed thermal management materials which includes Silicone and Non-Silicone heat sink compounds, Pads, Gap fillers and Epoxies are accessible around the world. Nano-Crystalline Diamond (NCD) in an amorphous carbon matrix deposited in a nanocomposite film as well as Carbide Nano-Films (CNF) combines the properties of diamond with extremely low friction, high toughness and biocompatibility. Another class of Nano-Thermal Interface Material (NanoTIM) with adhesion functions is developed. Nanoparticles example as nano-silver particles, Nano-Carbon Nanotubes (CNT) and Nano-Silicon Carbide (NSC) particles can be implanted into the Nano-Fibers (NF) to improve the thermal conductivity and to reduce the thermal resistivity. An extreme slender TIM composed of carbon nanotubes, silicon thermal grease, and chloroform was developed which has very low thermal impedance. TSE328-G silicone adhesive is a low viscosity, thermally conductive material, which will be in an uncured state at room temperature and cure to an elastomer after application of heat.

Expanded flexible graphite sheet materials with high thermal conductivity have capacity to adjust well to surfaces. These sheets are porous. The graphite material containing synthetic oil reduces the contact resistance because of decrease in materials elastic modulus and increase in its plastic deformation at low pressures (<700 kPa), shows high thermal stability than graphite material containing mineral oil. For improving the heat dissipation for high brightness LED (light emitting diode), thermal interface material with aluminum and graphite plate are fabricated and incorporated into power LED. An enormous variation in junction temperature and light output among the different heat-sink modules were explored.

The need to dissipate the sizable amounts of heat being generated in low-power electronic devices creates issues. To overcome this, 3M Company provides Thermally Conductive Adhesive Transfer Tapes, Interface pads and epoxies. Adhesive Research offers several sophisticated bonding technologies designed for bus bar, solar cell junction box, and encapsulation applications in crystalline and thin film photovoltaic (PV) modules. In elite performance flip-chip ball grid array (FCBGA) packages for ASIC and microprocessor devices, silver filled Thermal Paste Adhesives (TPA) are utilized.



Carbon Nanotubes (CNT) are sheets of graphite rolled up to make a tube. The dimensions are variable (down to 0.4 nm in diameter) and it exist likewise nanotubes within nanotubes, leading to a distinction between multi-walled and single-walled carbon nanotubes. The un-attached CNT arrays can be extremely good thermal interface materials under moderate load compared to indium sheet and phase-change thermal interface materials. Further, combinations of CNT arrays and existing thermal interface materials can improve these materials' thermal contact conductance. The Carbon Nanotubes and polymer composites can form foams. These lightweight materials foams will be formed with improved electrical, mechanical, and thermal properties. A double layer structure of aligned carbon nanotubes array was successfully developed as a result of the sandwich growth via thermal Chemical Vapor Deposition (CVD) method, for improving the performance of nanotubes-based devices.

Thermal tapes as a TIM function as a strong attachment between a heatsink and heat-generating component with proper heat conduction. They are designed to meet the microelectronic packaging industry's strict requirements. The downside of this tape is that sometimes the thermal resistance for a thick tape can be only marginally better than a dry joint or air gap. Thermal performance would be carefully evaluated alongside shear-creep resistance data of the tapes.

A nanostructured thermal tape is created that conducts heat like a metal while allowing the neighboring materials to expand and contract with temperature changes (metals are too stiff to even consider permitting this). This ability to reduce chip temperatures while remaining compliant is a critical breakthrough for electronic packaging. The nanotape performs so well is because of a combination of binder materials surrounding carbon nanotubes. This allows for very high thermal conduction while remaining flexible to adjust as based on the condition. The nanotape can eradicate solder pads with a thin lightweight material that improves thermal energy management. A process has been developed to integrate the high thermal conductivity of carbon nanotubes into a polymer matrix, thus creating a material with high thermal transport properties for laser and IC chip packaging.

Graphene acts as a strong heat conductor, which could mean lower temperatures and a concrete possibility for chip manufacturers to reach higher processing speeds with relative ease. Graphene is a one atom thick planar sheet of sp² bonded carbon atoms that are densely in a honeycomb crystal lattice packed. Graphene is highly conductive, conducting both heat and electricity better than any other material, including copper, and it is also stronger than diamond. It is almost completely transparent, yet so dense that not even helium, the smallest gas atom, can pass through it. Graphene electronic devices are expected to be substantially faster, thinner and efficient. The theoretical mobility of electrons in pure Graphene is 200 times that of silicon. This will make it extremely interesting material for future high speed electronics and sensors. Graphene Nano Ribbons (GNR) band zig-zag type structure can be semiconducting or metallic depending on width. The multiple layers of graphene show great heat conducting properties that can be harnessed in removing dissipated heat from electronic devices and improve performance as well as shelf life of the component.

IV. TYPICAL LOW-MELTING POINT ALLOY

Theoretically, metals are giant atomic structures held together by metallic bonds. Researchers at Lawrence Livermore National Laboratory have found that liquid sodium initially evolves into a more compact local structure as pressure is increased. In addition, electrons are transformed as well. The electronic cloud gets modified, the electrons sometimes get trapped in interstitial voids of the liquid, and atomic bonds adopt specific directions. Some typical metal coolants and their applications are evaluated as followed by table 1 that lists typical low-melting-point metals and alloys.

Table 1: Thermal properties of typical metal and alloys with low melting point

Metal /alloy	Melting point/°C	Evaporation point/°C	Evaporation pressure/mmHg	Specific heat (kJ·kg ⁻¹ ·K ⁻¹)	Density (kg·m ⁻³)	Thermal conductivity (W·m ⁻¹ ·°C ⁻¹)	Surface tension (N·m ⁻¹)
Mercury	- 38.87	356.65	$1.68 \times 10^{-3a)}$	0.139 ^{a)}	13546 ^{a)}	8.34 ^{a)}	0.455 ^{a)}
Gallium	29.8	2204.8	10^{-12}	0.37 ^{a)}	5907 ^{a)}	29.4 ^{a)}	0.707 ^{a)}
Gallinstan	- 19	> 1300	$< 10^{-8d)}$	0.200	6440 ^{a)}	16.5	0.718 ^{a)}
Cesium	28.65	2023.84	$10^{-6c)}$	0.236 ^{c)}	1796 ^{c)}	17.4 ^{c)}	0.248 ^{c)}
Rubidium	38.85	685.73	6×10^{-6}	0.363 ^{m)}	1470 ^{m)}	29.3 ^{m)}	0.081
Potassium	63.2	756.5	6×10^{-7}	0.78	664 ^{m)}	54.0 ^{m)}	0.103 ^{c)}
Sodium	97.83	881.4	10^{-10}	1.38	926.9 ^{c)}	86.9 ^{c)}	0.194 ^{c)}
Lithium	186	1342.3	10^{-10}	4.389 ^{b)}	515 ^{b)}	41.3 ^{b)}	0.405 ^{b)}
Na ₂₃ K _{76.7}	- 12.6	785	$2.5 \times 10^{-8c)}$	0.9538 ^{a)}	855 ^{c)}	23	0.11 ^{m)}

A. Mercury

Mercury is the only metal that stays as liquid under standard conditions for temperature and pressure. It has a freezing point of - 38.83 °C and a boiling point of 356.73 °C. Compared to other metals, it is a poor conductor of heat, but a fair conductor of electricity. Mercury has one of the narrowest ranges of its liquid state among all metals. The reason for its liquid state below room temperature has not been well disclosed. The most popular explanation is the one using relativistic mechanism. According to the principle of relativity

$$m = \frac{m_0}{\sqrt{(1 - v^2/c^2)}}$$

Where m is the relativistic mass;

m_0 , is the rest mass;

C, is the speed of light;

V, is the speed of the moving object.

The mass of s orbital electron increases with its speed, and 6s orbital contracts and stabilizes. The 6s-6p excitation energy of mercury is much greater than that of zinc and cadmium. So it cannot form a strong bond between mercury atoms unless they have enough energy. The bonding between them is van der Waals force which is so weak that makes mercury appear only in liquid state at room temperature between them is van der Waals force which is so weak that makes mercury appear only in liquid state at room temperature.


B. Gallium and Gallium Alloy

Performances of gallium and gallium alloys are at least as good as or better than mercury in a wide variety of applications. Therefore, gallium based metallic materials can be used as a mercury substitute to produce devices and materials such as temperature sensors and thermometers, pressure sensors or pressure activated switches, pumps and filters, liquid mirror telescopes, fluid unions, slip rings, bougies, sphygmomanometers, dental amalgam and a wide variety of other devices.

Table 2: Typical low-melting-point gallium alloy

Alloys	Melting point/°C	Alloys	Melting point/°C
Galinstan	-19	GaIn ₂₉ Zn ₄	13
GaIn ₁₅ Sn ₁₃ Zn ₁	3	Ga ₇₅ In ₂₅	16
GaIn ₂₅ Sn ₁₃	5	GaSn ₁₂	17
Ga _{62.5} In _{21.5} Sn ₁₆	10.7	GaIn ₁₂ Zn ₁₆	17
Ga _{69.8} In _{17.6} Sn _{12.6}	10.8	GaSn ₈	20
GaIn ₆₀ Sn ₁₀	12	GaZn ₅	25

The melting point of gallium is approximately 29.8°C, which is somewhat higher than needed. In fact, it is expected that a perfect coolant should always stay in liquid state with a wide temperature range, and the low melting point alloy should remain unfrozen at room temperature. According to the phase diagram of GaIn alloys exhibited in Fig. 1, the melting point of GaIn alloy remarkably changes with the addition of In

**Fig. 1:** Phase diagram for GaIn alloy

As is observed from Fig. 1, the eutectic alloy GaIn14.2% (atomic ratio) has a lower melting point of 289 K.

In fact, gallium alloys can possibly be made to form eutectic materials that melt below room temperature, of which galinstan has the lowest melting point of -19°C. But a reliable running of galinstan below 0°C has remained unsuccessful so far.

Liquid metal gallium or its alloys can be developed as excellent coolant for the thermal management of computer chips and other industrial fields because of their favorable thermal properties superior to those of conventional inorganic and organic coolants, such as higher thermal conductivity, higher electrical conductivity, low vapor pressure, low dissolution in water, higher boiling point above 2200°C, and single-phase liquid cooling.



C. Alkali Metal and its Alloys

(a) Alkali metals

Lithium, sodium, potassium, rubidium, and cesium constitute the first group of elements in the periodic table and have quite exceptional properties. They have low melting points and can be manipulated readily in a liquid state. Their operating temperature ranges are narrower than those of previously described metals, while sodium is a normal coolant used in large power stations. Lithium has two outstanding advantages in the task of heat transfer, a very high thermal conductivity and a very large specific heat capacity per unit volume. The relatively high melting points of these metals make them suitable for high temperature areas, such as in waste heat recovery plants. Such liquids are finding ever-increasing use as coolants in, for example, fast nuclear reactors and high-temperature storage batteries. The liquids also have low viscosity, low density and high thermal conductivity, which make them particularly suitable for use as heat-transfer media. Compared with gallium, alkali metals are more active and easily reactive to oxygen and water, and, therefore, of potential fire hazards. It is emphasized that the special safety considerations should be entailed when they are really adopted as coolants. In addition, liquid alkali metals can also act as solvents for other elements such as carbon, oxygen, nitrogen, hydrogen, and heavier elements. The presence of these elements in solution renders the liquid metals corrosive, and techniques have now been developed for their monitoring and removal.

(b) Na-K alloys

Multicomponent mutual liquid solutions of alkali metals are excellent coolants and working fluids for power engineering, technology and metallurgy because they possess the widest temperature range of liquid phase as effective both high-temperature and low-temperature coolants simultaneously.

Na-K alloys, the typical binary system, containing 40% to 90% potassium by weight, are liquid at room temperature. The eutectic mixture with the lowest melting point of -12.6°C has been investigated to contain 76.7% of potassium and 23.3% of sodium. The density of Na-K 76.7 (indicating the mass fraction of potassium is 76.7%) is 866 kg/m^3 at 21°C and 855 kg/m^3 at 100°C , making it less dense than water, but its specific heat capacity is $953.8\text{ J/(kg}^{\circ}\text{C)}$, which is roughly one fourth of that for water. Its thermal conductivity is approximately $23\text{ W/(m}^{\circ}\text{C)}$, which is much higher than the conventional fluid. Thus, if Na-K alloy is adopted as a cooling fluid, a much higher cooling capacity than that of traditional fluids can be obtained. In fact, the first conception of Na-K alloy used as a coolant is that it can be used as the coolant in experimental fast neutron nuclear reactors. Use of lead, pure sodium or the other materials in practical reactors, would require continual heating to maintain the coolant as a liquid, while Na-K alloy overcomes this.

(c) Other Alkali alloys

Compared with gallium alloys, alkali metal containing alloys, such as binary and ternary systems have pretty low melting point, some of which is even lower than Hg, as given in Table 3.

Table 3: Typical alkali metal containing alloys

Alloys	Melting point/°C	Eutectic state
$\text{Cs}_{73.71}\text{K}_{22.14}\text{Na}_{4.14}$	-78.2	Yes
$\text{Cs}_{77}\text{K}_{23}$	-37.5	No
$\text{Cs}_{94.6}\text{Na}_{5.4}$	-31.83	Yes
$\text{K}_{76.7}\text{Na}_{23.3}$	-12.7	Yes
$\text{K}_{78}\text{Na}_{22}$	-11	No
$\text{Na}_{6.2}\text{Rb}_{93.8}$	-4.5	Yes

(d) Wood's metal

Wood's metal (bismuth 50%, lead 25%, tin 12.5% and cadmium 12.5%) has a much lower melting point of 71°C, so it seems impractical to use it as a coolant in chip cooling. However, fortunately, the melting point of Wood's alloy can be reduced with the increase of indium by 1.45°C per 1 wt%. The alloy will have a melting point of 43°C when 19.1% of indium is added. The advantage of Wood's metal lies in the fact that it can intrude into voids and stress-induced micro cracks while the specimen is held at a desired stress level and then solidified to preserve the geometry of the induced micro cracks. For example, by substituting Wood's metal for mercury as the intruding liquid, Lange et al. adopted scanning electron microscopy and imaging techniques to treat the sample after intrusion for the characterization of the pore size distribution of cement-based materials. The important application may be realized in electronic packaging.

(e) Nano liquid metal

Aiming to realize the idealistic heat transfer performance, Ma and Liu proposed to further significantly magnify the conductivity of liquid metal coolant by adding nano particles with superior conductivity to liquid metals or their alloys. This may lead to the emergence of the highest thermally conductive fluid. Precisely speaking, a nano liquid metal is somewhat different from the above mentioned alloys. Probing into its physical properties requires additional work. The calculated results indicate that the effective thermal conductivity is much higher than that of the base liquid metal fluid as shown in Fig. 2




Fig. 2: Thermal conductivity enhancement ratio as a function of volume fraction for different nano-particles in liquid-gallium suspensions

(f) *Tin-Based*

Pewter is one common tin-based low melting alloy that is used. There will normally be a composition base where there will be about 50% tin element in the alloy. Manufacturers select tin due to its malleability when they require a metal that has a ductile characteristic, as it can be molded and shaped without becoming brittle.

(g) *Bismuth-Based*

Bismuth alloys will have a composition that is less of a ductile characteristic than tin, as it can become brittle. Manufacturers use bismuth due to its expansion qualities when it melts and then solidifies as it can expand to up to 3.3%. The more bismuth is in an alloy, the more it expands. It is less expensive than other alloys that are featured and the least toxic as it can be used in applications where there is drinking water present.

(h) *Indium-Based*

Indium alloys can be used when bonding onto gold, glass and ceramic surfaces as well as other materials. It can also weld onto itself and has the ability to wet surfaces that are non-metallic as well as metallic. When looking for a ductile element that offers fantastic fatigue resistance and a variety of low melting points, manufacturers may select indium alloys for their applications.

V. PROPERTIES OF TIMS

The excessive Coefficient of thermal expansion (CTEs) reason excessive thermal stresses while they're connected to the semiconductors and ceramics utilized in digital and optoelectronic applications. The CVD diamond, Kovar, copper / tungsten, copper / molybdenum, and the brand new composites and monolithic thermal control substances display low CTE. The CTE variations won't be sizeable while tool dimensions are small. Reliable difficult solder die connect strategies is used to bond big excessive CTE compound semiconductor cube immediately to copper packaging without compromising both reliability or thermal performance. The low density of TIM substances (like CVD diamond) is beneficial in maximum packaging substances, that's critical in weight-vital applications, inclusive of plane and spacecraft digital systems, pocket book computer systems and different cellular devices. In addition, density is critical even for desk bound applications, due

to the fact stresses bobbing up from surprise hundreds at some stage in shipping (50g is a not unusual place requirement) rely immediately on element mass.

Thermal conductivity, describes the substances gap potential to behavior warmth. Thermal resistance is a degree of the way a fabric of a particular thickness resists the waft of warmth. Thermal conductivity and thermal resistance describe warmth switch inside a fabric as soon as warmth has entered the material. The thermal impedance, of a fabric is described because the sum of its thermal resistance and any touch resistance among it and the contacting surfaces. This sort of records may be used to generate statistics approximately the gap potential of a fabric to comply with surfaces to limit touch Resistance. One look at suggests that the thermal conductivity of TIM adjustments with temperature. When temperature increases, floor contacts among surfaces in which TIM are carried out will be higher or worse, and therefore the thermal resistance version of a bundle may also growth or decrease. The thermal conductivity version with inside the LED chip region adjustments the thermal resistance coefficient of the LED.

VI. TECHNOLOGIES USED FOR IMPROVING THE PERFORMANCE OF TIMS

The CVD methods utilized by Element Six permit the boom of polycrystalline and unmarried crystal CVD diamond movies with constant traits and few defects. By managed production process, the synthesized fabric may be tailor-made to a selected utility at appealing costs. The diamond-like carbon (DLC) movie is deposited with the aid of using radio frequency plasma-greater chemical vapor deposition (rf-PECVD) on silicon (one hundred) wafers the use of methane (CH₄) and hydrogen (H₂) because the precursors. Two new microwave plasma reactors, excited with a hybrid TM₀₁₃ plus TEM₀₀₁ mode are designed and advanced that are operated with inside the 200-four hundred Torr strain regime. High pleasant unmarried crystal diamond (SCD) and polycrystalline diamond (PCD) is synthesized with deposition charges that exceed one hundred microns/hr and reactor strength efficiencies variety from 6 25 mm³ of diamond according to kW-h over a 25 mm diameter synthesis location as strain, strength density and gas chemistry are varied.

A remoted Nanocrystalline Diamond (NCD) fibers are produced at excessive boom charges with the aid of using excessive-strength microwave plasma greater chemical vapor deposition approach (MPECVD). The advanced nanocrystalline nature of the diamond fabric has best crystallinity of the sample. The programs of this novel fabric are in cold-cathode devices, warmth sinks in microelectronics and structural substances in micro- and nanoelectromechanical systems. The Nano diamond debris act as seeds for the in addition boom of NCD at the nanofibers. The affordable volume-averaged pace and temperature distribution have been received with the aid of using treating the microchannel as a fluid saturated porous media. This technique isn't constrained with the aid of using assumptions at the laminar or absolutely advanced nature of the float and is capable of are expecting the entire thermal resistance of any microchannel warmth sinks satisfactorily.

Adhesive studies unveils new bonding technique in a call of Pressure Sensitive Adhesive (PSA) generation for Photovoltaic(PV) producers which supply delivered capability for boosting the competencies and overall performance of a lot of PV modules along with ease-of-handling, non-stop roll formats, and no messy clean-up. Three one-of-a-kind cooling strategies are used the use of heatsink, thermoelectric cooler (TEC) and fan with a view to resolve the warmth dissipation problem. By this approach the thermal resistance reduces and the cooling ability improves. To construct 3 dimensional (3-D) MultiChip Modules (MCMs) for excessive-strength excessive-density lightweight digital systems, massive location free-status CVD-diamond is deposited on Si and Cu substrates as warmth spreading materials.

For the reason of graphite foam thermosyphon layout in electronics cooling, diverse consequences together with graphite foam geometry, sub-cooling, operating fluid effect, and liquid degree had been investigated. The use of graphite foam because the evaporator in a thermosyphon allows the switch of massive quantities of power with quite low temperature distinction and without the want for outside pumping. The graphitized carbon foam used is an open-mobolecular porous cloth that includes a community of interconnected graphite ligaments whose thermal conductivities are as much as 5 instances better than copper. While the majority graphite foam has a thermal conductivity much like aluminum, it has one-5th the density, making it an notable thermal control cloth.



A particular pin-fin carbon fiber epoxy composite cloth warmness sink is used for floor enhancement on the evaporator of thermosyphon. A thermosyphon is a passive method of utilizing two-segment waft in a system, much like a warmness pipe, with the simplest distinction being the absence of capillary action. The carbon-fiber warmness sink exhibited thermal overall performance beneath that of the carbon foam because of a smaller floor location as a consequence of the pin fin layout. However, the thermal overall performance is advanced while in comparison to the opposite conventional pin-fin evaporators. The adhesion capabilities are integrated into the evolved nano-TIMs the usage of lamination or direct blending methods. To acquire this, hot melt adhesive is at once laminated into the nano-TIM substances to acquire adhesion function. Thermally Conductive Resins offer rapid warmness dissipation for quite a few digital and business applications. For the examination of thermal overall performance of sun air collector system, neural community (NN) software program is used for simplification of overall performance analysis. This new formula may be hired with any programming language or spreadsheet program.

VII. FUTURE PROSPECTS

Researchers broaden thermal nanotape to assist cool destiny Central Processing Units (CPUs) and Graphics Processing Units (GPUs). The Grapheme may be used to provide extremely capacitors with a more power garage density than is presently available. Solar cells and gas cells are similarly capacity regions of utility of carbon primarily based totally nanomaterial with inside the subject of power associated applications.

VIII. ECONOMIC STATUS OF THERMAL INTERFACE MATERIAL

Thermal conductivity is the maximum critical requirement in thermal control applications. Values in extra of eight W/cm °K (approximately two times the fee of copper) are ok and recurring in maximum applications. Higher thermal conductivities are feasible but, to acquire them, movies have to be grown at decrease charges. Therefore, manufacturing expenses growth to the factor in which movie charges may be prohibitive. Films have to additionally be fairly thick so as to unfold the warmth properly. As the standard thickness required is three hundred to 500 μm , deposition strategies have to have excessive sufficient charges to maintain deposition instances inside sensible limits. The manner strategies which put off cracks are with inside the manner of development.

About 20% to 35% of the whole plant fee is going to assemble air cooler warmness exchangers in geothermal strength plant. Two layers of warm monitors above the electrical heater in exclusive top stronger the common air speed on the inlet of the version from 1.05 to 1.64msec-1 and more. This imposed layout of the cooling gadget elevated the plant overall performance and reduced the setup fee.

The movies require lapping or sprucing after deposition (typically on each sides). Polishing notably affects manufacturing expenses, (because of the hardness of a few TIM like diamond) and new sprucing strategies are continuously being evolved so as to lessen those expenses. The thermal houses of diamond accredited a fee discount of the general tool bundle despite the fact that the rate of the diamond substrate become better than the preceding substrate. AT&T introduced that thermal control comprised the biggest lively CVD diamond marketplace today. The finest effect at the rate of bulk diamond remains to come. The prospect for decrease expenses in destiny superior structures is excellent, with diamond manufacturing expenses anticipated to drop to much less than \$10/carat earlier than sprucing. Production expenses at this stage will open up new markets which might be rate sensitive.

IX. CONCLUSION

By the observation of the present application, it is clear that the thermal interface alloys or TIMs hold great potential for the upcoming developments in the field of improving the efficiency of the cooling pack of the electronic device. The efficiency of the TIMs mainly depend on the design, material and surface finish of the material. It is crystal clear that, with the help of TIMs the contact resistance can be reduce and hence maximize the heat flow by avoiding the air voids. At present the two major factors that hold back this technology is the cost and way of implementation. More intensive research in this



direction is needed to make the thermal interface materials more efficiently applicable for improving the heat rejection capability of electronic devices.

REFERENCES

- [1] P. kohli, , M. Sobczak, J. Bowin and M. Matthews,” Advanced thermal interface materials for enhanced flip chip BGA”, Proceedings of the 51st Electronic Components Technology Conference, May 29-June 1, USA., pp: 564-570, 2001.
- [2] J.J. Park. and M.Taya,” Design of thermal interface material with high thermal conductivity and measurement apparatus”, J. Electron. Packag., 128: 46-52, 2006.
10.1115/1.2159008
- [3] J. Xu, and T. Fisher,” Enhancement of thermal interface materials with carbon nanotube arrays”, Int. J. Heat Mass Transfer, 49:1658-1666, 2006.
- [4] S. Narumanchi, “ Advanced thermal interface materials for power electronics”, National Renewable Energy Laboratory, November 8, 2007.
- [5] M. Smak, J. Norley, R.A. Reynolds, R. Pachuta and D.W. Krassowski, “Advanced thermal interface materials using natrual graphite”,In Proceedings of the International Electronic Packaging Technical Conference and Exhibition, July 6-11, Maui, HI.
Pp: 253-261, 2003.
10.1115/IPACK2003-35113
- [6] S.S. Verma, “Graphene electronics: Science technology entrepreneur”,2010.
- [7] F.Y. Lim, S. Abdullah and I. Ahmad, “Numerical study of fluid flow and heat transfer in microchannel heat sinks using anisotropic porous media approximation”, J. Applied Sciences,10(18): 2047-2057, 2010.
- [8] A. Sencan and G. Ozdemir, “Comparison of thermal performances predicted and experimental of solar air collecto”., J. Applied Sci.,7(23): 3721-3728, 2007.
- [9] J. Klett, “ High thermal conductivity graphite foams for compact lightweight radiators”, Oak Ridge National Laboratory, May 9, 2002.
- [10] R. Petkie and P. Santini., ” Packaging aspects of CVD diamond in high performance electronics requiring enhanced thermal management”, In Proceedings of the 4th International Symposium on Advanced Packaging Materials, March 15-18, Braselton, GA, USA., pp: 223-228,1998. 10.1109/ISAPM.1998.664463
- [11] N.M. Mohamed, and L.M. Kou, ”Sandwich growth of aligned carbon nanotubes array using thermal chemical vapor deposition method”. Journal of applied sciences, 11(7), pp: 1341-1345, 2011
- [12] Andrew Musgrave, C. S., Lu, N., Sato, R., & Nagai, K. (2019). Gallium–tin alloys as a low melting point liquid metal for repetition-pulse-laser-induced high energy density state toward compact pulse EUV sources. RSC Advances, 9(24), 13927–13932. doi:10.1039/c9ra01905g
- [13] C. M. Arun kumar and P. C. Mukesh kumar., Review on Electronics Cooling Systems. Advances in Natural and Applied Sciences
- [14] Guyue Bo, Long Ren, Xun Xu, Yi Du & Shixue Dou (2018) Recent progress on liquid metals and their applications, Advances in Physics: X, 3:1, 1446359, DOI: 10.1080/23746149.2018.1446359
- [15] Yunxia GAO1 , Lei WANG1 , Haiyan LI1 , Jing LIU1, Liquid metal as energy transportation medium or coolant under harsh environment with temperature below zero centigradeFront. Energy » 2014, Vol. 8 » Issue (1) : 49-61. DOI: 10.1007/s11708-013-0285-3
- [16] Janis Galins, Aigars Laizans, Ainars galins, review of cooling solutions for compact electronic devices DOI: 10.22616/RRD.25.2019.030
- [17] Teng Li · Yong-Gang Lv · Jing Liu · Yi-Xin Zhou A powerful way of cooling computer chip using liquid metal with lowmelting point as the cooling fluid DOI 10.1007/s10010-006-0037-1
- [18] Roshan Manoj A K1, Abhilash C2, Low Melting Point Alloys: A Review ISSN: 2278-0181 Vol. 8 Issue 04, April-2019
- [19] MA Kunquan, LIU Jing, Liquid metal cooling in thermal management of computer chips, DOI 10.1007/s11708-007-0057-3
- [20] A. Miner and U. Ghoshal, Cooling of high-power-density microdevices using liquid metal coolants, DOI: 10.1063/1.1772862



- [21] Yang, E., Guo, H., Guo, J., Shang, J., & Wang, M. (2014). Thermal Performance of Low-Melting-Temperature Alloy Thermal Interface Materials. *Acta Metallurgica Sinica (English Letters)*, 27(2), 290–294. doi:10.1007/s40195-014-0042-6
- [22] Hill, R. F., & Strader, J. L. (2007). Rudimentary Finite Element Thermal Modeling of Platelet-Filled Polymer-Ceramic Composites. *IEEE Transactions on Components and Packaging Technologies*, 30(2), 235–241. doi:10.1109/tcpt.2007.898330
- [23] Yang, X.-H., Tan, S.-C., Ding, Y.-J., Wang, L., Liu, J., & Zhou, Y.-X. (2017). Experimental and numerical investigation of low melting point metal based PCM heat sink with internal fins. *International Communications in Heat and Mass Transfer*, 87, 118–124. doi:10.1016/j.ijheatmasstransfer.2017.07.0
- [24] Farhad Sarvar et.al, “Thermal interface materials - a review of the state of the art”, 2006
- [25] Roy, C. K., Bhavnani, S., Hamilton, M. C., Johnson, R. W., Nguyen, J. L., Knight, R. W., & Harris, D. K. (2015). Investigation into the application of low melting temperature alloys as wet thermal interface materials. *International Journal of Heat and Mass Transfer*, 85, 996–1002. doi:10.1016/j.ijheatmasstransfer.2015.02.029
- [26] Kempers, R., Kolodner, P., Lyons, A., & Robinson, A. J. (2009). A high-precision apparatus for the characterization of thermal interface materials. *Review of Scientific Instruments*, 80(9), 095111. doi:10.1063/1.3193715
- [27] Rauch, B. (n.d.). Understanding the performance characteristics of phase-change thermal interface materials. *ITHERM 2000. The Seventh Intersociety Conference on Thermal and Thermomechanical Phenomena in Electronic Systems* (Cat. No.00CH37069). doi:10.1109/itherm.2000.866806
- [28] Zhao, J.-W., Zhao, R., Huo, Y.-K., & Cheng, W.-L. (2019). Effects of surface roughness, temperature and pressure on interface thermal resistance of thermal interface materials. *International Journal of Heat and Mass Transfer*, 140, 705–716. doi:10.1016/j.ijheatmasstransfer.2019.06.045
- [29] Yang, E., Guo, H., Guo, J., Shang, J., & Wang, M. (2014). Thermal Performance of Low-Melting-Temperature Alloy Thermal Interface Materials. *Acta Metallurgica Sinica (English Letters)*, 27(2), 290–294. doi:10.1007/s40195-014-0042-6
- [30] Yang, E., Guo, H., Guo, J., Shang, J., & Wang, M. (2014). Thermal Performance of Low-Melting-Temperature Alloy Thermal Interface Materials. *Acta Metallurgica Sinica (English Letters)*, 27(2), 290–294. doi:10.1007/s40195-014-0042-6



**Impact Factor:
7.569**



INTERNATIONAL JOURNAL OF INNOVATIVE RESEARCH

IN SCIENCE | ENGINEERING | TECHNOLOGY

 **9940 572 462**  **6381 907 438**  **ijirset@gmail.com**



www.ijirset.com

Scan to save the contact details