



e-ISSN: 2319-8753 | p-ISSN: 2347-6710

IJIRSET

International Journal of Innovative Research in
SCIENCE | ENGINEERING | TECHNOLOGY



INTERNATIONAL JOURNAL OF INNOVATIVE RESEARCH

IN SCIENCE | ENGINEERING | TECHNOLOGY

Volume 10, Issue 7, July 2021

ISSN INTERNATIONAL
STANDARD
SERIAL
NUMBER
INDIA

Impact Factor: 7.569



9940 572 462



6381 907 438



ijirset@gmail.com



www.ijirset.com

Study of Mechanical Properties on Composite of Coconut and Rubber Material

Prof. Sharatchandraprabhu ¹, Mallikarjun G ², Chandrashekhar ², Ananda Bhovi ², Laxmanna H ²

Assistant Professor, Department of Mechanical Engineering, Alva's Institute of Engineering & Technology,

Moodbidri, Dakshina kannada, Karnataka, India¹

Student Scholar, Department of Mechanical Engineering, Alva's Institute of Engineering & Technology, Moodbidri,

Dakshina kannada, Karnataka, India²

ABSTRACT: Normal strands will play a significant job in the arising "green " economy dependent on energy productivity, the utilization of sustainable materials in polymer items, mechanical cycles that decrease fossil fuel by products and recyclable materials that limit squander. Common strands are a sort of inexhaustible assets, which have been recharged ordinarily and human creativity for millennia. They are additionally carbon nonpartisan; they assimilate the equivalent measure of carbon dioxide they produce. These fibers are totally sustainable, natural cordial, high explicit strength, non-grating, minimal effort, and bio-degradability. Because of these attributes, regular filaments have as of late become attractive to specialists and researchers as an elective strategy for strands fortified composites. This audit paper summed up the historical backdrop of characteristic filaments and its applications. Additionally, this paper zeroed in on various properties of normal strand

KEYWORDS: Natural fibre, polymer, carbon

I. INTRODUCTION

A composite material framework is made out of at least two truly particular stages whose mix produces total properties that are not the same as those of its constituents. Composites can be significant in view of its solid and firm, yet light in weight, so proportions of solidarity to weight and solidness to weight are a few times more grounded than steel or aluminium and furthermore conceivable to accomplish mixes of properties not feasible with metals, pottery, or polymers alone

[1]. In the new year, characteristic filaments strengthened composites are treated as most promising material in various application because of its alluring properties (Table 1). Common filaments are currently rule the car, development and branding enterprises by its best mechanical properties. These regular filaments incorporate flax, hemp, jute, sisal, coir and numerous others [2]. The different advertisement advantages of characteristic filaments are low thickness, ease, low energy inputs and tantamount mechanical properties and furthermore better versatility of polymer composites strengthened with common strands, particularly when adjusted with squashed filaments, weaved and 3-D weaved strands. Glass fibre Reinforced Polymer (GFRP) is a fibre strengthened polymer made of a plastic framework fortified by fine strands of glass. Fibre glass is lightweight, solid, and strong material utilized in various enterprises because of their incredible properties. Despite the fact that strength properties are fairly lower than carbon fibre and it is less hardened, the material is normally far less weak, and the crude materials are substantially less costly. Its mass strength and weight properties are truly good when contrasted with metals, and it very well may be handily framed utilizing shaping cycles. These days, normal filaments, for example, sisal and jute fibre composite materials are supplanting the glass and carbon strands inferable from their simple accessibility and cost. The utilization of regular strands is improved strikingly because of the way that the field of use is improved step by step particularly in car ventures. These days, natural composites have acquired expanding interest due to their eco-accommodating properties. A great deal of work has been finished by analysts dependent on these characteristic strands. Normal strands, for example, jute, sisal, silk and coir are modest, plentiful and inexhaustible, lightweight, with low thickness, high strength, and biodegradable. Characteristic strands, for example, jute can possibly be utilized as a substitution for customary fortification materials in composites for applications which require high solidarity to weight proportion and further weight decrease. This section incorporates an overview of the past exploration effectively accessible including the issues of revenue. It presents the exploration chips away at the half and half composites and the impact of different

boundaries on the exhibition of composites concentrated by different specialists. The writing audit is done situated in the accompanying focuses

II. INFLUENCE OF FILLER ON MECHANICAL PROPERTIES

2. Impact of Filler on Mechanical Properties Tapas et al. [4] contemplated the physical and mechanical properties of Al₂O₃ filled jute fibre strengthened epoxy composites. They completed trial to recognize the impact of filler on properties of composites. Jute and Al₂O₃ taken as support and epoxy as network, they have seen that filler rolls out huge improvements on various properties of composites. Moreover they have seen that Hardness, strength, flexural and ten-sile modulus expanded with increment in the fibre and filler and burst strength expanded exclusively by in-wrinkling fibre and diminished also of filler on composites. [5] considered the mechanical properties of woven banana fibre and banana/ mixture fibre composites. The mechanical strength of woven banana/fibre half and half composites in-wrinkles because of the hybridization, with banana strands. Elastic, flexural and sway qualities of the woven mixture composite of banana/ filaments are better than those of the individual strands. Sodium lauryl (SLS) medicines seem to give an extra improvement in mechanical strength through upgraded holding. Morphological investigations of cracked mechanical testing tests were performed by examining electron microscopy (SEM) to comprehend the de-holding of fibre/framework bond. Explored the mechanical properties of sisal, jute and glass fibre strengthened polyester composites. They saw that the expansion of glass fibre into jute fibre composite brought greatest elasticity. Similarly they have seen that jute and sisal blend composites test is skilled having most extreme flexural strength and greatest effect strength was gotten for the sisal fibre composite. Figure 1 shows a delineation of a composite material. The variety of elasticity, flexural strength and compressive strength of epoxy based sisal-glass cross breed composites has been concentrated by H. Ranganna et al. [5] they have seen that 2 cm fiber length crossover composite demonstrated greatest ideal tractable, flexural and compressive strength than 1 and 3 cm. The impact of salt treatment on the pliable flexural and compressive properties has likewise been considered. It is discovered that treated cross breed composites indicated higher strength than untreated composites. Gopinath et al. [7] tentatively examinations the mechanical conduct of jute fiber in polyester and epoxy lattices and the outcomes demonstrated that jute-polyester handling time is far lesser when contrasted with jute-epoxy overlay. A. Gowthami et al. [8] created sisal regular fiber composites with and without silica by joining 100% biodegradable sisal strands as fortification in the polyester network. The outcomes indicated that the elasticity and tractable modulus of composites with silica are 1.5 and 1.08 occasions more noteworthy than that of composite without silica separately. The effect strength of composite with sand 1.36 and 1.8 occasions more prominent than that of composites without silica and plain polyester, separately. Amar Patnai et al. [9] examined the three body rough wear and mechanical properties of particulate filled glass epoxy composites. Their work intended to concentrate on grating wear conduct of haphazardly arranged glass fiber (RGF) strengthened with epoxy gum loaded up with Al₂O₃, SiC and pine bark dust. Dry sand/elastic wheel scraped area tests (RWAT) were done at 100 rpm test speed. The tests were completed at 50 and 75 N loads by fluctuating the rubbing distance from 200 to 600 m. Test consequences of grating wear tests uncovered that wear of composite was touchy to varieties of rubbing distance and less delicate to sliding speed. Hemalat Jena et al. [10] considered the impact of bamboo fiber composite loaded up with cenosphere. They have re-reported that the effect property of bio-fiber strengthened composite is significantly impacted by expansion of cenosphere as filler and lamina. For a given overlaid composite, the effect strength is expanded with expansion of filler up to a specific cutoff and after which it is diminished on additional option. The outcomes uncover the affectability of the im-settlement properties to the centralization of the fillers. Expansion in lamina from 3 to 7, the effect strength is expanded and on additional expanding the lamina to 9, the strength is diminished. Among each of the 7 layers composite with 1.5 Cenosphere has the most extreme effect strength of 18.132 KJ/m². There is likewise seen that decline in thickness of the composites which are additionally enormously relied upon the substance of fillers and fibre. [11] Considered the mechanical properties of composites of synthetically treated filaments from husk of arecanut and strands from the product of tamarind. They saw that treated filaments demonstrated better outcomes when contrasted with untreated strands. They likewise saw that the strength of the mixture composites increments with increment in volume part of fibre the cross breed composites. In the examination coconut organic product husk strands and tamarind organic product filaments were fortified with Epoxy framework and composites have been created by manual hand layup technique. From the investigation it was discovered that all the cross breed common fibre composites demonstrated greatest mechanical properties for 40% - half of the fibre fortifications. From [4]-[11] writing on fillers inferred that physical and mechanical attributes of composites can be altered by adding a filler stage to the lattice body during the composite readiness. The joining of filler in composite is to improve mechanical and Tribological properties.



Effect of Process Parameters on Mechanical Characteristics

[12] Considers the impact of weight level of jute fibre strengthened in polypropylene based composites and discovered that mechanical properties improved as the jute weight rate expanded up to 40%. D. run et al. [13] presumed that the mechanical properties of composites, for example, rigidity and compressive strength of characteristic fibre composite was accounted for and contrasted the information for glass/epoxy composites. It has been seen structure ductile test that bamboo composite covers having higher rigidity and solidness than jute composite overlays, however not at standard the glass fibre strengthened composite. Compressive test shows that compressive strength and modulus of jute composite is higher than bamboo composite, yet not as much as glass composite the fibre direction point of 0/90, 15/-75, 30/-60, and 45/-45 as appeared in Figure 2, on ductile behaviour were examined and indicated that the fibre direction of 0 gives higher strength and modulus than 45 direction of fibre direction. The mechanical property likewise relies on individual material property. The glass fibre was made misleadingly in a modern plant with extraordinary device while the bamboo and jute fibre was accessible from nature and fabricated by straightforward apparatus and additionally physically that may result irregularity during assembling of item. Because of this explanation the strength of regular filaments doesn't come up to the degree of traditional fibre. Yet, the regular fibre strengthened composite can be utilized in spots where light burden application is significant and the financial aspects of normal fibre composite materials is more advantageous when contrasted with glass fibre composites. [14] Inferred that the composite with half sisal-glass fibre and half sap blend has most extreme rigidity of 97.71 mpa. The breaking heap of sisal-glass fibre fortified composite is found as high (10.285 KN). It is discovered that breaking heap of sisal-glass fibre fortified composite is 1.10 occasions higher than sisal-coir-glass fibre strengthened composite and 1.33 occasions higher than coir-glass fibre strengthened composite. The rate prolongation of coir-glass fibre strengthened composite is found as higher than different composites and subsequently it might have more flexible property in nature. The mixture with composite with 40% sisal-coir-glass filaments and 60% sap blend has high flexural strength (138.87 Mpa) and high effect strength (1.429 KJ/m²). [15] Contemplated the mechanical properties of jute/glass strengthened polyester with water retention condition. Composites are exposed to different water conditions and test were performed by inundating composite example in to three diverse water conditions, refined water, ocean water and acidic water, and water was in room temperature for a time of three weeks and furthermore impact of the different water conditions on the flexural and pressure qualities were examined in this examination. It discovered that the jute composite isn't suitable for submerged applications. [16] considers the properties, for example, tractable and flexural strength of glass/carbon cross breed example with layer by layer grouping before sway and after effect. It is discovered that carbon fibre on the end surfaces in wrinkles flexural strength and furthermore the elastic property of cross breed is better. [17] The mechanical properties of jute/glass fortified epoxy half and half overlay with shifting mixture groupings and unadulterated glass, jute and epoxy composite. Composites arrange hand layup method. Where set up with an aggregate of four heaps by fluctuating the situation of glass and jute. It is discovered that cross breeds have preferable properties over unadulterated jute and epoxy alone however not exactly unadulterated glass. [18] looked into the examination and probability of jute and banana fibre composites emphasizes both mechanical and actual properties and their synthetic creation. The use and utilization of the less expensive merchandise in superior machine is conceivable with the assistance of this composite innovation. Combining the helpful properties of two unique materials, less expensive assembling cost, adaptability and so forth, makes them valuable in different fields of designing, superior applications, for example, recreation and outdoor supplies, transport ping ventures, aviation and so on. Consequently, with this background, it is presumed that, the composite stands the most needed innovation in the quickly developing latest thing. Tara Sen et al. [19] investigated that the use of composites in primary offices is generally focused on expanding the strength of the structure with the assistance of fake filaments and doesn't address the issue of sustainability of these crude materials utilized for fortifying purposes. In an extending total populace and with the expansion of the buying possibilities, the requirement for crude materials needed for underlying reinforcing, that would fulfil the interest on world market is quickly developing. In the Table 2 give data about the properties of different normal strands. [20] examined the tentatively the impact of hybridization of banana and fibre strengthened half breed composites and discovered that cross breed composites offered better protection from water retention as compared to un-mixture composites. [21] examined the impact of hybridization on mechanical legitimate ties of coir-glass half and half cover and discovered that coir fibre (characteristic) flops speedier than glass fibre and incorporation of glass strands at outrageous handles upgrades the mechanical properties of coir covers. Rear. [22] analysed the impacts of number of layers and fibre headings on the mechanical conduct of composites. The outcomes show that the mechanical conduct of covered has improved by in-wrinkling the quantity of layers. The maximal properties were acquired in the event of composite at 5 layers. The composites at 0 degree fibre heading and 0 degree cutting course have high mechanical properties than different cases. The outcomes show a specific distinction between the deliberate and anticipated modulus (Young modulus, shear modulus, Poisson coefficient). This distinction is most likely because of the ideal holding among filaments and framework as considered

in presumptions. [23] With up a successful cycle to improve the mechanical properties of jute/poly lactic corrosive composites. From results they noticed that note that of hydrolysis is important to improve the general presentation. At the point when PLA without change against hydrolysis was utilized, expansion of jute fibre expanded the modulus yet brought down indisputably the rigidity. Ahmed and Mohammad et al. [24] uncovered the hypothetical powerful investigation of Reinforced Concrete chunk under without free and just upheld condition. They demonstrated that there is an impact of the help on the modular properties as the qualities are high in just upheld condition than other. Thus for test examination without free condition gives the exact modular properties. [25] examined the dynamic properties by test and FEA of glass/epoxy fortified mixture composite under sans free condition with various angle proportion and the utilize direction. Here the outcome shows that the expansion in perspective proportion prompts in-wrinkle of normal recurrence and increment of utilize direction about [45/-45] and [30/60] prompts lessening of natural recurrence. From [11]-[25] writing presumed that creation of composites predominantly impacted on the properties of the composites. The mechanical properties, for example, tractable, flexural and sway strength can be altered by manufacturing the composites utilizing various procedures. Figure 3 shows assortments of characteristic strands which are delivered by plants

III. CONCLUSION

The use of regular fibre as fortification in polymer composites was reviewed from the standpoint of position and assumptions for characteristic filaments, creation and portrayal of common fibre, surface refitting utilizing various fillers and properties change in the normal fibre based polymer composite. Contrasting common fibre and glass fibre strengthened composites found that characteristic filaments were in modern application. Also, because of the utilization of regular strands in various designing application and development ventures, it gives approach to monetary improvement in rustic zones. The outcomes in the examination show that, there is a likely hood to upgrade the properties of jute fibre rein-constrained polyester composites. In any case, not many examinations carried on jute/glass fibre fortified epoxy composites and properties. Writing demonstrated that there was no much data accessible on modular test strategy to locate the dynamic properties of the composites. Advancement of an appropriate half breed with a known stacking arrangement will have applications in car industry for weight and cost decrease; this leads path for the examination on mechanical and dynamic properties of jute/glass fibre fortified epoxy cross breed composites by utilizing both static test techniques and dynamic test strategies and approving the outcomes through FE recreation.

REFERENCES

1. Gujjala, R., Ojha, S., Acharya, S.K. and Pal, S.K. (2013) Mechanical Properties of Woven Jute-Glass Hybrid-Reinforced Epoxy Composite. *Journal of Composite Materials*.
2. Pujari, S., Ramakrishna, A. and Suresh Kumar, M. (2014) Comparison of Jute and Banana Fiber Composites: A Review. *International Journal of Current Engineering and Technology*.
3. Sen, T. and Jagannatha Reddy, H.N. (2011) Application of Sisal, Bamboo, Coir and Jute Natural. *International Journal of Innovation, Management and Technology*, 2, 186-191.
4. Samivel, P. (2013) Mechanical Behavior of Stacking Sequence in Kenaf and Banana Fiber Reinforced-Polyester Laminate. *IJSSIR*, 2.
5. Jayabal, S., Natarajan, U. and Sathiyamurthy, S. (2011) Effect of Glass Hybridization and Stacking Sequence on Mechanical Behaviour of Interply Coir-Glass Hybrid Laminate. *Bulletin of Materials Science*, 34, 293-298. <http://dx.doi.org/10.1007/s12034-011-0081-9>
6. Abdellaoui, H., Bensalah, H., Echaabi, J., Bouhfid, R. and Qaiss, A. (2015) Fabrication, Characterization and Modeling of Laminated Composites Based on Woven Jute Fibres Reinforced Epoxy Resin. *Materials and Design*, 68, 104-109. <http://dx.doi.org/10.1016/j.matdes.2014.11.059>
7. Arao, Y., Fujiura, T., Itani, S. and Tanaka, T. (2015) Strength Improvement in Injection-Molded Jute-Fiber-Reinforced Polylactide Green-Composites. *Composites Part B: Engineering*, 68, 200-206. <http://dx.doi.org/10.1016/j.compositesb.2014.08.032>
8. Ahmed, M.S. and Mohammad, F.A. (2014) Theoretical Modal Analysis of Freely and Simply Supported RC Slabs. *International Journal of Mechanical, Aerospace, Industrial and Mechatronics Engineering*, 8, 2026-2030.
9. Ratnaparkhi, S.U. and Sarnobat, S.S. (2013) Vibration Analysis of Composite Plate. *International Journal of Modern Engineering Research (IJMER)*, 3, 377-380.
10. Malhotra, N., Sheikh, K. and Rani, S. (2012) A Review on Mechanical Characterization of Natural Fiber Reinforced Polymer Composites. *Journal of Engineering Research and Studies*, 3, 75-80.



13. Samuel, O.D., Agbo, S. and Adekanye, T.A. (2012) Assessing Mechanical Properties of Natural Fibre Reinforced Composites for Engineering Applications. Journal of Minerals and Materials Characterization and Engineering, 11,780-784. <http://dx.doi.org/10.4236/jmmce.2012.118066>
14. Chandramohan, D. and Marimuthu, K. (2011) A Review on Natural Fibers. IJRRAS, 8, 194-206.
15. Swain, P.T.R. and Biswas, S. (2014) Physical and Mechanical Behavior of Al₂O₃/Jute Fibre Reinforced Epoxy Composites. International Journal of Current Engineering and Technology, 2, 67-71. <http://dx.doi.org/10.14741/ijcet/spl.2.2014.13>
17. Alavudeen, A., Rajini N., Karthikeyan, S., Thiruchitrambalam, M. and Venkateshwaren, N. (2015) Mechanical Properties of Natural Fiber Reinforced Epoxy Composites. Journal of Reinforced Plastics and Composites 20, 1263-1274.
18. Brahim, S. B., and Cheikh, R. B. (2006). "Influence of fiber orientation and volume fraction on the tensile properties of Unidirectional Alfa-Polyester Composite." Composites Science and Technology. .
19. Sarki J., Hassan S.B., Aigbodion V.S., Oghenevwe J.E. Potential of Using Coconut Shell Particle Fillers In Eco-Composite Materials. Journal of Alloys And Compounds, 2011, 2381-2385.
20. Sapuan S.M., Harimi m., Maleque M.A. Mechanical Properties of Epoxy/Coconut Shell Filler Particle Composites. The Arabian Journal of Science And Engineering, 2003, volume 28, 171-181.
21. Nguong C.W., Lee S.N.B. And Sujan D. A Review On Natural fiber Reinforced Polymer Composites. International Journal of Chemical, Nuclear, Metallurgical And Materials Engineering, 2013, Vol: 7 No:1, 33-39.
22. Ticoalu A., Aravinthan T., & Cardona F. A Review of Current Development In Natural fiber Composites for Structural And Infrastructure Applications. Southern Region Engineering Conference, 2010, 11-12.
23. Xue Li, Lope G. Table, Satanarayanan Panigrahi. Chemical Treatments of Natural Fiber For Use in Natural Fiber-Reinforced Composites. A Review, J Polym Environ, 2007, 25-33.
24. Prakash Tudu. Processing And Characterization of Natural fiber Reinforced Polymer Composites. Department of Mechanical Engineering, National Institute of Technology Rourkela. 2009, 35
25. John D. Venables. Polymer matrix-composites. Materials science, 2015.
26. Balaji A., Karthikeyan B., Sundar raji C. Bagasse Fiber-The Future Biocomposite Material. Review International Journal of Chem Tech Research. 2015, Vol: 7, 223-233.
27. Composite. 3rd Malaysian Postgraduate Conference, Sydney, New South Wales, Australia Editors: Noor M.M. Rahman, M.M., And Ismail J., 2013, 22-27.
28. Thoguluva Raghavan Vijayaram. Synthesis And Mechanical Characterization of Processed Cocunut Shell Particulate Reinforced Epoxy Matrix Composite. Metal world, 2013, 31-35.
29. Madakson P.B., Yawas D.S. And Apasi A. Characterization of Cocunut Shell Ash For Potential Utilization In Metal Matrix Composites For Automotive Applications. 2012, Volume:4, No:3, 1190- 1198.
30. Salmah H., Koay S.C., And Hakimah O. Surface Modulation of Coconut Shell Powder Filled Polylactic Acid Biocomposites. Journal of Thermoplastic Composite Material, 2012, 26 (6): 809-819.
31. Thryft R. Design News-Engineering Materials-Coconut & Fabric Improve Biocomposites. 2012.
32. Rahul Chanap. Study of Mechanical And Flexural Properties of Cocunut Shell Ash Reinforced Epoxy Composites. Department of Mechanical Engineering, National Institute of Technology. 2012, R. Udhayasankar et al /Int.J. ChemTech Res. 2015, 8(11), pp 624-637.
33. Hussein Syah S. And Mostapha M. @Zakaria. The Effect of Filler Content on Properties of Cocunut Shell Filled Polyester Composites. Malaysian Polymer Journal, 2011, Volume: 6, No:1, 87-89.
34. K. Gunasekaran *, P.S. Kumar, M. Lakshmi pathy. Mechanical and bond properties of coconut shell concrete. Construction and Building Materials, 2011, 25, 92-98.
35. Vignesh K., Sivakumar K., Prakash M., Palanivel A., And Sriram A. Experimental Analysis of Mechanical Properties of Alkaline Treated Coconut Shell Powder-Polymer Matrix Composites. International Journal of fiber reinforced polyester composites." Composites Science and Technology, 63, 283-2.
36. Neslihan Ozsoy, Murat Ozsoy, Abdullah Mimaroglu. Comparison of Mechanical Characteristics of Chopped Bamboo And Chopped Cocunut Shell Reinforced Epoxy Matrix Composite Materials. European International Journal of Science And Technology, 2014, Volume: 3, No: 8, 15-20.
37. Muthukumar S., Lingadurai K. Investigating The Mechanical Behavior of Coconut Shell And Groundnut Shell Reinforced Polymer Composite. Global Journal of Engineering Science And Researches, 2014, 19-23.
38. Durowaye S.I., Lawall G.I., Akande M.A., Durowaye V.O. Mechanical Properties of Particulate Coconut Shell And palm Fruit Polyester Composites, International Journal of Materials Engineering, 2014, 4 (4): 141-147.
39. Alok Singh, Savita Singh, Aditya Kumar, Anand Kumar. Characterization of Novel Coconut Shell Powder Reinforced-Epoxy Composite, Journal of Engineering And Technology Research, 2014, 1-7.

40. Salleh Z., Islam M.M., Yusopa M.Y.M., And Mun'aim M.A. Idrusa M. Mechanical Properties of Activated Carbon (AC) Coconut Shell Reinforced Polypropylene Composites Encapsulated With Epoxy Resin. Science Direct, 2014, 92-96.
41. Mohan Kumar, Rithin K, Raghuveer, Sharun, Yathiraj, Shanmukh, Shreeprakash. Study on Effect of Stirring Parameters on Tensile Properties of Coconut Shell Powder Reinforced Epoxy Matrix Composite, Applied Mechanics and Materials, 2014, Vols: 592-594, pp 1180-1184.
42. Koay Seong Chun, Salmah Husseinayah & Fatin Nasihah Azizi. Characterization and Properties of Recycled Polypropylene/Coconut Shell Powder Composites: Effect of Sodium Dodecyl Sulfate Modification. Polymer-Plastics Technology and Engineering, 2013, 287-232.
43. Bhaskar. J, V. K. Singh. Physical and Mechanical Properties of Coconut Shell Particle Reinforced Epoxy Composite, Mater. J. Environ. 2013, Sci 227-23.
44. Alok Singh, Savita Singh, Aditya Kumar. Study of Mechanical Properties and Absorption Behavior of Coconut Shell Powder-Epoxy Composites, International Journal of Materials Science and Applications, 2013,2 (5): 157-161.
45. Selma. H, Marliza. M and Teh. P. L. Treated Coconut Shell Reinforced Unsaturated Polyester Composite, International Journal of Engineering & Technology, 2013, 94-103.
46. Bhaskar. J, V. K. Singh, Water Absorption and Compressive Properties of Coconut Shell Particle Reinforced-Epoxy Composite Mater J. Environ. 2013, Sci, 4 (1), 113-118.
47. Olumuyiwa Agunsoye, J, Talabi S. Isaae, Sanni O. Samuel. Study of Mechanical Behavior of Coconut Shell Reinforced Polymer Matrix Composite, Journal of Minerals and Materials Characterization and Engineering, 2012, 11, 774-779.
48. Imoisili. P.E, Ibegbulam. C. M and Adejugbe. T. I. Effect of Concentration of Coconut Shell Ash on the Tensile Properties of Epoxy Composites. The Pacific Journal of Science and Technology, 2012, 463-468.
49. Sareena. C, Ramesan. M. T and Purushothaman. E. Utilization of Coconut Shell Powder as a novel Filler in Natural Rubber, Journal of Reinforced Plastics and Composites, 2012, 533-547.
50. Rahul Chanap. Study of Mechanical and Flexural Properties of Coconut Shell Ash Reinforced-Epoxy Composites, Department of Mechanical Engineering National Institute of Technology, 2012.
51. Pranaya Joshi Chandole. Mechanical and Tribological Behavior of Coconut Shell Char Reinforced Polymer Composites, Department of Mechanical Engineering, National Institute of Technology, 2012.
52. Husseinayah and Mostapha. M and Zakaria. The Effect of Filler Content on Properties of Coconut Shell Filled Polyester Composites, Malaysian Polymer Journal, 2011. Vol.6, 87-93.
- R. Udhayasankar et al /Int.J. ChemTech Res. 2015,8(11),pp 624-637.
53. Tengku Faisal.Z.H, Faisal Amri, Salmah.H and Iqmal Tahir. The Effect of Acetic Acid on Properties of Coconut Shell Filled Low Density Polyethylene Composites, Indo. J. Chem, 2010,334-340.
54. Andrzej K.Bledzki, Abdullah A.Mamun, Jurgen Volk. Barley Husk and Coconut Shell Reinforced Polypropylene Composites: The Effect of Fiber Physical, Chemical and Surface Properties, Composites Science and Technology, 2010,840-846.
55. Roopa. S and Siddaramaiah. Mechanical, Thermal and Morphological Behaviors of Coconut Shell Powder Filled Pu/Ps Bio composites, Advanced Materials Research, 2010,331-334.
56. Ramaraj. B. Modified Poly (Vinyl Alcohol) and Coconut Shell Powder Composite Films: PhysicoMechanical, Thermal Properties and Swelling Studies, Polymer-Plastics Technology and Engineering, 2007,1227-1231.
57. S. Shinoj, R. Visvanathan, S. Panigrahi, and M. Kochubabu, "Oil palm fiber (OPF) and its composites: a review," *Industrial Crops and Products*, vol. 33, no. 1, pp. 7-22, 2011.
58. M. M. Kabir, H. Wang, K. T. Lau, and F. Cardona, "Chemical treatments on plant-based natural fibre reinforced polymer composites: an overview," *Composites Part B: Engineering*, vol. 43, no. 7, pp. 2883-2892, 2012.
59. H. Ku, H. Wang, N. Pattarachaiyakoo, and M. Trada, "A review on the tensile properties of natural fiber reinforced polymer composites," *Composites Part B: Engineering*, vol. 42, no. 4, pp. 856-873, 2011.
60. F. Z. Arrakhiz, M. El Achaby, M. Malha et al., "Mechanical and thermal properties of natural fibers reinforced polymer composites: doum/low density polyethylene," *Materials & Design*, vol. 43, pp. 200-205, 2013.
61. G. Di Bella, V. Fiore, G. Galtieri, C. Borsellino, and A. Valenza, "Effects of natural fibres reinforcement in lime plasters (kenaf and sisal vs. Polypropylene)," *Construction and Building Materials*, vol. 58, pp. 159-165, 2014.
62. M. A. Norul Izani, M. T. Paridah, U. M. K. Anwar, M. Y. Mohd Nor, and P. S. H'Ng, "Effects of fiber treatment on morphology, tensile and thermogravimetric analysis of oil palm empty fruit bunches fibers," *Composites Part B: Engineering*, vol. 45, no. 1, pp. 1251-1257, 2013. View



- 63.I. S. M. A. Tawakkal, M. J. Cran, and S. W. Bigger, "Effect of kenaf fibre loading and thymol concentration on the mechanical and thermal properties of PLA/kenaf/thymol composites," *Industrial Crops and Products*, vol. 61, pp. 74–83, 2014.
- 64.M. J. John and S. Thomas, "Biofibres and biocomposites," *Carbohydrate Polymers*, vol. 71, no. 3, pp. 343–364, 2008.
- 65.E. Jayamani, S. Hamdan, M. R. Rahman, and M. K. B. Bakri, "Comparative study of dielectric properties of hybrid natural fiber composites," *Procedia Engineering*, vol. 97, pp. 536–544, 2014.
- 66.C. C. Eng, N. A. Ibrahim, N. Zainuddin, H. Ariffin, and W. M. Z. W. Yunus, "Impact strength and flexural properties enhancement of methacrylate silane treated oil palm mesocarp fiber reinforced biodegradable hybrid composites," *The Scientific World Journal*, vol. 2014, Article ID 213180, 8 pages, 2014.
- 67.N. Graupner, A. S. Herrmann, and J. Müssig, "Natural and man-made cellulose fibre-reinforced poly (lactic acid)(PLA) composites: an overview about mechanical characteristics and application areas," *Composites Part A: Applied Science and Manufacturing*, vol. 40, no. 6-7, pp. 810–821, 2009.
- 68.K. Bocz, B. Szolnoki, A. Marosi, T. Tábi, M. Wladyka-Przybylak, and G. Marosi, "Flax fibre reinforced PLA/TPS biocomposites flame retarded with multifunctional additive system," *Polymer Degradation and Stability*, vol. 106, pp. 63–73, 2014.
- 69.F. M. Al-Oqla and S. M. Sapuan, "Natural fiber reinforced polymer composites in industrial applications: feasibility of date palm fibers for sustainable automotive industry," *Journal of Cleaner Production*, vol. 66, pp. 347–354, 2014.
- 70.A. K. Mohanty, M. A. Khan, and G. Hinrichsen, "Surface modification of jute and its influence on performance of biodegradable jute-fabric/Biopol composites," *Composites Science and Technology*, vol. 60, no. 7, pp. 1115–1124, 2000.
- 71.T. Hänninen, A. Thygesen, S. Mehmood, B. Madsen, and M. Hughes, "Mechanical processing of bast fibres: the occurrence of damage and its effect on fibre structure," *Industrial Crops and Products*, vol. 39, no. 1, pp. 7–11, 2012.
- 72.V. K. Thakur and M. K. Thakur, "Processing and characterization of natural cellulose fibers/thermoset polymer composites," *Carbohydrate Polymers*, vol. 109, pp. 102–117, 2014.
- 73.I. Van de Weyenberg, J. Ivens, A. De Coster, B. Kino, E. Baetens, and I. Verpoest, "Influence of processing and chemical treatment of flax fibres on their composites," *Composites Science and Technology*, vol. 63, no. 9, pp. 1241–1246, 2003.
- 74.D. Dai and M. Fan, "Wood fibres as reinforcements in natural fibre composites: structure, properties, processing and applications," in *Natural Fibre Composites: Materials, Processes and Properties*, chapter 1, pp. 3–65, Woodhead Publishing, 2014.
- 75.V. S. Srinivasan, S. R. Boopathy, D. Sangeetha, and B. V. Ramnath, "Evaluation of mechanical and thermal properties of banana-flax based natural fibre composite," *Materials & Design*, vol. 60, pp. 620–627, 2014.
- 76.J.-C. Bénézet, A. Stanojlovic-Davidovic, A. Bergeret, L. Ferry, and A. Crespy, "Mechanical and physical properties of expanded starch, reinforced by natural fibres," *Industrial Crops and Products*, vol. 37, no. 1, pp. 435–440, 2012.
- 77.A. R. Kakroodi, S. Cheng, M. Sain, and A. Asiri, "Mechanical, thermal, and morphological properties of nanocomposites based on polyvinyl alcohol and cellulose nanofiber from *Aloe vera* rind," *Journal of Nanomaterials*, vol. 2014, Article ID 903498, 7 pages, 2014.
- 78.M. S. Sreekala, M. G. Kumaran, and S. Thomas, "Stress relaxation behaviour in oil palm fibres," *Materials Letters*, vol. 50, no. 4, pp. 263–273, 2001.
- 79.B. Ren, T. Mizue, K. Goda, and J. Noda, "Effects of fluctuation of fibre orientation on tensile properties of flax sliver-reinforced green composites," *Composite Structures*, vol. 94, no. 12, pp. 3457–3464, 2012.
- 80.Y. Pan and Z. Zhong, "A micromechanical model for the mechanical degradation of natural fiber reinforced composites induced by moisture absorption," *Mechanics of Materials*, vol. 85, pp. 7–15, 2015.
- 81.E. Jayamani, S. Hamdan, M. R. Rahman, and M. K. B. Bakri, "Investigation of fiber surface treatment on mechanical, acoustical and thermal properties of betelnut fiber polyester composites," *Procedia Engineering*, vol. 97, pp. 545–554, 2014.
- 82.L. Boopathi, P. S. Sampath, and K. Mysamy, "Investigation of physical, chemical and mechanical properties of raw and alkali treated *Borassus* fruit fiber," *Composites Part B: Engineering*, vol. 43, no. 8, pp. 3044–3052, 2012.
- 83.M. Ramesh, T. S. A. Atreya, U. S. Aswin, H. Eashwar, and C. Deepa, "Processing and mechanical property evaluation of banana fiber reinforced polymer composites," *Procedia Engineering*, vol. 97, pp. 563–572, 2014.
- 84.N. Venkateshwaran, A. Elaya Perumal, and D. Arunsundaranayagam, "Fiber surface treatment and its effect on mechanical and visco-elastic behaviour of banana/epoxy composite," *Materials & Design*, vol. 47, pp. 151–159, 2013.
- 84.S. N. Monteiro, K. G. Satyanarayana, A. S. Ferreira et al., "Selection of high strength natural fibers," *Matéria*, vol. 15, no. 4, pp. 488–505, 2010.
- 85.H. Ismail, H. D. Rozman, R. M. Jaffri, and Z. A. Mohd Ishak, "Oil palm wood flour reinforced epoxidized natural rubber composites: the effect of filler content and size," *European Polymer Journal*, vol. 33, no. 10–12, pp. 1627–



- 1632, 1997. 105.M. Jawaid and H. P. S. Abdul Khalil, "Cellulosic/synthetic fibre reinforced polymer hybrid composites: a review," *Carbohydrate Polymers*, vol. 86, no. 1, pp. 1–18, 2011.
- 86.M. George, P. G. Mussone, Z. Abboud, and D. C. Bressler, "Characterization of chemically and enzymatically treated hemp fibres using atomic force microscopy and spectroscopy," *Applied Surface Science*, vol. 314, pp. 1019–1025, 2014
- 87.P. Wongsriraksa, K. Togashi, A. Nakai, and H. Hamada, "Continuous natural fiber reinforced thermoplastic composites by fiber surface modification," *Advances in Mechanical Engineering*, vol. 5, Article ID 685104, 2013.



**Impact Factor:
7.569**



INTERNATIONAL JOURNAL OF INNOVATIVE RESEARCH

IN SCIENCE | ENGINEERING | TECHNOLOGY

 **9940 572 462**  **6381 907 438**  **ijirset@gmail.com**



www.ijirset.com

Scan to save the contact details