

e-ISSN: 2319-8753 | p-ISSN: 2320-6710

EDIA

International Journal of Innovative Research in SCIENCE | ENGINEERING | TECHNOLOGY

# INTERNATIONAL JOURNAL OF INNOVATIVE RESEARCH

808

IN SCIENCE | ENGINEERING | TECHNOLOGY

Volume 10, Issue 6, June 2021

INTERNATIONAL STANDARD SERIAL NUMBER INDIA

### Impact Factor: 7.512

9940 572 462

6381 907 438

 $\odot$ 





| e-ISSN: 2319-8753, p-ISSN: 2320-6710| <u>www.ijirset.com</u> | Impact Factor: 7.512|

||Volume 10, Issue 6, June 2021||

|DOI:10.15680/IJIRSET.2021.1006255|

## Study of Soil with Bamboo as A Reinforcement Material In Flexible Pavements

Piyush Agarwal<sup>1</sup>, Kunal Bhansali<sup>2</sup>, Gajendra Darade<sup>3</sup>, Mayur Tanpure<sup>4</sup>

U. G. Student, Department of Civil Engineering, D.Y.Patil S. O. E. T, Lohegaon, Maharashtra, India<sup>1,2,3</sup>

Associate Professor, Department of Civil Engineering, D.Y.Patil S. O. E. T, Lohegaon, Maharashtra, India<sup>4</sup>

**ABSTRACT**: This study tests the mechanical properties of fresh bamboo to explore its suitability for reinforcing subgrade of flexible pavement. A series experiments will be perform using a bamboo species Meshi (local name) and dhophil bamboo soil specimens (Black cotton soil and laterite soil) with bamboo grids that are similar to geogrids. This paper deals with efficiency of using bamboo as a reinforcement in beam and column. Bamboo is one of the oldest traditional building material also bamboo is a versatile material because of its high strength to weight ratio, easy workability and availability. The mechanical tests will include tensile and flexural test on bamboo strips, Standard procter test and CBR test on soil specimen with and without bamboo strips.

KEYWORDS: Meshibamboo, Dhophil bamboo, Black cotton and Laterite soil, CBR, StandardProcterFlexural, Tensile

#### 1) INTRODUCTION

The construction of various infrastructure projects on soft ground has almost become inevitable due to shortage of land in this rapid growing world. Soft ground engineering offers enormous challenges to the engineers across the globe. Ground improvement techniques are the largely preferred techniques for loading bearing application in soft soils. Engineers and scientist are constantly looking for new ground improvement techniques that are cheaper compared with present techniques such as vibrogeosynthetic, (geogrids, geocellsgcomembranes, and geotextile). This technique provides high tensile strength to the soil. Though these techniques has good durability, excellent Mechanical behaviour, and easy laying operation, it increases cost of engineering projects. Compaction, vacuum consolidation, does not comply with current environmental protection standards. Therefore in recent years some research has considered natural green building materials as an alternative to these above techniques. Natural green building materials are advantageous with respect to energy conservation, low cost and renewable.

The use of wood in soil stabilization is not a new concept. The world famous monument TAJ MAHAL is built on gigantic wooden slab made up of Ebony wood supported on deep wall foundation. The massive solid foundation of The TajMahál including the wooden shock absorbers has defied the onslaught of time keeping the superstructure stable for more than three and half century without any deterioration. Generally, in Geotechnical engineering application, bamboo is used in two ways. One is to use a bamboo directly to build a foundation as illustrated in case of the Taj Mahal. The other way to use bamboo as reinforcement in the soft soil to increase its bearing capacity. Bamboo is one of the oldest traditional natural building materials used by mankind which is cost effective and can be successfully utilized for structural and non-structural application. Bamboo is biodegradable material however nowadays techniques are available to increase the durability of bamboo. Due to a distinctive rhizome-dependent system, bamboos are one of the fastest-growing plants in the world and their growth is three times faster than most other species of plants. Bamboo has a six year life cycle. They are renewable and extremely versatile resource with multi-purpose usage. Bamboo as a building material is conventionally associated with the region of Southeast Asia and South America where climate is best suitable for its cultivation.

#### **II. OBJECTIVES**

The aim of this project is to do comparative study of soil with bamboo reinforcement and without bamboo reinforcement in flexible pavement.



| e-ISSN: 2319-8753, p-ISSN: 2320-6710| www.ijirset.com | Impact Factor: 7.512|

#### ||Volume 10, Issue 6, June 2021||

#### |DOI:10.15680/IJIRSET.2021.1006255|

- To compare properties of soil with and without use of bamboo reinforcement by conducting various mechanical test
- To increase load carrying capacity by load dispersion through reinforced sub-base on to the sub-grade.
- To reduce construction cost of flexible pavement by using bamboo reinforcement as an alternative to geo-grid.
- To increase service life of pavements.

#### **III. THEORETICAL CONTENT**

#### BOMBOO

Bamboo is a collective name for different species of Giant grasses. It is estimated that 60–90 genera of bamboo Exist, comprising approximately 1100–1500 species. These species come in various sizes and forms. Bamboo Mainly grows in tropical regions of Asia, Latin America And Africa. Locally available best species of bamboo in Pune are-

- 1. Dandrocalamum strictus.(Meshi bamboo)
- 2. Bambusa vulgaris.(Dhophil bamboo)

#### SOIL

Subgrade is the native material underneath of a Constructed road. Subgrade broadly consists of soil. In This study we are considered two types of soil that are –Black cotton soil and Laterite soil.

• Black cotton soil

Black cotton soil is one of major soil deposits of India. They exhibit height rate of swelling and shrinkage when Exposed to changes in moisture content and hence have Been found to be most troublesome from engineering Consideration.

• Laterite soil

Laterite is a soil and rock type rich In iron and aluminum and is commonly considered to Have formed in hot and wet tropical areas. Nearly all Laterites are of rusty-red coloration, because of high iron Oxide content. It is abundantly found in Konkan, Maharashtra.

#### DEFECTS IN FLEXIBLE PAVEMENT

- Cracking of Flexible Pavements
- Depressions in Flexible Pavements
- Potholes
- Rutting of Flexible Pavements
- Swelling of Flexible Pavements

In order to overcome the above problems, bamboo is added as reinforcing material. The function of reinforcement is to strengthen by additional assistance, material, or support. For the same reason that steel reinforcement is embedded in concrete, reinforcing materials can be incorporated into the base layer of flexible pavements so that the two materials act together to resist forces. Bamboo is a versatile material because of its high strength-to-weight ratio, easy workability and availability. Through research it has been found that some species of bamboo have ultimate tensile strength same as that of mild steel at yield point. Cellulose is the main component present in bamboo which is responsible for mechanical properties of bamboo.

#### **IV.TEST CARRIED OUT ON SPECIMENS**

#### The Tests Performed On Bamboo Specimens Are-

- 1. Tensile strength test
- 2. Flexural strength test



| e-ISSN: 2319-8753, p-ISSN: 2320-6710| <u>www.ijirset.com</u> | Impact Factor: 7.512|

#### ||Volume 10, Issue 6, June 2021||

[DOI:10.15680/IJIRSET.2021.1006255]

• Tensile Strength Test on Bamboo Specimen (IS 6874)

Significance of Tensile Strength

Tensile strength is a measurement of The force required to pull something such as rope, wire, or A structural beam to the point where it breaks .The tensile Strength of a material is the maximum amount of tensile Stress that it can take before failure .Tensile strength of The material is essential to determine its ability to Withstand tensile loads without failure.

• Flexural Strength Test on Bamboo Specimen (Is 1708 Part-5)

Significance Of Flexural Strength

The flexural strength represents the highest stress Experienced within the material at its moment of yield. Flexural strength of a material is determined to know its Ability to resist deformation under load.

#### Test Carried out on Soil specimens Are :

- 1. California Bearing Ratio Test (CBR)
- 2. Standard Procter Test
- California Bearing Ratio Test

#### Significance Of California Bearing Ratio Test

The California Bearing Ratio (CBR) test is a Penetration test used to evaluate the subgrade strength of Roads and pavements. The results of these tests are used With the empirical curves to determine the thickness of Pavement and its component layers. This is the most Widely used method for the design of flexible pavements

• Standard Procter Test

Significance of standard Proctor test

Standard Proctor test is used for determination of the Relation between the water content and the dry density of Soils using light compaction.

#### V. RESULTS AND DISCUSSIONS

#### SOIL RESULT

A. CBR TEST FOR LATERITE SOIL WITHOUT			
BAMBOO REINFORCEMENT			
Placement weight density	= 1.838		
Placement dry density	= 1.46		
Optimum moisture content	= 26.50		
• Soil at natural moisture content	= 3485		
• Soil at placement moisture content	= 4135		
Water added	= 850		
• Passing sieve(mm)20-4.75	= 613gm		
• Passing sieve(mm) 4.75	= 2872gm		
	<ul> <li>BAMBOO REINFORCEMENT</li> <li>Placement weight density</li> <li>Placement dry density</li> <li>Optimum moisture content</li> <li>Soil at natural moisture content</li> <li>Soil at placement moisture content</li> <li>Water added</li> <li>Passing sieve(mm)20-4.75</li> </ul>		

PENETRATION	LOAD	
Mould NO	F	L
0.5	20	13
1.0	28	19
1.5	32	23
2.0	35	29
2.5	38	33
3.0	43	37
4.0	45	45
5.0	49	49
6.0	51	51
7.5	53	55
10.0	50	54
12.5	56	68



| e-ISSN: 2319-8753, p-ISSN: 2320-6710| www.ijirset.com | Impact Factor: 7.512|

#### **||Volume 10, Issue 6, June 2021||**

|DOI:10.15680/IJIRSET.2021.1006255|

#### B. CBR TEST FOR LATERITE SOIL WITH BAMBOO REINFORCEMENT

- = 1.838 Placement weight density •
- Placement dry density = 1.46
- Optimum moisture content = 26.50•
- Soil at natural moisture content = 3485 •
- Soil at placement moisture content = 4135•
- Water added = 850•
- Passing sieve(mm)20-4.75 = 613gm •
- Passing sieve(mm) 4.75 = 2872gm •

PENETRATION	LOAD	
Mould NO	F	L
0.5	20	13
1.0	28	19
1.5	32	23
2.0	35	29
2.5	38	33
3.0	43	37
4.0	45	45
5.0	49	49
6.0	51	51
7.5	53	55
10.0	50	54
12.5	56	68

#### C. CBR TEST FOR BLACK COTTON SOIL WITHOUT BAMBOO REINFORCEMENT

- Placement weight density = 1.732
- Placement dry density = 1.27 •
- Optimum moisture content = 36.470
- Soil at natural moisture content = 3057 ٠
- Soil at placement moisture content = 3849• = 1040
- Water added •
- Passing sieve(mm)20-4.75 = 948gm •
- Passing sieve(mm) 4.75 = 21.09kg

PENETRATION	LOAD	
Mould NO	F	L
0.5	20	13
1.0	28	19
1.5	32	23
2.0	35	29
2.5	38	33
3.0	43	37
4.0	45	45
5.0	49	49
6.0	51	51
7.5	53	55
10.0	50	54
12.5	56	68



| e-ISSN: 2319-8753, p-ISSN: 2320-6710| <u>www.ijirset.com</u> | Impact Factor: 7.512|


#### ||Volume 10, Issue 6, June 2021||

|DOI:10.15680/IJIRSET.2021.1006255|


#### D. CBR TEST FOR BLACK COTTON SOIL WITH BAMBOO REINFORCEMENT

- Placement weight density = 1.732
- Placement dry density = 1.27
- Optimum moisture content = 36.470
- Soil at natural moisture content = 3057
- Soil at placement moisture content = 3849
- Water added = 1040
- Passing sieve(mm)20-4.75 = 948gm
- Passing sieve(mm) 4.75 = 21.09kg

PENETRATION	LOAD	
Mould NO	F	L
0.5	20	13
1.0	28	19
1.5	32	23
2.0	35	29
2.5	38	33
3.0	43	37
4.0	45	45
5.0	49	49
6.0	51	51
7.5	53	55
10.0	50	54
12.5	56	68



OMC : 36.47% MDD : 1.27 g/cc



OMC: 26.20% MDD: 1.46 g/cc

### STANDARD PROCTER TEST

#### BLACK COTTON SOIL

- Optimum Moisture Content = 36.47%
- Maximum Dry Density=1.27 g/cc

LATERITE SOIL

- Optimum Moisture Content=26.20%
- Maximum Dry Density=1.46g/cc




| e-ISSN: 2319-8753, p-ISSN: 2320-6710| <u>www.ijirset.com</u> | Impact Factor: 7.512|

||Volume 10, Issue 6, June 2021||


[DOI:10.15680/IJIRSET.2021.1006255]

#### TENSILE AND FLEXURAL STRENGTH GRAPH

#### A. GRAPHS OF MESHI TENSILE STRENGTH











| e-ISSN: 2319-8753, p-ISSN: 2320-6710| <u>www.ijirset.com</u> | Impact Factor: 7.512|

#### **||Volume 10, Issue 6, June 2021||**






: Load Vs Displacement

Sample no 4

#### C. GRAPH OF MESHI FLEXURAL TEST




#### [DOI:10.15680/IJIRSET.2021.1006255]



| e-ISSN: 2319-8753, p-ISSN: 2320-6710| <u>www.ijirset.com</u> | Impact Factor: 7.512|

#### ||Volume 10, Issue 6, June 2021||

|DOI:10.15680/IJIRSET.2021.1006255|



#### D. GRAPH OF DHOPHIL FLEXURAL TEST

#### VI.CONCLUSION

- Meshi bamboo species shows better tensile and Flexural strength as compare to Dhopil bambooSpecies.
- CBR value of Black cotton soil with bamboo Reinforcement do not show significant variation as Compare to CBR value of black cotton soil without Bamboo reinforcement.
- As there is no significant change in total thickness of Pavement in black cotton soil with bamboo Reinforcement it is not feasible to use bamboo as a Reinforcing material in black cotton soil.
- CBR value of Laterite soil with bamboo reinforcement Show desirable variation as compare to CBR value of Laterite soil without bamboo reinforcement.
- When bamboo reinforcement is used in laterite soil Subgrade, the total pavement thickness changes from 700mm to 540mm which is a desirable change.
- So, it is recommendable to use bamboo reinforcement In laterite soil subgrade.

#### REFERENCES

[1] Aazokhi Waruwu,RikaDeniSusanti(2015), "Behaviour of soil peat with reinforcement of bamboo grid",IOSR Journal of Engineering (IOSRJEN), ISSN€:2250-3021, ISSN (p): 2278-8719,page no.29-36

[2] Aazokhi Waruwu,HusniHalim,ThamrinNasution and YudhaHanova, "Bamboo grid reinforcement on peat soil under repeated loading

[3] A.Hegde and T.G.Sitharam(2014), "Use of bamboo in soft –ground engineering and its performance comparison with geosynthetics :experimental studies, Journal of Materials in Civil Engineering, © ASCE, ISSN 0899-1561/04014256(9)

[4] A.Hegde and T.G.Sitharam(2015), "Experimental and analytical studies on soft clay beds reinforced with bamboo cells and geocells" Int. J. of Geosynth. And Ground Eng, page no.1-11

[5]Causes Of Cracks On Recently Constructed Flexible Pavements: A Case Study On Kabati To Mareira Road In Kenya By:-Benjamin K. Chamia, Zachary AbieroGariy, Stephen M. Mulei(Mar-May 2017)

[6]Physical and mechanical characterization of fresh bamboo for infrastructure projects By:-Fei Ye and Wenxi Fu, Ph.D. (2017) [7]Fei Ye and WenxiFu,Ph.D.(2017), "Physical and Mechanical Characterization of Fresh Bamboo for Infrastructure Projects",

American Society of Civil Engineers.



Impact Factor: 7.512





## INTERNATIONAL JOURNAL OF INNOVATIVE RESEARCH

IN SCIENCE | ENGINEERING | TECHNOLOGY





www.ijirset.com