

e-ISSN: 2319-8753 | p-ISSN: 2320-6710

EDIA

International Journal of Innovative Research in SCIENCE | ENGINEERING | TECHNOLOGY

INTERNATIONAL JOURNAL OF INNOVATIVE RESEARCH

808

IN SCIENCE | ENGINEERING | TECHNOLOGY

Volume 10, Issue 6, June 2021

INTERNATIONAL STANDARD SERIAL NUMBER INDIA

Impact Factor: 7.512

9940 572 462

6381 907 438

 \odot







-ISSN: 2319-8753, p-ISSN: 2320-6710| <u>www.ijirset.com</u> | Impact Factor: 7.512|

||Volume 10, Issue 6, June 2021||

DOI:10.15680/IJIRSET.2021.1006070

Experimental Investigation on Coconut Shell and Coir Fibre as a Partial Replacement of Coarse Aggregate and Fine Aggregate in Concrete

S.Karuppasamy¹, E.Preethi²

M.E (Structural Engineering), Prathyusha Engineering College, Thiruvallur, India¹

Assistant Professor, Department of Civil Engineering, Prathyusha Engineering College, Thiruvallur, Indiia²

ABSTRACT: This paper presents an experimental study on coconut shell and coir fibre using partial replacement method. The aim of the project is to increase the strength of concrete and maintain cheap cost. Every construction industry totally relies on cement, sand and aggregate for the production of concrete. The high cost of conventional construction material affects the economics of the structure. With increasing concern over the excessive exploitation of natural aggregates, synthetic light weight aggregate production from environmental waste in viable new source of structure aggregate materials. Nowadays ,most of the reduce the cost of construction as well as increase the strength. Coconut shell and coir fibre are the natural materials which is abundantly available in tropical region .The replacement method by using coconut shell as coarse aggregate and coir fibre as fine aggregate by replacing 5%,10%,15% and 20%.The strength characteristics such as compressive strength ,split tensile strength and flexural strength of concrete mixes are found for 7 days,14 days and 28 days of curing period and results are analyzed and compared with the regular (conventional)mix.

KEYWORDS: Coconut shell, coir fibre, Self-curing agent, Eco friendly, Compressive, workability.

I. INTRODUCTION

Approximately,10 million cubic metres concrete is being produced yearly.Concrete is a composite material made of fine and coarese aggregate and bound together with the cement,water that hardens over time.Cement used isPPC of grade 53 is taken for testing in work.Cement is used right from ancient periods in construction industry.In the most general sense of the world,cement is a binder, a substance which sets and hardens independently, and can bind other material together.Coconut shell is an agricultural biodegradable waste found in most of tropical countries especiallyin Asia.India manufactures 15,739 million nute annually,which is next to Indoneria with 16,498 million.coconut shell may offer itself as a potential construction material in the field of construction industries and would solve the environmental problem of reducing the generation of solid wastes simultaneously.

Coconut fibre or coir is a product which is extracted from the outer shell of the coconut fruit. It is used in a varitey of ways world wide, being especially popular for rope and matting, and there are anumber of source for coir and coir products. Coir comes from a matted fibrous layer found between the inner and outer husk of the coconut.

Coconut shell is one of the main polluter that contributes to the nation's pollution problem. It is a solid waste in form of shell with approximately 3.18 millon tonnes produced annually. The common waste materials that used to improve the strength of concrete. Coconut shell and coir fibre are known as new waste materials that used in high industry. This is because coconut shell has good weather resistant that it is suitable to use as construction materials. Besides, it has no economic value and its dispose process is costly and will cause environment problem.

1.1 **OBJECTIVE**

To find economical solution for high cost construction material

1. To prepare light weight concrete by using coconut shell and coir fibre as coarse aggregate and fine aggregate



·ISSN: 2319-8753, p-ISSN: 2320-6710| www.ijirset.com | Impact Factor: 7.512|

||Volume 10, Issue 6, June 2021||

DOI:10.15680/IJIRSET.2021.1006070

2. The partial replacement of coconut shell and coir fibre of coarse aggregate and fine aggregate to determine the Compressive strength and Split tensile strength and Flexural strength test.

To prove that the conventional concrete results are compared with replacement concrete to increase the strength of 3. concrete and it is obtained from experimental tests and represent these values with suitable graphs.

1.2 SCOPE

- Application of coconut shell and coir fiber increases the strength 1.
- 2. Using of coconut shell(or) waste natural materials the cost is reduced due to waste materials use of concrete
- 3. To determine the strength characteristics of concrete.

1.3 ADVANTAGE

- 1. It promotes the green construction
- 2. It has more resistance and it is light weight materials and it is economic and reduce its cost of material.
- There is no need of treating coconut shells before usage except for water absorption 3.
- It is a good alternative to wood and helps to prevent deforestation and also inexpensive 4.

II. MATERIALS

This section introduces the properties of materials used in this research . All materials were obtained from local sources.

2.1CEMENT

Cement is the hudraulic binder which is used to reduce concrete

. cement paste sets and hardens by hydration, both in air and under water.

Name of the tests	Tested value
Final setting time	9hrs 28mins
Initial setting time	30 min
Fineness modulus	2.56%
Specific gravity	3.15

Table 1. Test result of Cement

2.2 M-Sand

Passing through 4.75 mm seive coarse aggregate-20mm and down size. The fine aggregate passing through 4.75 mm seive is tested as per IS:2386 Part 3 and specific gravity is fine aggregate is 2.52.

Table 2. Test results of M-sand			
Description	M-sand		
Specific gravity	2.58		
Water absorption	1.5%		
Sieve analysis	Conforming to zone III		
Fineness modulus	3.90%		

Table ? Test results of M sand



DOI:10.15680/IJIRSET.2021.1006070

2.3 Coarse Aggregate

Aggregate which are used i the surface course have to with stand the high magnitude of load stresses and wear and dear due to abrasion .

Table 3. Test results of c	coarse aggregate
----------------------------	------------------

Description	Coarse aggregate	Coconut shell
Specific gravity	2.80	1.72
Water absorptin	2%	2%

Concrete mix proportion

The mixes were designated in accordance with IS 10262-2009 mix design method. Based on the results, the mix proportions M20 was designed. Concrete mix with w/c ratio of 0.44 was prepared. The details of mix proportions for $1m^3$ of concrete are given

Table 4. Material required for 1m³ of Concrete (Kg/m³)

Grade	Cement (kg)	FA (kg)	CA (kg)	Water (lit)
M20	425	642	1051	191.6

About Coconut shell and Coir fibre

Coconut shell and coir fibre are natural materials.Coconut shell is obtained from temples and local areas.Coir fibre is a product which is extracted from the outer shell of the coconut fibres are strong, light in weight..The addition of coconut fibre can reduce the thermal conductivity of the composite specimens. Coconut fibres are commercial available in three forms, namely bristle(longfibres),mattress(relatively short)and decorticated(mixed fibers).These different types of fibres have different uses depending upon the requirement.

VARIOUS TYPES OF FIBRE USED IN CONCRETE

- 1. Brown fibre
- 2. White fibre
- 3. The brown fibre is extracted from matured coconut .The white fibre is extracted from immatured coconut.

III.TESTING RESULTS

Compression Test:

Compressive strenght is defined as resistance of concrete to axial loading. It was tested in compressive testing machina and reading were recorded of the final crack. It is determine by using the formula :

compressive strenght = maximum load/cross sectional area=P/A



入うMA IJIRSET

||Volume 10, Issue 6, June 2021||

DOI:10.15680/IJIRSET.2021.1006070

S.No	Mix (ml)	Compressive strength (N/mm2)			
		7 Days	14 Days	28Days	
1	0	17.00	20.50	22.00	
2	5	17.25	22.38	22.00	
3	10	16.90	22.10	21.91	
4	15	16.00	10.11	22.50	
5	20	18.34	20.10	23.11	

TABLE 5. Compressive test for concrete



Figure.1Compressive strength Graph



Figure.2Testing of compressive strength



-ISSN: 2319-8753, p-ISSN: 2320-6710| <u>www.ijirset.com</u> | Impact Factor: 7.512|

||Volume 10, Issue 6, June 2021||

DOI:10.15680/IJIRSET.2021.1006070

Flexural Strength Test

Flexural strength is the another method of measuring tensile strength of concrete. It is a measure of an and reinforced concrete beam to resist failure in bending.

S.No	Mix(%)	Flexural strength (N/mm²)		
		7 Days	14 Days	28Day s
1	0	3.60	4.60	4.59
2	5	2.70	4.36	4.10
3	10	2.65	3.84	4.35
4	15	2.55	4.30	5.10
5	20	2.35	5.50	5.40

Table 6. Flexural strength for concrete



Test Result For Flexural strength





FIGURE 4. Testing of flexural strenght



-ISSN: 2319-8753, p-ISSN: 2320-6710| <u>www.ijirset.com</u> | Impact Factor: 7.512|

||Volume 10, Issue 6, June 2021||

DOI:10.15680/IJIRSET.2021.1006070

Split Tensile strength Test

Split tensile strength test concrete cylinder is a method to determined the tensile strength of concrete.

S.NOMix Split Tensile strength (N/mm²) 7 Days 14 Days 28Days 2.50 1.40 2.70 0 2 5 0.95 2.47 1.80 10 0.85 2.10 2.38 3 15 0.85 1.62 2.65 4 20 5 1.14 1.50 2.40

 Table 7. Split Tensile strength for concrete



Figure.5 Split Tensile strength graph



-ISSN: 2319-8753, p-ISSN: 2320-6710| <u>www.ijirset.com</u> | Impact Factor: 7.512|

||Volume 10, Issue 6, June 2021||

DOI:10.15680/IJIRSET.2021.1006070



Figure.6Testing of Split Tensile strength

IV. CONCLUSION

The use of coconut shell and coir fibre as a patial replacement of coarse aggregate and fine aggregate should be encouraged for sutainable and economic construction. By the utilization of agricultural waste materials in concrete tends to low cost construction and waste management. The result conclude that the concrete with coarse aggregate and fine aggregate partially replaced with coconut shell and coir fible shows the increase in strenght of the concrete.

REFERENCES

1.K.Muthusamy and N.A.Sabari (2012) "Coconut shell: A Potential Partial Coarse Aggregate Replacement in Concrete" International Journal of Science Environment and Technology, Vol.1, No.4, 2012, 260 -267.

2.N.A. Rashidi, et al "A Study of Calcination and Carbonation of Cocnut Shell ", World Academy of Science, Engineering and Technology, Vol:5 2011-12-27.

3.Nor Hazurina.O, et al "Potential use of Coconut (Anadaragranosa) Shell Ash as Partial Cement Replacement in Concrete ",Caspian Journal of Applied Sciences Research, 2(AICCE"12&GIZ"12),pp.369-376,2013.

4.Chandramouli K. et al, "Strength Properties of Glass Fibre Concrete ", ARPN Journal of Engineering and Applied Science, ISSN 1819- 6608, Vol.5, No.4, April 2010.

5.Kavitha S Kene, et al "Experimental Study on Behaviour of Steel and Glass Fiber Reinced Concrete Composites ",Bonfring International Journal of Industrial Engineering and Management Science, Vol.2,No.4, December 2012.

6.AvinashGornale, et al "Strength Aspects of Glass fibre Reinforced Concrete ", International Journal of Scientific & Engineering Research, Volume 3,Issue 7,July 2012.

7.ShrikantHarle, Prof.RamMeghe, "Glass fibre reinforced Concrete & Its Properties", International Journal of Engineering And Computer Science ISSN:2319-7242, Vol.2 Issue12 Dec, 2013 Page no.3544-3547

8.Dr.P.SrinivasaRao, et al, "Durability Studies on Glass Fibre Reinforced Concrete ",Journal of Civil Engineering Science: An International Journal, Vol.1 No.1-2(January-December, 2012). 57

9.Eng.PshtiwanN.Shakor, et al, "Glass Fibre Reinforced Concrete Use in Construction ", International Journal of Technology And Engineering System(IJTES):Jan-March 2011-Vol.2,No.2.

10.J.P.J.G.Ferreira and F.A.B.Branco, "The Use of Glass Fiber-Reinforced Concrete as a Structural material", Experimental Tecniques May-June 2007, Page 64-73. 12. E.G.Nawy. "Reinforced Concrete (Prentice Hall), 1985. • Mindess, J.F.Young and Darwin (2003) Concrete Prentice Hall.

11.Daneshmand and O.Saadatian(2011) "Influence of oil palm shell on workability and compressive strength of high strength concrete" Annals of Faculty Engineering Hunedoara – International Journal of Engineering. Vol.2 (1),p51-56.

12.Abdullahi,M.(2012) "Effect of aggregate type on compressive strength of concrete" International Journal of Civil and Structural Engineering. Vol.2 (3),p791-800. • Shrikant M.Karle, "Review on the Performance of Glass Fiber Reinforced Concrete ",International Journal of Civil Engineering Research, ISSN 2278- 3652 Volume 5, Number 3(2014), pp.281-284.



Impact Factor: 7.512





INTERNATIONAL JOURNAL OF INNOVATIVE RESEARCH

IN SCIENCE | ENGINEERING | TECHNOLOGY





www.ijirset.com