

e-ISSN: 2319-8753 | p-ISSN: 2347-6710

EDIA

International Journal of Innovative Research in SCIENCE | ENGINEERING | TECHNOLOGY

INTERNATIONAL JOURNAL OF INNOVATIVE RESEARCH

IN SCIENCE | ENGINEERING | TECHNOLOGY

Volume 11, Issue 4, April 2022

INTERNATIONAL STANDARD SERIAL NUMBER INDIA

Impact Factor: 8.118

9940 572 462

6381 907 438

 \bigcirc



| e-ISSN: 2319-8753, p-ISSN: 2320-6710| <u>www.ijirset.com</u> | Impact Factor: 8.118|

||Volume 11, Issue 4, April 2022||

| DOI:10.15680/IJIRSET.2022.1104102 |

An Experimental Study on Evaluation of Properties and Structural Integrity for Pervious Concrete Pavement System

Giridhar K. Nirvikar¹, Narendra L. Gaydhane², Chetan D. Baraskar³, Ajay A. Lanje⁴,
Zulelal P. Lanje⁵, Sneha Y. Karwade⁶, Disha Y. Waghmare⁷, Simran V. Quireshi⁸,
Dnyaneshwar T. Parshuramkar⁹, Mangala W. Rahangdale¹⁰, Dhawal S. Somalwar¹¹,

Parag P. Koche¹²

U.G. Students, Department of Civil Engineering, Madhukarrao Pandav College of Engineering, Bhilewada ,Bhandara, Maharashtra , India^{1.,2,3,4,5,6,7,8,9,10,11}

Professor, HOD of Civil Engineering, Department of Civil Engineering, Madhukarrao Pandav College of Engineering, Bhilewada, Bhandara, India¹²

ABSTRACT:Increased precipitation in recent years due to the effect of climate change is leadingto increased surface runoff and water logging in urban areas while impervious concrete orasphalt covering of urban lands hinders groundwater recharge. However, Pervious ConcretePavements have the capacity of functioning as a Sustainable Urban Drainage System (SUDS)by allowing surface water to infiltrate downwards through the porous structure of thepavements, thereby minimizing flooding risks, recharging ground water, reducing run off andpeak flows, alleviating the precipitation load on overstressed drainage systems, and improving water quality by capturing pollutants. This research provides an overview on pervious concretemix designs and their effect on strength and permeability. Materials of pervious concreteinclude those used in conventional concrete, however eliminating the fine aggregate content.Different mix designs have been prepared and tested to understand the behavior of PerviousConcrete and recommend an ideal mix.

KEYWORDS: Pervious Concrete, Mix Design, Coarse Aggregates, Grade, Compressive Strength

I. INTRODUCTION

Pervious concrete is nothing but no fines concrete, which is also known as porous, gap graded or permeable concrete mainly consists of normal Portland cement, CA, water. In which FA are not existent or present in very small amount i.e< 10% by weight of the total aggregates. In general, for making porous concrete, we will use the aggregates of size which passes through 12.5mm sieve and retained on 10mm sieve. In this project we have taken single size aggregates i.e 12.5mm. the single size aggregates make a good no-fines concrete, which addition to having large voids and hence light in weight, also offers architecturally attractive look. Pervious concrete pavement is an unique effective means to address the important environmental issues which support green and sustainable growth

II. APPLICATIONS OF PERVIOUS CONCRETE

- 1. Pervious Concrete as a Road pavement (Foot path, Parking area)
- 2. Residential roads and driveways
- 3. Parking lots
- 4. Noise barriers
- 5. Slope stabilization



| e-ISSN: 2319-8753, p-ISSN: 2320-6710| www.ijirset.com | Impact Factor: 8.118|

Volume 11, Issue 4, April 2022

| DOI:10.15680/IJIRSET.2022.1104102 |

1. METHODOLOGY

The methodology adopted and material characterization and design mix is carried out is presented in the Form of flow chart and parameters studied.

- Collection Of Materials
- Physical Test on Materials
- Casting Of Sample
- Test For Fresh and Harden Concrete
- Fresh Concrete Test
- Slump Cone Test
- Harden Concrete Tests
- Compressive Strength (For 7, 14, 28 Days)
- Permeability Test

III. EXPERIMENTAL RESULTS

All of the mixing, ratios, calculations, and testing culminate into the final experiment, compression testing. **Compressive Strength:**

Compressive strength is dependent on size of coarse aggregate, void ratio, bond between mortar and coarse aggregate. In 7 days cubes of permeable concrete gain 30% of its strength, in 21 days of permeable concrete gain 70% of its strength, and for 28 days it gains 95% strength.




Fig. 7 & 28 Days Compressive Strength Test on Pervious Concrete

PERMEABILITY TEST:-

Permeability of the pervious concrete is determined by special arrangement of cylindrical shape bucket or specific container which should be open from both the side and has to arrange in such a way so that one side could be used for pouring of water and other resting on pervious concrete as shown in figure below.

Formulaused, I= (KM)/ (D²×T) I- Infiltration rate M- Mass of water K- Constant D- Diameter T- Time



| e-ISSN: 2319-8753, p-ISSN: 2320-6710| <u>www.ijirset.com</u> | Impact Factor: 8.118|

Volume 11, Issue 4, April 2022

| DOI:10.15680/IJIRSET.2022.1104102 |



Fig. Arrangement for Permeability Test of Pervious Concrete Specimen

PRESSURE DIFFERENCE	PERMEABILITY OF CONVENTIONAL CONCRETE(cm/sec)			PERMEABILITY OF NO FINES CONCRETE(cm/sec)		
(Pa)	M15	M20	M25	M15	M20	M25
5	5.6X10 ⁻¹⁴	3.2X10 ⁻¹⁴	1.39 X10 ⁻¹⁴	6.6 X10 ⁻³	1.01X10 ⁻³	9.42 X10 ⁻⁴
10	1.8X10 ⁻¹⁴		7.47 X10 ⁻¹⁵	1.2 X10 ⁻³	8.2 X10 ⁻⁴	6.01 X10 ⁻⁴
15	8.6X10 ⁻¹⁵	6.23 X10 ⁻¹⁵	3.25 X10 ⁻¹⁵	8.9 X10 ⁻⁴	5.4 X10 ⁻⁴	2.9 X10 ⁻⁴

Table of Permeability Test Result

IV. FUTURE SCOPE

- Pervious concrete can be used in building for rainwater harvesting as well as for cooling purpose by providing permeable wall.
- In the presence of clayey soil, water can be percolated through providing borehole at every 1-2km with the help of drainage system.
- Water can be filtered and stored as fresh water below the ground

V. CONCLUSION

The following conclusions are drawn based on the experimental investigations are:

1. The pervious concrete is suitable only for low volume road pavement like foot path, parking slots. Due to voids in pervious concrete it is difficult obtained required compressive strength.

2. Using smaller size aggregate (10 mm) can enhance the compressive strength of pervious concrete than bigger size aggregate (20mm).

3. Compressive strength can be increase by using proper admixtures also.

4. Water absorption, abrasion resistance are good property of pervious concrete.

5. It is an eco-friendly concrete material.

REFERENCES

- 1. AGUADO (1999) he told that highly permeable materials provide drainage and noise-absorptionproperties that are useful in pavement top layers.
- 2. J.YANG AND G.JIANG (2003) In this paper, a pervious concrete pavement materialused for roadway is introduced. Using the common material and method, the strength of the pervious concrete is low.
- 3. **A.M.MULLIGAN(2005)**Thisthesisinvestigatedpriorstudiesonthecompressivestrength on pervious concrete as it relates to water-cement ratio, aggregate-cement ratio, aggregatesize, and compaction.
- 4. **S.VALAVALA AND F.MONTES** (2006) they concluded that Pervious concrete is analternative paving surface that can be used to reduce the nonpoint source pollution effects of stormwaterrunofffrom paved surfaces.



| e-ISSN: 2319-8753, p-ISSN: 2320-6710| <u>www.ijirset.com</u> | Impact Factor: 8.118|

Volume 11, Issue 4, April 2022

| DOI:10.15680/LJIRSET.2022.1104102 |

- 5. **M.SULEIMAN AND J.KEVERN (2007)** This paper summarizes a study performed to investigate the effects of compaction energy on pervious concrete void ratio, compressivestrength, tensilestrength, unitweight, and freeze-thawdurability.
- 6. **C.WOLFERSBERGER** (2008) in this paper, Pervious concrete usually requires much less maintenance. But inspection and some attention will keep it working for many years.
- 7. **K.WANG(2008)** This paper describes the current state of practice in pervious concreteplacement methods and presents results from a laboratory-based study to compare various placement practices and develop QA/QC criteria.
- 8. **R. C.MEININGER(2009)** in this paper Conclusions are drawn regarding the percentageof air voids needed for adequate permeability, the optimum water-cement ratio range, and theamountsof compaction and curing required.





Impact Factor: 8.118





INTERNATIONAL JOURNAL OF INNOVATIVE RESEARCH

IN SCIENCE | ENGINEERING | TECHNOLOGY





www.ijirset.com