



e-ISSN: 2319-8753 | p-ISSN: 2347-6710

IJRSET

International Journal of Innovative Research in
SCIENCE | ENGINEERING | TECHNOLOGY

INTERNATIONAL JOURNAL OF INNOVATIVE RESEARCH

IN SCIENCE | ENGINEERING | TECHNOLOGY

Volume 11, Issue 8, August 2022

ISSN INTERNATIONAL
STANDARD
SERIAL
NUMBER
INDIA

Impact Factor: 8.118

9940 572 462

6381 907 438

ijirset@gmail.com

www.ijirset.com

A Review Study on Utilization of Fibre in Concrete as a Replacement of Cement

Shivek Tuli¹, Amit Kumar², Ravikant Sharma³

M. Tech Scholar, Dept. of Civil Engineering, R.P.E.T Bastara, Karnal Haryana, India^{1,2}

Head of Department and Assistant Professor, Dept. of Civil Engineering, R.P.E.T Bastara, Karnal Haryana, India³

ABSTRACT

In the current world, concrete has become a very important part of the construction industry and the materials which are used in making concrete have evolved due to better quality of cement and better grade of coarse aggregates. The sand is an important part of concrete. It is mainly procured from natural sources. Thus the grade of sand is not under our control. The concrete cubes of M-25 grade were threw in this trial explore work and tried to analyze different properties of concrete like compressive quality, workability. In this study we are reviewing literatures related to advances in concrete technologies, and utilization of fibers and materials in construction industry.

KEYWORDS : Concrete, Fibers, Compressive Strength, Flexure Strength, Improvement, Grade, Waste.

I. INTRODUCTION

In the current world, concrete has become a very important part of the construction industry and the materials which are used in making concrete have evolved due to better quality of cement and better grade of coarse aggregates. The sand is an important part of concrete. It is mainly procured from natural sources. Thus the grade of sand is not under our control.

II. LITERATURE REVIEW

In this study we are preparing review of literatures, journals related to advances in construction industry mainly in concrete technology. Following research has been reviewed as follows:

Roy et. al. (2015) (Effect of Steel Fibres on Concrete with M-Sand as a Replacement of Natural Sand) Here author described the experimental study of fiber reinforced concrete with m-sand. Investigated the compressive strength and tensile strength of the concrete grades M25 & M30 having different percentage of steel fibre (0%, 1%, 1.5% & 2%). The chemical admixtures is used to increase the workability of concrete. The investigation is carried out on a total no of 96 specimen by conducting compressive strength test and split tensile test.

Concluded that the strength obtained by natural sand and replacement of natural sand with M sand in concrete with addition of steel fibers. The investigation derives the following conclusion. By adding steel fibers to fresh concrete compressive strength increases by resisting cracks and their by increasing the durability. Replacement of river sand with m sand gives a satisfactory strength and can be used as alternate material for river sand. Using steel fiber reinforcement admixture enhances the both compressive strength and flexural strength.

Uttamraj and Rafeeq (2017) (A Experimental study on m- sand and recron 3s fiber for m30 concrete) Here Author find the effect of fresh properties of concrete like workability and hardened properties like compressive strength, split tensile & flexure strength of the concrete by replacing natural sand by robo sand in proportions of 0% and 50% & 100% with cubes 18 cubes of 150mmx150mmx150mm, 18 cylinders of 150mmx300mm, 18 prisms of 150mmx150mmx700mm were casted and tested at the age of 7 days and 28 days. is studied for M30 design mix. In second phase recron 3s was mixed in Concrete containing 100% m- sand at different percentages of 0%, 0.5%, 1%, 1.5% & 2% and cubes 27 cubes of 150mmx150mmx150mm, 27 cylinders of 150mmx300mm, 27 prisms of

150mmx150mmx700mm were casted and tested at the age of 7 days and 28 day. Concluded that The compressive strength of concrete specimens made with 0% replacement of robo sand gives higher strength when compared with 50% and 100%.

Magudeaswaran and Eswaramoorthi (2016) (High Performance Concrete Using M Sand) Presented efforts on the enhancement of vacuum condition in concrete by focusing on the surface area to volume ratio phenomenon to improve the impermeability of concrete and thereby improving its living standard in terms of workability, Compressive strength and durability. The mechanical parameter of concrete was tested by inoculation of silica fume at the progressive interval of 2.5% with fully replacement of river sand by M sand. From the observation it was inferred that rise in percentage of fractional replacement of silica fume, improve the compressive, tensile strength, flexure strength and revealed a better picturesque in terms of allied standard durability indicators of High Performance Concrete.

Marcalíková et. al. 2019 Illustrated work is focused on the area of mechanical properties of two types of Steel Fibers for reinforced concrete. In both cases, the same concrete mixture is used. The Steel Fibers used differ in shape. The first one is short and straight fiber and the second one is 3D steel fiber. Steel Fiber Reinforced Concrete was prepared at a dosage of 40 and 75 kg steel fibers/m³. The experiment includes determination of strengths, concretely compressive strength, a three-point flexural test and Splitting Tensile Strength test. The results are summarized; fracture mechanics parameters necessary for structural modeling are also included.

Roy et. al. (2018) (Effect of Steel Fibres on Concrete with M-Sand as a Replacement of Natural Sand) Here author described the experimental study of fiber reinforced concrete with m-sand. Investigated the compressive strength and tensile strength of the concrete grades M25 & M30 having different percentage of steel fibre (0%, 1%, 1.5% & 2%). The chemical admixtures is used to increase the workability of concrete. The investigation is carried out on a total no of 96 specimen by conducting compressive strength test and split tensile test.

Concluded that the strength obtained by natural sand and replacement of natural sand with M sand in concrete with addition of steel fibers. The investigation derives the following conclusion. By adding steel fibers to fresh concrete compressive strength increases by resisting cracks and their by increasing the durability. Replacement of river sand with m sand gives a satisfactory strength and can be used as alternate material for river sand. Using steel fiber reinforcement admixture enhances the both compressive strength and flexural strength.

Neeraja et. al. (2017) (Study on strength characteristics of concrete using M-Sand and coconut fibers) Here author attempt was made to use M-sand and coconut fiber in concrete. In this study, a total of around 90 specimens were made and concrete was both hand mixed and machine mixed. The grade concrete used was M-35. In this study initially 100% river sand was used to make the samples. The different types of concrete mixes involved in specimen making were 100% river sand, 20% riversand replacement with M-sand and similarly 40%, 60%, 80%, 100% replacement by the M-sand. After curing of the above samples for 7 or 28 days, tests were done on them to determine the maximum compressive tensile and flexural strength of the different mixes. Here they Concluded that The addition of M-sand significantly increased the compressive, tensile and flexural strengths of concrete with maximum strengths in each case being achieved at 80% M-sand. The compressive strength of concrete with above mix increased by about 25 %. The addition of coconut fibers significantly improved engineering properties of the concrete like tensile strength and flexural strength. It is also noted that Compressive strength decreased as the percentage of coconut fiber was varied from 0.2% to 1.0 %. This is due to the fact that addition of coconut fibers increases the void ratio of concrete, which in turn decreases the compressive strength.

Uttamraj and Rafeeq (2017) (A Experimental study on m- sand and recron 3s fiber for m30 concrete) Here Author find the effect of fresh properties of concrete like workability and hardened properties like compressive strength , split tensile & flexure strength of the concrete by replacing natural sand by robo sand in proportions of 0% and 50% & 100% with cubes 18cubes of 150mmx150mmx150mm, 18 cylinders of 150mmx300mm , 18prisms of 150mmx150mmx700mm were casted and tested at the age of 7 days and 28 days.is studied for M30 design mix. In second phase recron 3s was mixed in Concrete containing 100% m- sand at different percentages of 0%, 0.5%, 1%, 1.5% & 2% and cubes 27cubes of 150mmx150mmx150mm, 27 cylinders of 150mmx300mm , 27 prisms of 150mmx150mmx700mm were casted and tested at the age of 7 days and 28 day. Concluded that The compressive strength of concrete specimens made with 0% replacement of robo sand gives higher strength when compared with 50% and 100%.

Deepa and Kumar (2018) (Experimental Study On Hybrid Fibre Concrete With Using GGBS And M Sand) Here Author illustrated that advancement of concrete technology can reduce the utilization of natural resources and energy sources and lessen the burden of pollutants on environment. Presently large amounts of GGBS (Ground granulated blast furnace slag) generated in industries with an impact on environment and humans. Conventional concrete has two major defects: low tensile strength and a destructive and brittle failure. In an attempt to increase concrete ductility and energy absorption, fibre reinforced concrete has been introduced. The present investigation revealed the effect of using GGBS and M Sand as a partial replacement of cement and fine aggregate along with optimum percentage of polypropylene and steel fiber. For this study (M30) grade concrete is designed. Partial replacement of cement with GGBS will be made for varying percentages such as by weight 0%, 10 %, 20% and 30% .Along with M Sand as fine aggregate and with optimum fibre percentage as polypropylene (0.4%) and steel fiber (0.6%) respectively. From this study the strength properties of the concrete have been investigated.

Manogna and Guruprasad (2017) (Experimental study on the properties of PFRC using M-Sand) Author stated that River sand is becoming a scarce commodity and hence an exploration alternative to it has become imminent. Manufactured sand is the good alternative to river sand and it is purposely made, fine crushed aggregate produced under controlled conditions from a suitable sand source rock. Plastics are non-biodegradable common environmental polluting materials. These are going to affect the fertility of soil. Consider a design mix of M25 grade concrete with replacement of 0%, 20%, 40%, 60%, 80% and 100% of M-sand have been considered for laboratory analysis that is slump test, compressive strength for cube and split tensile strength for cylinder, sieve analysis and specific gravity tests for both fine and coarse aggregates and M-Sand and results were compared with standards to achieve the desired parameter.

Concluded that manufactured sand is the good alternative to river sand and it is purposely made, fine crushed aggregate produced under controlled conditions from a suitable sand source rock. Plastics are non-bio-degradable common environmental polluting materials. These are going to affect the fertility of soil. In our study the detailed experimental investigation was carried out on plastic fiber reinforced concrete by partial replacement of natural sand by manufactured sand with different percentages (0%, 20%, 40%, 60%, 80%, 100%) and adding fixed percentage (0.5% of weight cement) of plastic fibers (PP fibers).

Magudeaswaran and Eswaramoorthi (2016) (High Performance Concrete Using M Sand) Presented efforts on the enhancement of vacuum condition in concrete by focusing on the surface area to volume ratio phenomenon to improve the impermeability of concrete and thereby improving its living standard in terms of workability, Compressive strength and durability. The mechanical parameter of concrete was tested by inoculation of silica fume at the progressive interval of 2.5% with fully replacement of river sand by M sand. From the observation it was inferred that rise in percentage of fractional replacement of silica fume, improve the compressive, tensile strength, flexure strength and revealed a better picturesque in terms of allied standard durability indicators of High Performance Concrete.

Suresh and Revathi (2017) (High Performance Concrete with M-Sand and Its Further Aspects) Examined that building constructors have been using river sand as fine aggregate in the manufacture of concrete. But in due course, an enormous increase has happened in the construction activities. It causes a heavy shortage in the availability of good quality sand and it also affects concrete manufacture. Because, excessive sand mining from river causes the degradation of river beds and environmental pollution. Besides, river sand mining deepens the river courses and disturbs the aquatic life style. In short, the agricultural activities are totally affected. Therefore, river mining is restricted. As a result, a necessity has arisen to find out an alternative solution. That is, we are left in a position to select manufactured sand that contains the equal properties of river sand. Because, the higher practical density of manufactured sand would intensity the durability of concrete. In this dissertation, on investigation.

Vishal Gadgihalliet. al. (2017) (analysis of properties of concrete using manufacture sand as fine aggregates) Analyzed that Aggregate in concrete acts as structural filler, these place a crucial than simple statement implies it is the material that the cement paste coats and blind together. Now a day's using river sand is prohibited by government, as these cause soil erosion. In this paper analysis of properties of concrete using manufacture sand as course aggregate is studied and verified the strength of concrete and temperature emitted due to chemical reaction to the normal Portland cement. Using manufacture sand as course aggregate the temperature emitted due to exothermal reaction of concrete has reduced. Although the compressive strength of the concrete has reduced compared to normal concrete where no admixtures were used to enhance the properties of concrete.

Bhishma k Vaidya et. al. (2016) (Comparative Study on Cost Analysis of Natural & Manufacture Sand in Residential Building) The huge quantity of concrete is consumed by construction industry all over the world. In India, the conventional concrete is produced by using natural sand obtained from riverbeds as fine aggregate. The cheapest and the easiest way of getting substitute for natural sand is by crushing natural stone to get manufactured sand which would be free from all impurities. Manufactured sand is a term used for aggregate materials less than 4.75mm and which are processed from crushed rock or gravel. The concrete mixes having different mix proportions for both natural and manufactured sand (i.e. 100%NS+0%MS, 70%NS+30%MS, 40%NS+60%MS, and 0%Ns+100%MS) were prepared for M30 grade of concrete for cubes. Then there were 2 case studies is taken in which slab concrete cost of building by done construction and concrete cost of same quantity by my trial mix variation is compared. And this cost comparison of trial mix is done with cost of Natural sand & Manufactured Sand obtained from 3 different cities.

Suseela et. al. (2017) (strength analysis on concrete with m-sand as a partial replacement of fine aggregate) In general concrete is a combination of cement, fine and coarse aggregate. These days, natural river sand is difficult to acquire and extraction of sand from river has represented an awesome threat to environment. In addition, government has connected limitation on extraction of sand from riverbed. Subsequently, insufficiency of natural river sand and increase in demand contemplate research seek towards alternate fine aggregate. This seek turns the research intention towards effective utilization of Manufactured sand (M-sand) for commercial purpose. This research incorporates effectiveness of M-sand by investigation compressive stress, split tensile stress and durability of concrete with various mix.

Vaishali et. Al. (2018) (Effect of Manufactured Sand on Mechanical Properties of Concrete) Natural river sand was the cheapest sand readily available. But excessive mining increased the demand for sand and had lead to the ecological imbalance. Now the sand available contains very high amount of silt and clay which holds dampness and reduces the strength of concrete. Though the researchers suggest M-sand for construction purposes, it has not fully come to practice. Also the property of M-sand available in different places varies. Hence after going through several works, full replacement of river sand with Msand in concrete has been carried out. For this study M-sand from three different localities were collected and tested. M20 mix is adopted as grade of concrete and water cement ratio 0.45 is followed. Three variants of samples containing different M-sand are casted. Workability and Mechanical properties have been examined. Slump tests showed that river sand is highly workable than the M-sand. On comparing their Mechanical Properties, concrete containing Msand obtained from Karur showed 10.71%, 12.15% and 8.22% increase in Compressive Strength, Split Tensile Strength and Flexural Strength when compared to the conventional concrete at the end of 28 days curing.

Sachin and Roshan (2018) (M-SAND, An Alternative To The River Sand In Construction Technology) A few alternatives have come up for the industry to bank on of which manufactured sand or M-sand, as it is called, is found to be the most suitable one to replace river sand. M-sand has caught the attention of the construction industry and environmentalists alike for its quality and the minimum damages it causes to nature. Usage of M-Sand can drastically reduce the cost since like river sand, it does not contain impurities and wastages is nil since it is made with modern technology and machinery. Once the M-sand becomes more popular in the construction industry, the demand for river sand and illegal sand mining would come down, A well processed manufactured sand as partial or full replacement to river sand is the need of the hour as a long term solution in Indian concrete industry until other suitable alternative fine aggregate are developed. In the present study, a comparison of the Compressive strengths of River Sand and M-sand is done with the hundred percent replacement of river sand by M sand.

III. CONCLUSION

From the above studies it is found that the different materials are used by the various author's some have used single and some have more than two materials. In literature survey it is observed that none of them provide a proper mix design using admixture and manufacturing sand In above survey effect of Hair fiber and its beneficial advantages are not mentioned. workability and setting time of concrete. we would some be able to nations, higher summer temperatures, low relative moistness and sweltering breeze blowing cause fast dissipation of water from the crisp concrete surface. Thus concrete sets prior and no appropriate time is left accessible for cementing operations. For

instance, it has been accounted for that, when the temperature of concrete mortar met a water/bond (w/c) proportion of 0.6 is expanded from 27°C to 45°C both the underlying and last setting circumstances are about divided.

REFERENCES

- [1]. Huang L, Xu L, Chi Y, Xu H. Experimental investigation on the seismic performance of steel– polypropylene hybrid fiber reinforced concrete columns. *Construction and Building Materials*. 2015;87:16-27
- [2]. Bentur A. Microstructure, interfacial effects, and micromechanics of cementitious composites. *Ceramic Transactions*. 1990;16:523-550
- [3]. Burati N, Mazzoti C, Savoia M. Post-cracking behaviour of steel and macro-synthetic fiber reinforced concretes. *Construction and Building Materials*. 2011;25(5):2713-2722
- [4]. Ramakrishnan V. *Materials and Properties of Fibre Reinforced Concrete*. London: Civil Engineering; 1988. pp. 29-40
- [5]. ACIFC. *An Introduction Guide: Steel Fibre Reinforced Concrete Industrial Ground Floors*. Warwickshire: ACIFC; 1999
- [6]. Brandt AM. Fibre reinforced cement-based (FRC) composites after over 40 years of development in building and civil engineering. *Composite Structures*. 2008;86(1-3):3-9
- [7]. Di Prisco M, Plizzari G, Vandewalle L. Fibre reinforced concrete: New design perspectives. *Materials and Structures*. 2009;42(9):1261-1281
- [8]. Aoude H, Belghiti M, Cook WD, Mitchell D. Response of steel fiber-reinforced concrete beams with and without stirrups. *ACI Structural Journal*. 2012;109(3):359
- [9]. Barros JA, Lourenço LA, Soltanzadeh F, Taheri M. Retracted article: Steel fiber reinforced concrete for elements failing in bending and in shear. *European Journal of Environmental and Civil Engineering*. 2014;18(1):33-65
- [10]. Susetyo J, Gauvreau P, Vecchio FJ. Steel fiber reinforced concrete panels in shear: Analysis and modeling. *ACI Structural Journal*. 2013;110(2):285
- [11]. Caggiano V, Fogassi L, Rizzolati G, Casile A, Giese MA, Thier P. Mirror neurons encode the subjective value of an observed action. *Proceedings of the National Academy of Sciences*. 2012;109(29):11848-11853
- [12]. de Montaignac R, Massicote B, Charron JP, Nour A. Design of SFRC structural elements: Postcracking tensile strength measurement. *Materials and Structures*. 2012;45(4):609-622
- [13]. Safeer-ul-Hassan M, Munir M, Mujahid MY, Kisana NS, Akram Z, Nazeer AW. Genetic analysis of some biometric characters in bread wheat (*Triticum aestivum* L.). *Journal of Biological Sciences*. 2004;4(4):480-485
- [14]. Ventura-Gouveia A. *Constitutive models for the material nonlinear analysis of concrete structures including time dependent effects PhD thesis*. Department of Civil Engineering; 2011
- [15]. Granju JL, Balouch SU. Corrosion of steel fiber reinforced concrete from the cracks. *Cement and Concrete Research*. 2005;35(3):572-577
- [16]. Jiang Z, Banthia N. Size effects in flexural toughness of fiber reinforced concrete. *Journal of Testing and Evaluation*. 2010;38(3):332-338
- [17]. Shi C, Qian J. High performance cementing materials from industrial slags—A review. *Resources, Conservation and Recycling*. 2000;29(3):195-207
- [18]. Aiello A, Lindlein N, Marquardt C, Leuchs G. Transverse angular momentum and geometric spin Hall effect of light. *Physical Review Letters*. 2009;103(10):100401
- [19]. Graeff C, Durante M, Bert C. Motion mitigation in intensity modulated particle therapy by internal target volumes covering range changes. *Medical Physics*. 2012;39(10):6004-6013
- [20]. Neocleous K, Tlemat H, Pilakoutas K. Design issues for concrete reinforced with steel fibers, including fibers recovered from used tires. *Journal of Materials in Civil Engineering*. 2006;18(5):677-685



INNO SPACE
SJIF Scientific Journal Impact Factor
Impact Factor: 8.118



ISSN INTERNATIONAL
STANDARD
SERIAL
NUMBER
INDIA



INTERNATIONAL JOURNAL OF INNOVATIVE RESEARCH

IN SCIENCE | ENGINEERING | TECHNOLOGY

 **9940 572 462**  **6381 907 438**  **ijirset@gmail.com**



www.ijirset.com

Scan to save the contact details