



e-ISSN: 2319-8753 | p-ISSN: 2347-6710

IJIRSET

International Journal of Innovative Research in
SCIENCE | ENGINEERING | TECHNOLOGY

INTERNATIONAL JOURNAL OF INNOVATIVE RESEARCH

IN SCIENCE | ENGINEERING | TECHNOLOGY

Volume 11, Issue 12, December 2022

ISSN INTERNATIONAL
STANDARD
SERIAL
NUMBER
INDIA

Impact Factor: 8.118

9940 572 462

6381 907 438

ijirset@gmail.com

www.ijirset.com

A Review on CFD Analysis and Experimental Investigation of Plate Type PCM Heat Sink Using Nanofluids

Namrata Desai¹, Dr. Vilas A. Pharande², Prof. Suraj S. Ghadage³

P.G. Student, M-Tech Heat and Power Engineering, Department of Mechanical Engineering, Arvind Gavali College of Engineering Satara, India¹

Professor & Principal, Arvind Gavali College of Engineering Satara, India²

Assistant Professor, Department of Mechanical Engineering, Arvind Gavali College of Engineering Satara, India³

ABSTRACT: Integrated circuits operate best in a limited range of temperature hence their package must be designed in order to remove the excessive heat. As an alternative passive cooling technique means, phase change materials or phase change materials have been widely investigated for such transient cooling applications considering their advantages such as high specific heat, high latent heat of fusion, controllable temperature stability and small volume change during phase changes, etc. This types of PCM based cooling techniques have different application in various devices which are not be operated continuously over a long period of time, but in intermittently using devices like digital cameras ,cellular phones, notebook etc. Melting of a phase change material (PCM) is studied in a heat sink with vertical internal fins and a horizontal base. In this project thesis, both experimental and CFD investigations have to be carried out to evaluate the cooling performance of a PCM based Heat Sink consisting of fins on upper surface of flat plate. Copper oxide base Nano fluids contain a small fraction of solid copper nano particles in base fluids flowing through copper pipe arrangement in bottom plate attached with heater at base. . Computational Fluid Dynamics (CFD) simulations are to be carried out to study the heat sinks heat transfer mechanism. In this research work the experimental and numerical investigation for the improved heat transfer characteristics of mini channel heat sink using CuO/water nano with (1 and 2 % volume fraction) fluid is to be done.

KEYWORDS: PCM, ANSYS, CFD, Heat sink, nano particles, CuO/water Nano fluid.

I. INTRODUCTION

Phase change material (PCM) absorbs a large amount of heat when melting, thus can play a role as heat reservoir or temperature controller in many applications [1-3]. PCM-based heat sink is widely used for thermal management of remotely located and intermittently operated avionics on aircraft or missile avionics [4]. Such heat sinks have a simple structure and provide a substantial weight reduction, which is of significant importance for avionics equipment's. As increasing electronic chips with smaller size and higher Power are employed, "hot points" raise in *avionics equipment's, which lead to a non-uniform temperature field. Unfortunately, thermal stress caused by the non-uniform temperature field is a major reason for the mechanical failure of avionics* [5-7]. It is important to overcome the non-uniformity of the temperature field in the PCM-based heat sink. With the advances in processing innovation in the course of recent decades, hardware has gotten quicker, littler and all the more impressive. This outcomes in an ever-expanding heat age rate from electronic gadgets. Much of the time, the chips are cooled utilizing constrained wind current. Nonetheless, when managing a segment that contains billions of transistors working at high recurrence, the temperature can arrive at a basic level where standard cooling strategies are not adequate. Notwithstanding superior electronic chips, high heat transition evacuation is likewise required in gadgets, for example, laser diode exhibits and high-vitality mirrors. Progressed extremely enormous scope coordination (VLSI) innovation has brought about huge enhancements in the presentation of electronic frameworks in the previous decades. With the pattern toward higher circuit thickness and quicker activity speed, be that as it may, there is a consistent increment in the dissipative heat transition at the segment, module, and framework levels.

Most activity parameters of an electronic segment are emphatically influenced by its temperature just as its prompt warm condition. This prompts an expanding interest for exceptionally effective electronic cooling innovations. To fulfill this need, different electronic cooling plans have been created. Complete surveys of the diverse heat move

methods utilized in electronic cooling. The utilization of smaller scale directs in heat move was first proposed by Tuckerman in the electronic chip which could be viably cooled by methods for water stream in miniaturized scale channels manufactured on the circuit board on which the chips are mounted. The requirement for warm administration in top of the line power electronic workstations cooling, application servers and server farms is an exceedingly requesting zone that requires persistent research endeavours to create proficient and cost serious cooling arrangements.

A portion of the regularly utilized heat move liquids are the Air, ethylene glycol and motor oil for the past certain decades. The Nano liquids were first presented by Choi in the Argonne National Laboratory, USA, who found that Nano particles increment the warm conductivity of the working liquid, in this manner improving the heat move execution. Nano liquids are characterized as suspension of nanoparticles in a base liquid. Some run of the mill Nano liquids are ethylene glycol based copper Nano liquids and water based copper oxide Nano liquids, Nano liquids are weakened suspensions of functionalized nanoparticles composite materials created about 10 years back with the particular point of expanding the warm conductivity of heat move liquids, which have now advanced into a promising Nano mechanical territory.



Fig. Existing heat sink

II. LITERATURE REVIEW

S.K. Saha et.al [1] Portrayal of softening cycle in a Phase Change Material (PCM)- based heat sink with plate balance type warm conductivity enhancers (TCEs) is mathematically concentrated on in this paper. Point by point parametric investigations are performed to find the impact of angle proportion of nook and the applied intensity motion on the warm execution of the intensity sinks. Different non-layered numbers, for example, Nusselt number (Nu), Rayleigh number (Ra), Stefan number (Ste) and Fourier number (Fo) in view of a trademark length scale, are recognized as significant boundaries. The half blade thickness and the balance level are shifted to get an extensive variety of viewpoint proportions of a nook. It is observed that a solitary connection of Nu with Ra isn't material for all perspective proportions of nook with liquefy convection considered. To find suitable length scales, nooks with various angle proportions are separated into three classifications, viz. (a) shallow nook, (b) rectangular walled in area and (c) tall walled in area. Likewise, a proper trademark length scale is distinguished for each sort of nook and connection of Nu with Ra in light of that roast acteristic length scale is created.

V. Shatikian et.al [2] Intensity stockpiling limit of Phase change materials (PCMs) is enormous because of the way that it depends on the inactive intensity of dissolving. In any case the low warm conductivity of numerous forthcoming PCMs, particularly the natural ones, makes it hard to actually use this limit. To improve the pace of intensity move into PCMs, different strategies have been recommended, similar to blades, metal and diagram ite-build networks, scattered high-conductivity particles inside the PCM, and miniature exemplification. In the current work, softening of a Phase change material (PCM) in an intensity sink with a consistent intensity transition flat base and vertical inward plate blades has been concentrated mathematically. It has been shown that inside a similar math, the liquefy part relies upon a mix of the Fourier, changed Stefan and adjusted Rayleigh numbers, where the adjusted gatherings depend on the

consistent intensity transition. This outcome relates, as a general rule, to the past discoveries for the steady temperature instance of a similar con figuration. Nonetheless, apparently for a steady intensity motion at the base, balance proficiency contemplations couldn't be utilized for speculation. It is in this way proposed to represent the width impact utilizing an extra Rayleigh number, in light of the half-width of the PCM layer. The total outcomes show that a genuinely decent speculation has been gotten for the dissolve portion, while for the comparing Nusselt numbers the understanding for various cases is excellent and a relationship is recommended. The outcomes accomplished for steady temperature and steady intensity motion cases show that the proposed layered examination yields predictable outcomes in the two circumstances. In this manner, the methodology grew thus can be utilized in the plan of PCM-based cooling frameworks.

Adeel Arshad et.al [3] this trial concentrate on presents the parametric examination for the round pin-finned heat sinks exposed to consistent intensity densities for powerful and dependable cooling of versatile electronic gadgets. Phase change material (PCM) to be specific paraffin wax is taken on as energy stockpiling material and aluminum made round pin-blades are chosen as warm conductivity enhancers (TCEs). A consistent volume part of 9% of round pin-blades is chosen with pin measurement of 2mm, 3mm and 4mm and input heat transition was given from 1.6kW/m² to 3.2kW/m² with an addition of 0.4kW/m². Three volume parts of $\psi = 0.0$, $\psi = 0.5$ and $\psi = 1.0$ of PCM sum are poured in every setup of pin-finned heat sinks. An intensity sink with no balance is picked as a kind of perspective intensity sink to measure the impact of PCM and TCEs. The warm presentation of PCM filled heat sinks are dissected to investigate the impact of volumetric parts of PCM, heat densities, nail measurement to idle intensity Phase, improvement in activity time, heat limit and warm conductance. Three reference set point temperatures (SPTs) are picked and results have proven that a 3mm pin breadth heat sink has best warm execution.

Muthamil Selvan Nedumaran et.al [4] In this paper it presents Phase change materials (PCM) RT-28HC, RT-35HC, and RT-44HC with three different dissolving temperatures, 29 °C, 36 °C, and 44 °C, with comparable warm properties, are thought of. The PCM is situated from the left to right half of the intensity sink in its rising request. The blades are connected to the intensity sink longitudinally, and its direction impacts are concentrated on low (100-500 W/m²) and high (1000-5000 W/m²) heat motions applied on the even base surface of the intensity sink. A 2D model is created utilizing ANSYS Familiar 19, and the balance direction impacts are researched mathematically. The direction of balances at various points, for example, 0°, +15°, +30°, +45°, +60°, - 15°, - 30°, - 45°, - 60° are thought of. The impact of balances on the charging cycle is evaluated by contrasting a solitary and twofold PCM heat sink. Three beginning circumstances are explored by adjusting the underlying temperature 300 K, 303 K, and 310 K. At expanding heat input, the negative calculated balances have a higher liquefying rate. For various introductory circumstances, - 60° gives higher upgrade, and +60° has drawn out liquefying for practically all cases. The exhibition of a triple PCM configuration is contrasted and single and twofold PCM coun terparts under comparable circumstances.

Azeem Anzar et.al [5] The PCM based cooling methods have an extraordinary expected application in electronic gadgets. In this work study and examination of PCM based heat sinks are done. Mathematical investigation is finished by utilizing Familiar 14.0. The works remembers the review for qualities of PCM and its applications are completed. Here we led three design of intensity sinks, for example, blade loaded up with PCM material, balance loaded up with half PCM material, balance as it were .The attributes of Intensity sink with PCM is broke down in both dissolving cycle and hardening and figure out the time in which PCM controls temperature up to 2400s for full filled PCM. Execution of intensity sink for consistent activity is completed for various wind stream conditions. The time prerequisites for control the temperature of PCM for various constrained convection conditions to different fluid portion levels are arranged, which can be utilized as a simple to-utilize configuration rule for PCM based heat sinks with constrained convection.

Marta Kuta et.al [6] Expanding energy utilization in private and public structures requires advancement of new advancements for nuclear power creation and capacity. One of opportunities for the second recorded need is the utilization of Phase change materials (PCMs). This work is cantered around arrangements around here and comprises of two sections. Initial one is centered around various plans of nuclear power stockpiling (TES) tanks in light of the Phase change materials. The subsequent part is the investigation of tests results for TES tank containing rack and cylinder heat exchanger and loaded up with Phase change material. Nuclear power stockpiling tank is dissected to involve it in home-grown warming and hot utility water establishments. The point of this exploration was to check the appropriateness of Phase change material for referenced reason. Results show that utilizing Phase change materials for nuclear power stockpiling can build measure of put away intensity. The utilization of appropriately chosen PCM and heat exchanger empowers the course of nuclear power putting away and delivering to turn out to be more effective.

Bo Wu et.al [7] In this review, an orthotropic plate organized at the lower part of the Phase change material (PCM) - based heat sink is utilized to upgrade the temperature field consistency (TFU) in the intensity sink. The presentation of the orthotropic plate in upgrading the TFU is mathematically considered during the softening system of the PCM. The impacts of the orthotropic conductivity (R) are analyzed at $R = 10 R_b$, $5 R_b$, $0.2 R_b$ and $0.1 R_b$. The setup including a copper plate is likewise thought about as a difference to accomplish a more goal and more profound understanding. It is found that the orthotropic plate can essentially improve the TFU by up to multiple times in the PCM areas; it can likewise limit the temperature range in the intensity sink district. When the orthotropic conductivity is more noteworthy than R_b , it might help in working on the exhibition of warm administration of the intensity sink. Standards about the orthotropic conductivity are drawn and far reaching assessments are led to direct in planning PCM-based heat sink for warm administration of flight.

M.M. Prieto et.al [8] This paper presents an examination of the warm exhibition of a paraffin (RT60) utilized as Phase change material (PCM) in heat exchangers of a warming framework, the working temperatures of the water being around $80\text{ }^\circ\text{C}$ at the stock and $30\text{ }^\circ\text{C}$ at the return. The formed model considers the consequences of a CFD porosity model for the PCM Phase change processes, yet sums up the information on this model in helpful polynomial conditions. These conditions, combined with one-aspect conditions (1D) for the aluminum case and for the water, were carried out in a hand crafted program. The half and half CFD-1D model was applied to a module comprising of a level plate (container loaded up with 30 and 10 mm thickness of PCM) washed by water channels. The outcomes were effectively contrasted and those got from a full CFD model, the computational time dropping from a little while to a couple of moments. The application to PCM heat exchangers of volume $0.8 \times 0.6 \times 0.6\text{ m}^3$ agreeing plates courses of action (level and vertical), Phase change processes (liquefying and cementing), PCM thicknesses and it were considered to work conditions. The level course of action is quicker than the upward, the dissolving time being close to half in the previous.

S. Rahmanian et.al [9] another setup of Phase change material (PCM) heat sink has been created to be joined with a structure incorporated concentrated photovoltaic (BICPV) framework. This new proposed framework incorporates PCM epitomized in aluminum pack and drenched in nanofluid holder to work on warm conductivity. A complete mathematical model was approved and mimicked to assess warm and electrical execution of the proposed framework for both detached and dynamic cooling conditions. Two distinct arrangements of nanofluid PCM walled in areas with single PCM pack or multi-more modest packs were contrasted and traditional BICPV-PCM framework. Liquefying and hardening of PCM were additionally considered with sunlight based fixation proportion of 5. In latent cooling, single-pack arrangement managed the silicon temperature of CPV under $78\text{ }^\circ\text{C}$ with more uniform temperature dispersion. Though the multi-packs arrangement exhibited 97% Phase change to fluid PCM which gave the most noteworthy put away nuclear power. The exhibition improvement would be credited to the upgrade of warm conductivity and normal convection of nanofluid in PCM holder. Besides, in dynamic cooling condition, the silicon temperature controlled under $43\text{ }^\circ\text{C}$ with uniform appropriation. The nanofluid stream could be cemented up to 97% and 90% of at first liquefied PCM after 60 min for multi-packs and single-pack designs, separately.

Anuj Kumar et.al [10] Present trial concentrate on reports the warm exhibition of nano-improved Phase change material (NePCM) based nuclear power stockpiling framework for cooling of electronic parts. The NePCM based heat sink (HS) cooling is a latent cooling procedure that can wipe out the fan-based customary cooling strategy. A plate radiator was utilized to imitate the intensity created by microelectronics. Here, copper oxide (CuO), paraffin wax, and aluminum are considered as nanoparticle, Phase change material (PCM), and HS material, separately. Different HS designs like HS with no blade (HSNF), HS with rectangular plate balances (HSRPF), HS with square pin balances (HSSPF), and HS with roundabout pin balances (HSCPF) are read up for a proper volume part of blade material. In the present exploratory examination, different arrangements of HS like HSNF, HSCPF, HSSPF, and HSRPF implanted with various mass parts of NePCM composite are contemplated to extend the working season of electronic gadgets. Consistent volume divisions (9.0%) of balances have been utilized to guarantee an equivalent amount of PCM/NePCM. Tests are con ducted for different intensity motion values going from $1.5\text{-}3.0\text{ kW/m}^2$ and different mass part of CuO ($\phi = 0.0\text{-}3.0$). The significant ends drawn from the review are introduced beneath.

III. CONCLUSIONS

An initial study on the multiple PCMbased heat sink on electronic cooling. So, the combination of the fin with multiple PCM has been investigated. These results will be the guidelines for the upcoming study, where the number of PCM can be increased. Therefore, our main concern is employing multiple PCM for thermal management and obtaining their significance in this present work. Also, fins are placed vertically in the heat sink to enhance PCM thermal conductance.

REFERENCES

1. S.K. Saha, P. Dutta “Heat transfer correlations for PCM-based heat sinks with plate fins” [Volume 30, Issue 16](#), November 2010, Pages 2485-2491
2. V. Shatikian, G. Ziskind “Numerical investigation of a PCM-based heat sink with internal fins: Constant heat flux” *International Journal of Heat and Mass Transfer* 51 (2008)
3. Adeel Arshadl , Hafiz Muhammad Ali “Experimental Investigation of PCM based Round Pin-Fin Heat Sinks for Thermal Management of Electronics: Effect of Pin-Fin Diameter”
4. Nedumaran, M. S., Nagarajan, G., & Hooman, K. (2022). Numerical analysis of multiple phase change materials based heat sink with angled thermal conductivity enhancer. *Journal of Energy Storage*, 55, [105316]. <https://doi.org/10.1016/j.est.2022.105316>
5. Azeem Anzar, Azeem Hafiz P A, N R M Ashiq, “Heat Transfer Analysis on PCM Based Heat Sink Incorporated With Air Convection” *International Journal of Scientific & Engineering Research*, Volume 7, Issue 4, April-2016.
6. Marta Kuta^{1,*} , Dominika Matuszewska “Designs of PCM based heat exchangers constructions for thermal energy storage tanks – examples and case study for selected design” *E3S Web of Conferences* 70, 010 (2018)
7. Wu, B., Li, P., Zhang, F., Tian, F. (2021). A novel phase change material -based heat sink with an orthotropic plate to enhance the temperature field uniformity for avionics. *Journal of Mechanical Science and Technology* 35 (5) (2021) 2237~2246. <http://doi.org/10.1007/s12206-021-0440-4>
8. M.M. Prieto, I. Suárez, B. González, Analysis of the thermal performance of flat plate PCM heat exchangers for heating systems, *Applied Thermal Engineering* (2017), doi: <http://dx.doi.org/10.1016/j.applthermaleng.2017.01.065>
9. S. Rahmanian “Nanofluid-PCM heat sink for building integrated concentrated photovoltaic with thermal energy storage and recovery capability” [Sustainable Energy Technologies and Assessments Volume 46](#), August 2021, 101223
10. Anuj Kumar , Rohit Kothari, “Thermal performance of heat sink using nano-enhanced phase change material (NePCM) for cooling of electronic components” [Microelectronics Reliability Volume 121](#), June 2021, 114144



INNO SPACE
SJIF Scientific Journal Impact Factor
Impact Factor: 8.118



ISSN INTERNATIONAL
STANDARD
SERIAL
NUMBER
INDIA



INTERNATIONAL JOURNAL OF INNOVATIVE RESEARCH

IN SCIENCE | ENGINEERING | TECHNOLOGY

 **9940 572 462**  **6381 907 438**  **ijirset@gmail.com**



www.ijirset.com

Scan to save the contact details