

ISSN(O): 2319-8753

ISSN(P): 2347-6710



# International Journal of Innovative Research in Science Engineering and Technology (IJIRSET)

(A Monthly, Peer Reviewed, Refereed, Scholarly Indexed, Open Access Journal)



**Impact Factor: 8.699** 

Volume 14, Issue 8, August 2025





www.ijirset.com | A Monthly, Peer Reviewed & Refereed Journal | e-ISSN: 2319-8753 | p-ISSN: 2347-6710 |

Volume 14, Issue 8, August 2025

|DOI: 10.15680/IJIRSET.2025.1408052|

## An Experimental Study on Glass Fiber Reinforced Geopolymer Concrete

#### Harshal Harishchandra Kadu<sup>1</sup>, Somanagouda. R. Takkalaki<sup>2</sup>

PG Student, B.R. Harne College of Engineering & Technology, Mumbai, Maharashtra, India Department of Civil Engineering, B.R. Harne College of Engineering & Technology, Mumbai, Maharashtra, India

ABSTRACT: The production of Ordinary Portland Cement (OPC) concrete has high environmental impact due to significant CO<sub>2</sub> emissions. Geopolymer Concrete (GPC), made using industrial waste like fly ash from thermal power plants, offers a sustainable alternative with excellent strength and durability. Fly ash reacts with alkaline solutions (NaOH, Na<sub>2</sub>SiO<sub>3</sub>) to form a binding gel, but GPC's brittleness limits its structural use. This study investigates Glass Fiber-Reinforced GPC (GFRGPC) with fiber volume fractions of 0%, 0.1%, 0.2%, 0.3%, and 0.4%, and lengths of 6 mm, 12 mm, and 25 mm, using M30 grade GPC with 100% fly ash binder. Mechanical properties (compressive, flexural, and split tensile strength) were compared to plain GPC to evaluate the effectiveness of glass fibers in improving performance.

#### I. INTRODUCTION

Geopolymer concrete (GPC) presents a sustainable alternative to conventional Portland cement concrete, offering lower carbon emissions and effective use of industrial by-products such as fly ash. Despite its durability and strength, the brittle nature of GPC limits its ductility and cracking resistance. Fiber reinforcement—specifically glass fibers—offers a potential solution due to their high tensile strength, corrosion resistance, and cost-effectiveness. This study explores the effect of varying glass fiber content and length on the mechanical and durability properties of GPC.

#### II. LITERATURE REVIEW

Prior studies have demonstrated the benefits of glass and polymer fibers in conventional and geopolymer concretes. However, research predominantly focused on shorter fibers (≤6 mm). There remains a gap regarding the performance of longer fibers (12 mm and 25 mm) in GPC. This study addresses that gap through a comprehensive experimental evaluation.

- Geopolymer concrete's highest compressive strength observed at 60°C.
- 0.3% glass fiber volume fraction results in an 11.62% increase compared to conventional concrete.
- Tensile strength in geopolymer concrete shows a linear variation.
- Peak strength at 60°C with 0.3% glass fiber, exhibiting a 3.64% gain over conventional concrete.
- Maximum flexural strength for geopolymer concrete found at 60°C with 0.3% glass fiber.
- Strength surpasses normal concrete by 2.65% at the same volume fraction.
- Geopolymer concrete achieves maximum strength at 60°C with 0.3% glass fiber volume fraction.
- Noteworthy that concrete strength can be increased without cement, promoting an eco-friendly approach.

#### **Objectives**

- 1. To investigate the mechanical, durability, and fracture properties of glass fiber-reinforced geopolymer concrete (GFRGPC).
- 2. To optimize mix design to achieve high performance and sustainability.
- 3. To enhance strength, toughness, and resistance to environmental factors.
- 4. To contribute to advancements in sustainable construction technology.

#### Scope of Work

To study effect of glass fibres of geo polymer concrete. To compare the fly ash-based geo polymer concrete with addition of glass fibres geopolymer concrete.





www.ijirset.com | A Monthly, Peer Reviewed & Refereed Journal | e-ISSN: 2319-8753 | p-ISSN: 2347-6710

#### Volume 14, Issue 8, August 2025

#### |DOI: 10.15680/IJIRSET.2025.1408052|

#### **Problem Statement**

To study the strength parameters of geopolymer concrete with addition of glass fibers on strength of concrete. i.e. (0%, 0.1%, 0.2%, 0.3%, & 0.4%) with Varying length of Glass fiber 6 mm, 12 mm & 25 mm.

#### III. METHODOLOGY

#### Non-Destructive Test Methods

- Rebound Hammer Test: Measures surface hardness to estimate concrete strength. Higher rebound values = stronger concrete. Quick and useful for preliminary quality checks.
- Ultrasonic Pulse Velocity (UPV) Test: Measures speed of ultrasonic pulses in concrete. Higher velocity = denser, more uniform, and better-quality concrete.
- Destructive Test Methods
- $\bullet$  Compressive Strength Test: Cube specimens are loaded in a compression testing machine until failure. Formula: Fc = P / A
- Split Tensile Strength Test: Cylindrical specimens tested per IS:516-1989. Formula: Fsp =  $2P / (\pi \times D \times H)$
- Flexural Strength Test: Beam specimens tested for modulus of rupture.

#### Formulas:

- Fr = M / S
- $\bullet S = (b \times d^2) / 6$
- $M = P \times L / 4$  (for third-point loading)

#### IV. RESULTS AND DISCUSSION


Rebound Hammer: Values increased up to 0.3% fiber content, peaking at ~31.6 MPa with 25 mm fibers.

UPV: Peak velocity of 4.6 km/s at 0.3% fiber (25 mm).

Compressive Strength: Maximum of 32.3 MPa at 0.3% fiber (6 mm).

Split Tensile Strength: Increased from 2.5 MPa (control) to 3.6 MPa at 0.3% fiber (25 mm).

Flexural Strength: Peaked at 5.1 MPa at 0.3% fiber (25 mm).









www.ijirset.com | A Monthly, Peer Reviewed & Refereed Journal | e-ISSN: 2319-8753 | p-ISSN: 2347-6710 |

#### Volume 14, Issue 8, August 2025

#### |DOI: 10.15680/IJIRSET.2025.1408052|











www.ijirset.com | A Monthly, Peer Reviewed & Refereed Journal | e-ISSN: 2319-8753 | p-ISSN: 2347-6710

#### Volume 14, Issue 8, August 2025

#### |DOI: 10.15680/IJIRSET.2025.1408052|





#### V. CONCLUSION

- 1. Rebound Hammer: Increased with fiber addition; peak ~31–32 at 0.3–0.4% (25 mm fiber) → higher surface hardness & durability.
- 2. UPV: Improved for all cases; peak ~4.6–4.7 km/s at 0.3% (25 mm fiber) → excellent internal quality, fewer voids/microcracks.
- 3. Compressive Strength: Increased up to 0.3% fiber (peak  $\sim$ 37–39 MPa at 6 mm length); higher dosages gave marginal gains or slight reduction.





www.ijirset.com | A Monthly, Peer Reviewed & Refereed Journal | e-ISSN: 2319-8753 | p-ISSN: 2347-6710 |

#### Volume 14, Issue 8, August 2025

#### |DOI: 10.15680/IJIRSET.2025.1408052|

- 4. Flexural Strength: Rose with both fiber content & length; best (~5.0-5.3 MPa) at 0.3% (25 mm) due to crack bridging & ductility.
- 5. Split Tensile Strength: Improved with fibers; max (~3.6–3.8 MPa) at 0.3–0.4% (25 mm), indicating better crack resistance.3

#### REFERENCES

- 1. QURAT UL AIN, ER. SHUBHAM BHADORIYA Mechanical and Durability Properties of Glass Fiber Reinforced Geopolymer Concrete- Eur. Chem. Bull. 2023
- 2. Mazaheripour H, Ghanbarpour S, Mirmoradi SH, Hosseinpour I. The effect of polypropylene fibers on the properties of fresh and hardened lightweight self-compacting concrete, Construction and BuildingMaterials, 25(2011) 351-8.
- 3. K. Vijaia, R. Kumuthaaand B.G.Vishnuramb, "Properties of glass fibre reinforced geopolymer concrete composites". Asian journal of civil engineering (building and housing) vol. 13, no. 4 (2012) pages 511-520.
- 4. Mr.R.Balamurugan, "Experimential investigation of glass fibre reinforced geo polymer concrete".IRACST–Engineering Science and Technology: An International Journal (ESTIJ), ISSN: 2250-3498 Vol.7, No.2, Mar-April 2017.
- 5. Sundis M.S. Taher, Shireen T. Saadullah a, James H. Haido, Bassam A. Tayeh Behaviour of geopolymer concrete deep beams containing waste aggregate of glass and limestone as a partial replacement of natural sand-ELSEVIER-2021.
- 6. Menatalah A. Kotop, M.S. El-Feky, Yousef R. Alharbi, Aref A. Abadel, Abobaker S. Binyahya, Engineering properties of geopolymer concrete incorporating hybrid nano-materials ELSEVIER-2021.
- 7. Mohamed Amina, Bassam A. Tayehb,, Ibrahim saad agwaa, Investigating the mechanical and microstructure properties of fibre-reinforced lightweight concrete under elevated temperatures- ELSEVIER-2020.
- 8. Weiwen Li a, Eskinder Desta Shumuye, Tang Shiying, Zike Wang, Eco-friendly fibre reinforced geopolymer concrete: A critical review on the microstructure and long-term durability properties- ELSEVIER-2022.
- 9. Dr. Weena Lo kuge Fibre reinforced geopolymer concrete with ambient curing for in-situ applications-2014.
- 10. Dr. Mrs. S. A. Bhalchandra, Mrs. A. Y. Bhosle Properties of Glass Fiber Reinforced Geopolymer Concrete-IJMER-2013.
- 11. Kasım MERMERDAŞ, Esameddin Saeed MULAPEER, Safie Mahdi OLEIWI, Effect of glass fiber addition on the strength properties and pore structure of fly as based geopolymer composites 2019.
- 12. G. Ravichandran, M. Sivaraja, M. Jegan, M. Harihanandh, A.R. Krishnaraja, Performance of Glass fiber reinforced geopolymer concrete under varying temperature effect IJCIET- Volume 9, Issue 4, April 2018.
- 13. Mr. Kakade V.D., Dr. Kawade U. R. Review on-Glass fiber geopolymer concrete IJARIIE Vol-4 Issue-6 2018.
- 14. Mr. Kakade Vishal D, Miss. Sathe Pooja R., Glass fiber geopolymer concrete- In Association with Nonvoter Publications Journal-ISSN No: 2581-4230- February, 22nd and 23rd, 2019.











## INTERNATIONAL JOURNAL OF INNOVATIVE RESEARCH

IN SCIENCE | ENGINEERING | TECHNOLOGY







9940 572 462 🔯 6381 907 438 🔀 ijirset@gmail.com

