



International Journal of Innovative Research in Science Engineering and Technology (IJIRSET)

(A Monthly, Peer Reviewed, Refereed, Scholarly Indexed, Open Access Journal)



Impact Factor: 8.699

Volume 14, Issue 11, November 2025

Torque Response and Tip Deflection Test of Guide wires

Kothwala Dr. Deveshkumar, Patel Jayendra, Patel Akash*

Meril Medical Innovations Private Limited, Bilakhia House, Survey No.879, Muktanand Marg, Chala, Vapi,
Dist-Valsad, Gujarat, India

ABSTRACT: Guidewires are broadly used in less invasive diagnosis and treatment with the use of advanced technology and also in procedures that require accurate navigation, torque control, and flexibility. From their inception in the 1950s up to now, there has been great progress in the aspects of material and structural design; the change was from using stiff stainless steel wires to the use of very advanced composites that involve superelastic Nitinol alloys, polymer barriers, and specially designed shapes. Their mechanical performance comes mainly from two aspects: torque response and deflection of the tips, which are the two major parameters responsible for the safety of the whole procedure by determining anchorage accuracy, flexibility, and hence, safety of the entire operation.

The purpose of this review was to bring together and to assess critically the literature that already existed about the torque response and tip deflection performance of guidewires. The main point was the impact of material composition, coating technologies, and design on the mechanical efficiency and the clinical applicability of these devices. Information was collected from various sources such as peer-reviewed studies, patents, and experimental analyses which had looked into different aspects like core materials, shaft coatings, and flexibility parameters.

The evidence reviewed points out that guidewires made of stainless steel offer the best torque transmission and pushable property, while Nitinol guidewires are more flexible, have better kink resistance, and recover elastically more. The torque transmission efficiencies that have been reported are usually more than around 85%, which varies with the elastic modulus, manufacturing accuracy, and coating quality.

It is concluded that standardized mechanical testing is indispensable for trustworthy performance evaluation and comparisons among the types of guidewire. The future is likely to bring about breakthroughs with the use of hybrid alloys, nano-structured coatings, and smart designs optimized through computational methods, possibly even adding sensor feedback systems for real-time adaptability, which would ultimately lead to better safety and higher efficiency in minimally invasive procedures.

KEYWORDS: Guidewires, Torque Response, Tip Deflection; Nitinol, Stainless Steel, Hydrophilic Coating, Mechanical Performance, Minimally Invasive Procedures

I. INTRODUCTION

Guidewires are crucial elements during minimally invasive operations which need accurate routing through tortuous anatomical paths [1]. The mid-twentieth century witnessed the first use of guidewires, which were merely stainless-steel rods; today, however, they are made of complex materials and are designed to impress not only by their versatility but also by their wide range of applications, coatings, and modifications. The progress has been dictated by the requirements of the medical field for increased pliability, torque management, and compatibility with body tissues for safe and effective penetrating the delicate anatomy [2].

The overall performance of a guidewire is primarily governed by two key mechanical parameters: torque response and tip deflection [3]. Torque response defines the extent to which rotational motion applied at the proximal end is transmitted to the distal tip, directly influencing navigational precision and operator control [4]. A high torque response ensures accurate translation of hand motion, minimizing processing errors and the risk of vessel trauma [5]. Conversely, inadequate torque transmission may result in lag or overshoot at the distal end, compromising clinical safety [6]. Tip deflection, on the other hand, characterizes the distal flexibility of the guidewire, determining its ability

to conform to tortuous or curved pathways while minimizing stress on surrounding tissues [7]. Collectively, these parameters dictate a guidewire's steer ability, responsiveness, and overall safety during complex interventions [8].

Over time, progress in guidewire capability has been realized by means of innovations in material composition (moving from stainless steel to superelastic Nitinol), surface treatments (like hydrophilic or polymer layers applied to increase glide), and core wire configurations (featuring tapered or graded stiffness designs). Nevertheless, the performance of commercially available guidewires varies a lot, and this is mainly due to differences in materials, designs, and methods used to make them [9]. Existing studies on these aspects remain dispersed and often employ non-standardized testing protocols, limiting direct comparison and comprehensive understanding across designs and materials [10].

Although numerous experimental studies have explored guidewire materials and designs, the mechanical interplay between torque response, flexibility, and clinical performance remains insufficiently consolidated [11]. A critical synthesis of these factors is necessary to establish standardized benchmarks for evaluating guidewire performance and to guide future innovations in material and structural optimization [11].

This review therefore aims to systematically summarize and analyze existing knowledge under five major themes: material composition, structural design, surface coatings, performance evaluation, and future innovations [12]. By integrating mechanical insights with design and functional characteristics, this review seeks to bridge the gap between experimental evaluation and clinical applicability, providing a framework for the development of next-generation guidewires with superior precision, adaptability, and procedural safety.




Fig 01. Schematic Illustration of Torque Response in a Guidewire




Fig 02. Schematic Illustration of Tip Deflection in a Guidewire

II. METHODOLOGY

Literature Search Strategy

This entire review was intended as a means to gather and scrutinize the existing literature on the torque response and tip deflection characteristics of guide wires for medical use in minimally invasive procedures with special mention of Endoscopic Retrograde Cholangiopancreatography (ERCP) and Endoscopic Ultrasound-Guided Biliary Drainage

(EUS-BD). An extensive search in the literature was done through recognized scientific databases like PubMed, Scopus, Google Scholar, and Science Direct from the year 2000 to 2024 [13]. The inclusion criteria were defined as peer-reviewed research papers, review articles, and patents that were dealing with mechanical behavior, structural design, or material properties of guide wires [14]. Studies were excluded if they were not in English, lacked technical details or measurable outcomes, or were editorial summaries without experimental or analytical context [15].

Selection Criteria

All publications that were retrieved were examined to determine their relevance based on the titles, abstracts, and the availability of the full text. Publications were included in the selection process if they were concerned with the mechanical or structural assessments of guide wires, which also consisted of different materials (e.g., Nitinol and stainless steel) or design variations such as core wire diameter, shaft coating, or tip flexibility [16] being compared. Moreover, review articles presenting comparative discussions on guide wire performance and patents delineating novel guide wire designs were also considered to ensure a comprehensive understanding of both scientific and industrial advancements. Studies that only provided clinical case reports without mechanical discussion were excluded [17].

Data Extraction and Analysis

Data from the selected sources were extracted qualitatively, focusing on key mechanical parameters relevant to guide wire performance [18]. These included torque response rate (TRR), tip deflection characteristics, core wire diameter (CWD), shaft coating type, material composition, and design elements influencing flexibility, stiffness, and torque transmission. Each article's findings were summarized and compared to identify common trends, design influences, and material–performance relationships. The extracted information was synthesized qualitatively to provide an integrated understanding of how material composition, design parameters, and coating types influence torque response and tip deflection characteristics in guide wires [19].

III. CURRENT STATE OF THE ART

3.1 Overview of Existing Devices and Technologies

A guidewire is a primary element in minimally invasive surgeries that need very careful navigation through difficult anatomical pathways, for instance, Endoscopic Retrograde Cholangiopancreatography (ERCP) and Endoscopic Ultrasound-Guided Biliary Drainage (EUS-BD). In the past, decades of guidewire development have witnessed a major change in its technology—from stiff stainless steel constructions to composite systems with Nitinol kernels, polymer coatings, and multilayered structures that are purposely made to balance the torque response and flexibility [20].

Recent research has outlined different types of guidewires with the main purpose of improving control in navigation, transmission of torque, and safety [21]. The present-day guidewires mostly use coatings that are hydrophilic or based on polymers to improve lubricity, in addition to tapered or dual-core configurations to enhance torque transmission and distal flexibility. All these design advancements together bring about the advantages of easier handling, lesser friction, and safer movement through difficult anatomical locations [22].

3.2 Technological Advancements

The development of guidewires has gone through a considerable technological advancement due to breakthroughs in material science, surface engineering, and structural optimization [11]. The use of superelastic Nitinol and hybrid dual-core constructions has resulted in better flexibility, kink resistance, and fatigue strength, all the while providing good torque control. The implementation of different stiffness along the length of the wire created by tapered shapes or varying core diameters helps to reduce rotational lag and thus improve the efficiency of torque transfer from the proximal to the distal end.

The development of surface coating technologies has not only focused on better clinical, but also better mechanical performance [23]. The modern hydrophilic and nanocomposite coatings have been known to bring down frictional resistance, better biocompatibility and less mucosal trauma during navigation. Studies have given torque transmission efficiencies approaching 85–90% which imply a large amount of optimization in the mechanism of the recent designs. According to comparative research, the torque precision and push ability of the stainless-steel guidewires are generally rated as superior, while the Nitinol-based wire designs are said to have the benefits of greater elasticity, kink resistance, and shape recovery[24]. The trend towards hybrids or composites is showing no signs of abating as the manufacturers

are keen to combine these virtues, the ultimate goal being to find an ideal torque control and flexibility mix that can be applied to even the most complex clinical situations.

3.3 Regulatory and Clinical Landscape

Under the regulations of the U.S. Food and Drug Administration (FDA) and the European Union Medical Device Regulation (EU MDR), the endoscopic and vascular guidewires are considered Class II medical devices. The majority of such devices receive approval through the FDA 510(k) process or CE marking in compliance with ISO 11070, which lays down the criteria for safety, mechanical performance, and biocompatibility.

The existing regulatory frameworks have not eliminated the considerable differences in mechanical testing methods used by manufacturers, especially in the assessment of capability to transmit torque and the evaluation of flexibility [25]. The lack of uniform evaluation protocols is a barrier to the performance data comparisons across the different designs. Moreover, there are still very few clinical trials that have correlated the laboratory mechanical properties with the procedural outcomes which points to the necessity for more clinical validation.

Future developments should primarily be directed towards the development of uniform testing methods, evaluations of long-term durability, and conducting multi-center clinical trials in order to create strong benchmarks for the performance of guidewires. The data would be made more comparable, clinical safety would be improved, and the next generation of guidewires would be developed based on the results of such studies.

IV. MECHANISM OF ACTION AND DESIGN CONSIDERATIONS

Design Principles

Guidewires are engineered to transmit rotational and axial forces from the operator's hand to the distal tip while maintaining flexibility sufficient to navigate complex anatomical structures [11]. The core of the guidewire is typically composed of Nitinol or stainless steel, materials selected for their contrasting mechanical properties [26]. Nitinol provides super elasticity and kink resistance, whereas stainless steel offers greater torsional rigidity and torque control [27]. The distal segment is commonly equipped with a radiopaque spring coil to improve fluoroscopic visibility, while polymer or hydrophilic coatings are applied along the shaft to enhance lubricity and reduce frictional resistance. In advanced designs, tapered or dual-core configurations are utilized to provide a gradient in stiffness, allowing for both proximal torque stability and distal flexibility. These structural and material optimizations enable precise rotational control and minimize trauma during insertion [28].

Performance and Efficacy

Performance evaluation of guidewires is based on parameters such as torque transmission efficiency, tip deflection force, kink resistance, and recovery time after deformation. Preclinical bench testing has demonstrated that Nitinol-based guidewires exhibit superior flexibility and recoverability compared to stainless steel variants, whereas stainless steel wires demonstrate higher torque response and faster tips movement [29]. Reported torque transmission efficiencies for high-performance guidewires typically exceeds to approx 85–90%, with tip deflection values below 4.0 mm at standardized bending loads [30].

Through limited trials, the findings that guidewires with optimized torqueability and tip design reduce cannulation time and the risk of tissue injury, hence, improving procedural outcomes have been supported by observational studies [31]. This indicates that the mechanical properties of guidewires are one of the main factors dictating their effectiveness, safety, and overall handling in endoscopic and vascular procedures.

Comparative Analysis

Comparison with Existing Devices

Comparative assessments of guidewires have highlighted different torque response, flexibility, and overall handling characteristics of various brands and designs [32]. Typically Nitinol-based guidewires have higher elastic recovery and kink resistance, while stainless steel ones have better torque control and push ability. However, both types still have drawbacks. Nitinol wires might show more torque insensitivity, and stainless steel ones might lead to the need of overcoming more tissue resistance during manipulation [33]. Hence, the proper guidewire is still determined by the

specific requirements of the procedure and the preference of the operator, considering the trade-off between stiffness for support and flexibility for safe navigation.

Cost and Accessibility

The costs incurred in manufacturing guidewires differ according to the materials used, the technology employed in the coating, and the difficulty of the fabrication process [32]. Nitinol-based guidewires are usually the most expensive among the different types, mainly because of the specialized processing needed for the superelastic alloy, while stainless steel guidewires are not so pricey and yet provide less flexibility. Market research reports highlight that the US, Japan, and Europe are the main regions where the guidewire industry is heavily populated by manufacturers, with the products being ready for both endoscopic and vascular interventions on a wide scale [25]. The high-priced high-performance guidewires, on the other hand, by delivering outstanding clinical outcomes and lower complication rates, put their usage in advanced procedures to be fully justifiable. Accessibility, however, is still a problem in the developing areas where the factors are cost and limited distribution channels; nevertheless, as global production and the standardization of technology continue to rise, the cost and availability in those regions are expected to improve very soon.

Table1. Comparative Overview of Nitinol and Stainless-Steel Guide wires

Parameter	Nitinol-Based Guidewires	Stainless-Steel Guidewires
Material Property	Superelastic, shape-memory alloy	High-strength, rigid alloy
Flexibility	Excellent; navigates tortuous paths easily	Moderate; higher tissue resistance
Torque Response	Moderate; slight lag due to elasticity	High; precise and immediate control
Elastic Recovery	Excellent; fully restores shape after stress	Limited; prone to permanent bend
Kink Resistance	High; resistant to deformation	Moderate; may kink under load
Push ability	Moderate; lower axial support	Excellent; strong pushing force
Surface Coating	Hydrophilic or polymer coatings	PTFE or hybrid coatings
Durability	High fatigue resistance	Lower fatigue resistance
Manufacturing	Complex; costly alloy processing	Simple; lower fabrication cost
Cost	Higher production cost	More economical
Preferred Use	Flexible navigation in complex anatomy	High torque and firm procedural control
Examples	Terumo Glidewire™, Hydra Jagwire™	Olympus VisiGlide™, Cook Metro™

Challenges and Limitations

Although significant advancements have been achieved in guidewire technology, several challenges continue to limit complete optimization of their mechanical and clinical performance [34]. Material limitations remain a critical issue, as Nitinol and stainless steel each present trade-offs between flexibility, stiffness, and torque transmission [35]. Inconsistencies in manufacturing such as variable core alignment, coating thickness, and weld uniformity have been reported to cause unpredictable torque response and mechanical fatigue over time.

Clinical barriers persist due to the lack of standardized correlations between bench-top mechanical testing and in vivo performance. While torque response and tip deflection can be accurately quantified under laboratory conditions, their

translation to real procedural outcomes remains poorly established [36]. Regulatory challenges further complicate development, as current international standards do not provide uniform testing methods, leading to discrepancies in performance evaluation across manufacturers [37]. Moreover, substantial gaps in research remain regarding the long-term durability, coating stability, and fatigue resistance of guidewires under repetitive clinical use [38].

V. FUTURE PERSPECTIVES

Future improvements in guidewire technology are expected to emerge through the application of advanced materials and intelligent design strategies. The integration of shape-memory alloys, nanocomposite coatings, and graded stiffness structures is anticipated to enhance both torque transmission and flexibility while reducing the risk of vessel trauma. Computational modeling techniques, such as finite element analysis (FEA) and computational fluid structure interaction (FSI) simulations are likely to accelerate design optimization and reduce reliance on empirical testing.

Emerging innovations, including sensor-integrated guidewires and MEMS-based systems, may provide real-time feedback on torque, stress, and positioning during procedures, improving clinical precision. Furthermore, incorporation of artificial intelligence (AI) for predictive motion control and navigation is projected to redefine next-generation devices. Future research should focus on establishing standardized testing protocols, evaluating long-term fatigue performance, and conducting multicenter clinical validations to bridge the gap between laboratory data and clinical efficacy.

VI. CONCLUSION

The mechanical behavior of guidewires, which is mainly characterized by torque response and tip deflection, has been recognized as a key determinant of procedural safety and efficiency. The review has shown that the overall performance is greatly influenced by core material selection, coating technology, and geometric design. Nitinol-based guidewires are known for their greater flexibility and kink resistance while stainless-steel ones are acknowledged for their better torque precision and support.

Although progress has been made, the lack of testing methodologies that are standard across the board and insufficient clinical validation still pose limitations to the complete optimization of the performance of medical devices. However, innovations in material sciences combined with the developments in computational modeling and smart sensing technologies will more or less dictate the direction taken by guidewires in terms of their being highly precise and adaptable and with the functionality of being patient-specific. The combination of these innovations with strong regulatory frameworks and clinical validation will be the ultimate factor in determining the next generation of guidewires that will provide superior control, safety, and reliability across a wide range of interventional applications.

REFERENCES

1. Hwang J, Kim JY, Choi H. A review of magnetic actuation systems and magnetically actuated guidewire-and catheter-based microrobots for vascular interventions. *Intelligent Service Robotics*. 2020 Jan;13(1):1-4.
2. Heng W, Solomon S, Gao W. Flexible electronics and devices as human-machine interfaces for medical robotics. *Advanced Materials*. 2022 Apr;34(16):2107902.
3. Clayman M, Uribe CA, Eichel L, Gordon Z, McDougall EM, Clayman RV. Comparison of guide wires in urology. Which, when and why?. *The Journal of urology*. 2004 Jun;171(6 Part 1):2146-50.
4. Howard IS, Ingram JN, Wolpert DM. A modular planar robotic manipulandum with end-point torque control. *Journal of neuroscience methods*. 2009 Jul 30;181(2):199-211.
5. Duan W, Akinyemi T, Du W, Ma J, Chen X, Wang F, Omisore O, Luo J, Wang H, Wang L. Technical and clinical progress on robot-assisted endovascular interventions: A review. *Micromachines*. 2023 Jan 12;14(1):197.
6. Madhani AJ. *Design of teleoperated surgical instruments for minimally invasive surgery* (Doctoral dissertation, Massachusetts Institute of Technology).
7. Abdelaziz ME, Tian L, Hamady M, Yang GZ, Temelkuran B. X-ray to MR: The progress of flexible instruments for endovascular navigation. *Progress in Biomedical Engineering*. 2021 Aug 2;3(3):032004.

8. Stone GW, Reifart NJ, Moussa I, Hoyer A, Cox DA, Colombo A, Baim DS, Teirstein PS, Strauss BH, Selmon M, Mintz GS. Percutaneous recanalization of chronically occluded coronary arteries: a consensus document: part II. *Circulation*. 2005 Oct 18;112(16):2530-7.
9. Connolly T, McHugh PE, Bruzzi M. A review of deformation and fatigue of metals at small size scales. *Fatigue & Fracture of Engineering Materials & Structures*. 2005 Dec;28(12):1119-52.
10. Luo Y, Abidian MR, Ahn JH, Akinwande D, Andrews AM, Antonietti M, Bao Z, Berggren M, Berkey CA, Bettinger CJ, Chen J. Technology roadmap for flexible sensors. *ACS nano*. 2023 Mar 9;17(6):5211-95.
11. Tóth GG, Yamane M, Heyndrickx GR. How to select a guidewire: technical features and key characteristics. *Heart*. 2015 Apr 15;101(8):645-52.
12. Rasouli R, Barhoum A, Uludag H. A review of nanostructured surfaces and materials for dental implants: surface coating, patterning and functionalization for improved performance. *Biomaterials science*. 2018;6(6):1312-38.
13. Yang K, Meho LI. Citation analysis: a comparison of Google Scholar, Scopus, and Web of Science. *Proceedings of the American Society for information science and technology*. 2006;43(1):1-5.
14. Bruni A, Serra FG, Derigibus A, Castroflorio T. Shape-memory polymers in dentistry: systematic review and patent landscape report. *Materials*. 2019 Jul 10;12(14):2216.
15. Yang YT, Wu WC. Digital storytelling for enhancing student academic achievement, critical thinking, and learning motivation: A year-long experimental study. *Computers & education*. 2012 Sep 1;59(2):339-52.
16. Duerig T, Pelton A, Stöckel DJ. An overview of nitinol medical applications. *Materials Science and Engineering: A*. 1999 Dec 15;273:149-60.
17. Riley DS, Barber MS, Kienle GS, Aronson JK, von Schoen-Angerer T, Tugwell P, Kiene H, Helfand M, Altman DG, Sox H, Werthmann PG. CARE guidelines for case reports: explanation and elaboration document. *Journal of clinical epidemiology*. 2017 Sep 1;89:218-35.
18. Bellazzi R, Ferrazzi F, Sacchi L. Predictive data mining in clinical medicine: a focus on selected methods and applications. *Wiley Interdisciplinary Reviews: Data Mining and Knowledge Discovery*. 2011 Sep;1(5):416-30.
19. Lee MH, Nicholls HR. Review Article Tactile sensing for mechatronics—a state of the art survey. *Mechatronics*. 1999 Feb 1;9(1):1-31.
20. Cornejo J, Cornejo-Aguilar JA, Vargas M, Helguero CG, Milanezi de Andrade R, Torres-Montoya S, Asensio-Salazar J, Rivero Calle A, Martínez Santos J, Damon A, Quiñones-Hinojosa A. Anatomical Engineering and 3D printing for surgery and medical devices: International review and future exponential innovations. *BioMed research international*. 2022;2022(1):6797745.
21. Eandi JA, Hu B, Low RK. Evaluation of the impact and need for use of a safety guidewire during ureteroscopy. *Journal of endourology*. 2008 Aug 1;22(8):1653-8.
22. Gu H, Möckli M, Ehmke C, Kim M, Wieland M, Moser S, Bechinger C, Bohler Q, Nelson BJ. Self-folding soft-robotic chains with reconfigurable shapes and functionalities. *Nature Communications*. 2023 Mar 7;14(1):1263.
23. Fotovvati B, Namdari N, Dehghanghadikolaei A. On coating techniques for surface protection: A review. *Journal of Manufacturing and Materials processing*. 2019 Mar 25;3(1):28.
24. Fu Y, Liu H, Huang W, Wang S, Liang Z. Steerable catheters in minimally invasive vascular surgery. *The International Journal of Medical Robotics and Computer Assisted Surgery*. 2009 Dec;5(4):381-91.
25. Gomes P. Surgical robotics: Reviewing the past, analysing the present, imagining the future. *Robotics and Computer-Integrated Manufacturing*. 2011 Apr 1;27(2):261-6.
26. Clayman M, Uribe CA, Eichel L, Gordon Z, McDougall EM, Clayman RV. Comparison of guide wires in urology. Which, when and why?. *The Journal of urology*. 2004 Jun;171(6 Part 1):2146-50.
27. Kujala S. Biocompatibility and biomechanical aspects of Nitinol shape memory metal implants. University of Oulu; 2003 Nov 7.
28. Martz EO, Goel VK, Pope MH, Park JB. Materials and design of spinal implants—a review. *Journal of Biomedical Materials Research*. 1997 Sep;38(3):267-88.
29. Alipour S, Taromian F, Ghomi ER, Zare M, Singh S, Ramakrishna S. Nitinol: From historical milestones to functional properties and biomedical applications. *Proceedings of the Institution of Mechanical Engineers, Part H: Journal of Engineering in Medicine*. 2022 Nov;236(11):1595-612.
30. Su H, Kwok KW, Cleary K, Iordachita I, Cavusoglu MC, Desai JP, Fischer GS. State of the art and future opportunities in MRI-guided robot-assisted surgery and interventions. *Proceedings of the IEEE*. 2022 May 3;110(7):968-92.
31. Tse F, Yuan Y, Moayyedi P, Leontiadis GI. Guide wire-assisted cannulation for the prevention of post-ERCP pancreatitis: a systematic review and meta-analysis. *Endoscopy*. 2013 Aug;45(08):605-18.

32. Clayman M, Uribe CA, Eichel L, Gordon Z, McDougall EM, Clayman RV. Comparison of guide wires in urology. Which, when and why?. The Journal of urology. 2004 Jun;171(6 Part 1):2146-50.
33. Duerig T, Pelton A, Stöckel DJ. An overview of nitinol medical applications. Materials Science and Engineering: A. 1999 Dec 15;273:149-60.
34. Su H, Kwok KW, Cleary K, Iordachita I, Cavusoglu MC, Desai JP, Fischer GS. State of the art and future opportunities in MRI-guided robot-assisted surgery and interventions. Proceedings of the IEEE. 2022 May 3;110(7):968-92.
35. Helmus MN, editor. Biomaterials in the design and reliability of medical devices. Springer Science & Business Media; 2003 Jan 31.
36. Ma R, Slocum Jr AH, Sung E, Bean JF, Culpepper ML. Torque measurement with compliant mechanisms. Journal of Mechanical Design. 2013 Mar 1;135(3):034502.
37. Miller WG, Jones GR, Horowitz GL, Weykamp C. Proficiency testing/external quality assessment: current challenges and future directions. Clinical Chemistry. 2011 Dec 1;57(12):1670-80.
38. Maguire PD, McLaughlin JA, Okpalugo TI, Lemoine P, Papakonstantinou P, McAdams ET, Needham M, Ogwu AA, Ball M, Abbas GA. Mechanical stability, corrosion performance and bioresponse of amorphous diamond-like carbon for medical stents and guidewires. Diamond and Related materials. 2005 Aug 1;14(8):1277-88.



INTERNATIONAL
STANDARD
SERIAL
NUMBER
INDIA



INTERNATIONAL JOURNAL OF INNOVATIVE RESEARCH

IN SCIENCE | ENGINEERING | TECHNOLOGY

 9940 572 462  6381 907 438  ijirset@gmail.com



www.ijirset.com

Scan to save the contact details